手性酞菁的合成及其绝对构型

王康^a 王海龙^a 约翰·马克^b 李文军^a
小林长夫^{*,b} 姜建壮^{*,a}

(^a 北京科技大学化学与生物工程学院 功能分子与晶态材料科学与应用北京市重点实验室 北京 100083)

(^b 日本东北大学理学院化学系 仙台 980-8578)

摘要 在锂存在的条件下在正戊醇中回流环化四聚相应的光学活性的前驱体联二萘[2,1-*e*:1',2'-*g*][1,4]二羟基-5,6-邻苯二酞, 然后用醋酸酸化处理, 合成了一对对映的四个联二萘酚基团取代的手性自由酞菁四(联二萘[1,2-*e*:1',2'-*g*]-1,4-二羟基)[2,3-*b*:2',3'-*k*;2'',3''-*t*:3'''-*c'*]酞菁(**1**), 并利用一系列的光谱学方法以及元素分析表征了这种新型的手性酞菁化合物. 单晶 X 衍射分析确定了两种对映体的绝对构型, 从而阐明了自由酞菁(**1**)的手性分配.

关键词 酞菁; 手性; 光学活性; 绝对构型; 单晶 X 衍射分析

Chiral Phthalocyanine with Unambiguous Absolute Molecular Structures for Both Enantiomers

Wang, Kang^a Wang, Hailong^a Mack, John^b Li, Wenjun^a
Kobayashi, Nagao^{*,b} Jiang, Jianzhuang^{*,a}

(^a Beijing Key Laboratory for Science and Application of Functional Molecular and Crystalline Materials, Department of Chemistry, University of Science and Technology Beijing, Beijing 100083, China)

(^b Department of Chemistry, Graduate School of Science, Tohoku University, Sendai 980-8578, Japan)

Abstract (*R*)- and (*S*)-Enantiomers of chiral metal free tetrakis(dinaphtho[1,2-*e*:1',2'-*g*]-1,4-dioxocine)-[2,3-*b*:2',3'-*k*;2'',3''-*t*:2''',3'''-*c'*]phthalocyanine (**1**) were synthesized via a cyclic tetramerization of the corresponding optically active benzo[*b*]dinaphtho[2,1-*e*:1',2'-*g*][1,4]dioxocine-5,6-dicarbonitrile (**2**) in refluxing *n*-pentanol in the presence of lithium followed by treatment with acetic acid. This novel chiral phthalocyanine compound has been characterized by a series of spectroscopic methods in addition to elemental analysis. The absolute molecular structures of both enantiomers have been unambiguously elucidated by single crystal X-ray diffraction analysis, resulting in the direct assignment of the chirality of metal free phthalocyanine **1**.

Keywords phthalocyanine; chiral; optically active; absolute molecular structure; single crystal X-ray diffraction analysis

1 Introduction

In close association with the significance of chiral porphyrin derivatives like cytochrome P-450 and chlorophylls for life science, chiral porphyrinoids have been extensively studied for more than five decades.^[1] Chiral phthalocyanines, the most important synthetic analogues of porphyrins, have potential applications in various fields including chiral recognition,^[2] chiral memory,^[3] and asymmetric catalysis.^[4] Alkoxy and thioalkyl substituents with chiral carbon atoms were first introduced onto the phthalocyanine periphery as far back as 1988.^[5] Despite the absence of significant circular dichroism (CD) intensity across much of the typical electronic absorption range for

phthalocyanines, introducing these chiral substituents onto the ligand periphery has become one of the most widely used approaches for preparing chiral phthalocyanines.^[6] In 1990s, a number of optically active phthalocyanines were prepared by incorporating binaphthyl units at the peripheral or nonperipheral positions of the fused benzene rings.^[7] Optically active mixed (phthalocyaninato)-(porphyrinato) rare earth double-decker complexes have also been prepared by this group, by incorporating one of these chiral phthalocyanine ligands.^[8] Optically activity has even been successfully induced into bis(phthalocyaninato) rare earth double-decker complexes using this approach.^[9] During a systematic study of a series of racemic mixtures of chiral heteroleptic (phthalocya-

* E-mail: jianzhuang@ustb.edu.cn; nagaok@m.tohoku.ac.jp; Fax: (0086)-010-62332462.

Received May 31, 2012; published July 18, 2012.

Supporting information for this article is available free of charge via the Internet at <http://sioc-journal.cn>.

Project supported by the National Natural Science Foundation of China, the National Ministry of Science and Technology of China (No. 2012CB224801), Fundamental Research Funds for the Central universities of Ministry of Education of China, Beijing Municipal Commission of Education, Grant-in-Aid for Scientific Research on Innovative areas (No. 20108007, "pi-Space"), Scientific Research (B) (No. 23350095).

项目受国家自然科学基金(No. 2012CB224801)、教育部重点学校基础研究基金、北京市教育委员会和日本教育部科学创新基金(No. 20108007)及科学研究基金(B)(No. 23350095)的资助。

nine*)(tetrapyrrole) rare earth double-decker complexes (where phthalocyanine* represents the C_s isomer),^[10] we reported the optical resolution of a mixed (phthalocyaninato)(porphyrinato) rare earth double-decker complexes.^[11] However, there still lacks straightforward elucidation on the relationship between the absolute molecular structure and chirality for the optically active phthalocyanine derivatives owing to the incomplete separation and/or structural characterization of corresponding enantiomers despite the in depth theoretical treatment based on the observed CD signal in the Q and Soret band regions.

In this paper, we describe the synthesis and characterization of a novel chiral metal free tetrakis(dinaphtho-[1,2-*e*:1',2'-*g*]-1,4-dioxocine)[2,3-*b*;2',3'-*k*;2'',3''-*t*;2''',3'''-*c'*] phthalocyanine (**1**), Scheme 1. The structures of both (*R*)-**1** and (*S*)-**1** have been characterized by single crystal X-ray diffraction analysis and this enables the straightforward and unambiguous elucidation of the chirality of optically active phthalocyanine compound.

2 Results and discussion

2.1 Synthesis and characterization

The chiral benzo[*b*]dinaphtho[2,1-*e*:1',2'-*g*][1,4] dioxocine-5,6-dicarbonitrile (**2**) precursors were prepared by a simple one-step procedure from 4,5-dichlorophthalonitrile and (*R*)/(*S*)-1,1'-binaphthyl-2,2'-diol with K_2CO_3 in DMF,

Scheme 1. The (*R*)- and (*S*)-enantiomers of **1** were then prepared and isolated in relatively good yield based on a cyclic tetramerization of (*R*)- and (*S*)-**2**, respectively, in refluxing *n*-pentanol in the presence of lithium followed by treatment with acetic acid.

Satisfactory elemental analysis results were obtained for both enantiomers and further characterization was carried out by MALDI-TOF mass, NMR, electronic absorption, and IR spectroscopy. The MALDI-TOF mass spectra of (*R*)-**1** and (*S*)-**1** contains intense signals for the molecular ion $[M+3H]^+$ and a dimeric ion $[2M+4H]^+$. The isotopic patterns closely match the simulated ones, Figure S1 (Supporting Information). The NMR spectra and single crystal X-ray diffraction analyses are consistent with this result.

As would normally be expected, the two enantiomers have identical NMR, electronic absorption, and IR spectroscopic spectra. Only the data for the (*R*)-**1** are, therefore, discussed. Figure 1(a) shows the 1H NMR spectrum of **1** recorded in $CDCl_3$ at a concentration of $ca. 2.0 \times 10^{-3}$ mol/L. This appears somewhat surprising at the first glance due to the presence of two Pc α proton singlet signals at δ 9.29 and 7.84, despite the D_2 molecular symmetry. A similar pattern is also observed for each of the six protons of peripherally linked binaphthyl substituents, Table 1. However, this phenomenon could be easily rationalized based on the formation of a pseudo double-decker supramolecu-

Scheme 1 Synthesis of (*R*)- and (*S*)-enantiomers of metal free phthalocyanine **1**

Table 1 ^1H NMR data (δ) for **1** recorded in CDCl_3 with the concentration of $ca. 2.0 \times 10^{-3}$ mol/L at 20°C

Pc H _a	H _a	H _b	H _c	H _d	H _e	H _f	NH
9.29 (s, 4H)	8.62 (d, 4H)	8.48 (d, 4H)	7.33 (d, 4H)	7.50 (m, 4H) ^a	7.45 (m, 4H) ^a	7.97 (d, 4H)	—4.25 (s, 2H)
7.84 (s, 4H)	7.71 (d, 4H)	6.86 (d, 4H)	7.10 (d, 4H)	6.97 (t, 4H)	7.22 (4H) ^b	7.87 (d, 4H)	

^a These signals overlap with each other. ^b This signal is overlapped by the strong bands of CHCl_3 .

lar structure with the C_2 symmetry due to molecular aggregation. Actually similar NMR spectroscopic feature was observed in the ^1H NMR spectrum of a bis(phthalocyaninato) yttrium compound with a C_4 symmetry double-decker structure.^[12] Nevertheless, the pseudo double-decker supramolecular structure with C_2 symmetry formed by two phthalocyanine molecules of **1** in CHCl_3 at relatively high concentration depending on π - π interaction is supported by single crystal X-ray diffraction analysis result as detailed below. As shown in Figure 1 and Table 1, the four doublets at δ 8.62, 8.48, 7.71 and 6.86, which are correlated with each other in the ^1H - ^1H COSY spectrum, Figure 1(b), are assigned to the four protons in the benzene rings close to the Pc π -system, while the two sets of signals at δ 7.96, 7.22, 7.10, 6.97 and δ 7.87, 7.45—7.51, 7.33 are assigned to the protons on the outer set of benzene rings. Actually, along with decreasing the concentration of this compound in CDCl_3 to 2.0×10^{-4} mol/L, new proton signals due to the monomeric species could be observed. As can be seen in Figure S2 (Supporting Information), the singlet signal appearing at δ 9.44 is assigned to the Pc α proton of the monomeric species of **1**, while the signals for the protons in the naphthalene are overlapped with those of dimeric species of the same compound in the range of δ 7.0—8.2. According to the integral of the singlet signal at δ 9.44 for the monomer (M) and the one at δ 9.29 for the dimer (D) species, the equilibrium constant, K_D , for dimerization Eq. (1) can then be derived by the Equations (a—c) as detailed below.

$$I_M/I_D = [\text{M}]/[\text{D}] \quad (\text{a})$$

$$C_t = [\text{M}] + 2[\text{D}] \quad (\text{b})$$

$$K_D = [\text{D}]/[\text{M}]^2 \quad (\text{c})$$

where I_M and I_D denote the integral of the singlet signal at δ 9.44 for the monomer and the singlet signal at δ 9.29 for the dimer, respectively, measured by quantitative ^1H NMR method,^[13] C_t is the total concentration of **1**. As summarized in Table S1 (Supporting Information), the equilibrium constant K_D , 1.1×10^4 , was obtained at 20°C for this compound in CHCl_3 .

Vibrational spectroscopy has proven to be a useful and versatile technique for studying the intrinsic properties of phthalocyanine compounds. The IR spectrum of **1**, Figure S3 (Supporting Information), is dominated by bands that are associated with the central aromatic Pc macrocycle, such as the wagging and torsion vibrations of C—H groups, and the isoindole and C=N aza group stretching vibrations.^[14] The weak peak observed at 3296 cm^{-1} is obviously due to the asymmetrical isoindole N—H

Figure 1 ^1H NMR (a) and ^1H - ^1H COSY (b) spectra of **1** recorded in CDCl_3 at a concentration of $ca. 2.0 \times 10^{-3}$ mol/L. * denotes a solvent impurity

stretching vibration.^[15] Nevertheless, the observation of peaks at 3053 , 2916 and 2851 cm^{-1} was unexpected and can be attributed to the asymmetric and symmetric C—H stretching vibrations of alkyl groups due to solvated *n*-hexane and chloroform molecules contained in the crystalline samples as detailed below.

2.2 Structural studies

Single crystals of (*R*)-**1** and (*S*)-**1** suitable for X-ray analysis were obtained by slow diffusion of *n*-hexane into CHCl_3 solutions. This enables unambiguous example of a single crystal X-ray analysis of an optically active phthalocyanine derivative. Both enantiomers crystallize in the orthorhombic system with a $P2_12_12_1$ space group with eight phthalocyanine molecules per unit cell as well as eight solvated *n*-hexane and thirty six solvated chloroform molecules. The crystal data are summarized in Table S2

(Supporting Information). As shown in Figure 2, the two metal free phthalocyanine molecules of (*R*)-**1** are bound to each other, forming a pseudo-double-decker structure. This also holds true for (*S*)-**1**. The average twist angle, defined as the rotation angle of one macrocycle away from a fully eclipsed conformation, was found to be about 24° . The ring-to-ring separation of these two virtually parallel N(isoindole)₄ mean planes of phthalocyanine ring is 3.28 Å. This value is comparable to that observed in sandwich-type bis(phthalocyaninato) lanthanum complex La(Pc)₂, 3.20 Å.^[16] This demonstrates that there is an intense π - π interaction between the two phthalocyanine rings. Neither a plane nor centre of symmetry could be found in either of the rings, Figure 2(a), confirming the chiral nature of the structure.

Figure 2 Molecular structure of **1** (a) and pseudo-double-decker structure in crystal of **1** in side view (b) and top view (c) with hydrogen atoms

2.3 Electronic absorption, magnetic circular dichroism, and circular dichroism

The electronic absorption, magnetic circular dichroism (MCD), and CD spectra of the (*R*)- and (*S*)-enantiomers of **1** were recorded in CHCl₃. The data are summarized in Table S3 (Supporting Information). As can be seen in Figure 3, a 5.0×10^{-6} mol/L solution of **1** in CHCl₃ exhibits the features typically observed in the electronic absorption spectra of metal free phthalocyanine compounds^[1,15b,17] and this demonstrates that there is almost no aggregation at this concentration. The absorption of **1** in CHCl₃ obeys Beer's rule in the 1.0×10^{-6} — 1.0×10^{-5} mol/L concentration range, Figure S4 (Supporting Information) and further evidence for the lack of aggregation is provided by Eq. 1. In a spectrum recorded for a 5.0×10^{-6} mol/L solution in

CHCl₃, more than 95% of the sample is in the monomeric form. As shown in Figure 3, symmetry split Q(0,0) bands are observed at 666 and 703 nm with vibrational shoulders at 608 and 638 nm.

Many key breakthroughs in the understanding of the electronic structure of the porphyrinoids have been derived from MCD spectroscopy.^[18] Analysis of MCD spectra is based on the three Faraday terms, $\mathcal{A}_1$, $\mathcal{B}_0$ and $\mathcal{C}_0$. Since there are no three-fold or higher axes of symmetry, the MCD spectrum of **1** is completely dominated by positively and negatively-signed and Gaussian-shaped Faraday $\mathcal{B}_0$ terms due to a complete lifting of ground and excited state degeneracies. In the MCD spectrum, coupled oppositely-signed $\mathcal{B}_0$ terms are observed at 662 and 701 nm as would normally be anticipated for the *x*- and *y*-polarized components of the Q bands. The introduction of fused benzene rings results in the presence of a number of additional higher energy $\pi\pi^*$ states, which can interact with the B excited state through configurational interaction. In the region of 340—410 nm, a broad envelope of absorption is observed with an intensity maximum at 347 nm. Two intense negatively signed Faraday $\mathcal{B}_0$ terms are observed at 356 and 403 nm with a positive envelope of intensity at higher energy with a maximum at 329 nm in the MCD spectrum, Figure 3. This region can, therefore, be assigned to overlapping B1 and B2 bands.^[19] As detailed in Figures S5 and S6 and Table S4 (Supporting Information), TD-DFT calculation revealed that the most intense bands predicted in both the Q and B1/B2 band regions are associated primarily with the four frontier π -MOs derived from the parent hydrocarbon perimeter. Weak tails of absorbance which lie between the Q and B1/B2 regions have been attributed to $n \rightarrow \pi^*$ transitions associated with the lone pairs of electrons on the oxygen and sulfur atoms in the context of alkoxy- and thioalkyl-substituted Pcs.^[20-22] In the context of **1**, however, transitions out of high lying occupied MOs which are associated with the binaphthyl moieties, Figure S6 (Supporting Information), may be a more significant factor in the intensity to the red of the B1 and B2 bands between 450—500 nm.

As would normally be anticipated, near perfect mirror image symmetry is observed in the CD spectra of the (*R*)- and (*S*)-enantiomers, Figures 3 and S7 (Supporting Information). Significant CD intensity can be induced in transitions associated with the achiral Pc chromophore when optically active substituents are introduced at the ligand periphery. Analyses of the induced circular dichroism (ICD) of binaphthyl-linked Pcs were carried out previously based on a consideration of the Kuhn-Kirkwood coupled oscillator and “CD stealing” mechanisms for A and B transitions which are symmetric and antisymmetric with respect to the two-fold axes running through the central bridge of the binaphthyl substituents.^[7d,18] It has been demonstrated that the average dihedral angle α of the binaphthyl substituents of the (*R*)- and (*S*)-enantiomers (which is $66.1^\circ \pm 0.1^\circ$ in the context of the B3LYP geometry optimizations and $65.8^\circ \pm 6.8^\circ$ in the context of the X-ray structures for **1**) and the average angle θ formed between the axis of polarization of the B_b transition of the substituents and the Pc plane of the (*R*)- and (*S*)-enantiomers (which is $61.8^\circ \pm 0.1^\circ$ in the context of the B3LYP geometry optimizations and $59.8^\circ \pm 4.1^\circ$ in the

context of the X-ray structures for **1**) play the key role in determining the signs of the CD signals, see Supporting Information, and that the ratio between the rotatory strengths of the symmetrical and antisymmetrical components (R_A and R_B) for the Q bands of the (*R*)-enantiomer is dependent on easily derived geometrical parameters:

$$R_A = 2pr_{12}\sin\alpha \quad (2)$$

$$R_B = \rho(-2R_{12}\sin^2(\alpha/2)\sin 2\theta + r_{12}\sin\alpha\sin^2\theta) \quad (3)$$

where ρ is a readily calculated constant,^[7d] and r_{12} and R_{12} denote the distance between the naphthalene rings as calculated based on the centers of the fused benzene rings and between the centers of gravity of the Pc and binaphthyl chromophores, respectively. As was the case previously with TNPcMg,^[7d] the positive R_A value in the context of the (*R*)-enantiomer, which is related to the “CD stealing” intensity mechanism, is predicted to be significantly larger than the negative R_B value, which has contributions from both of the ICD intensity mechanisms, Table S5 (Supporting Information). In particular, in the case of the (*R*)-**1** enantiomer, an anticlockwise arrangement is observed for the dinaphthyl moieties in the crystal structure, Figure 2, and the sign of the CD signal is positive across almost the entire 300–730 nm range, Figures 3 and S7 (Supporting Information). Conversely, a negative CD sign is observed for the (*S*)-**1** isomer which has a clockwise binaphthyl arrangement.

Figure 3 Electronic absorption (bottom), MCD (center), and CD (top) spectra of the (*R*)-enantiomer of **1** in CHCl_3 . A dashed line is used to plot the CD spectrum of the (*S*)-enantiomer, which shows the anticipated mirror symmetry.

Interestingly, in the context of the (*R*)-enantiomer, although positive intensity would be expected for the entire band envelope, significant negative intensity is observed for a tail absorbance to the red of the Qx band. This is not without precedent. The CD spectra of 1,1'-biphenyls contain similar changes in sign to low energy of the main bands, although the reasons for this have not been examined in any depth.^[23] The most plausible explanation for this is that the flexibility of the binaphthyl substituents results in a wide range of different conformations in solution. As revealed by single crystal analysis, the naphthalene ring moieties exhibit obvious deviation from planarity due to the wide range of different values for α ($\alpha = 65.8^\circ \pm 6.8^\circ$) and θ ($\theta = 59.8^\circ \pm 4.1^\circ$), also in combination with the flexibility of the binaphthyl substituents. Although the two naphthalene moieties of the binaphthyl substituents are generally assumed to be aligned in a parallel arrangement during theoretical treatments,^[7d] the distance between the 8- and 8'-positions may be slightly larger than that between the 1- and 1'-positions when the dihedral angle between the two naphthalene rings is adjusted to 0° . Nevertheless, an interaction between the Q band and the weak short-axis-polarized La transition of the binaphthyl substituents, which lies beyond 250 nm, also cannot be completely discounted as a contributing factor despite its three orders of magnitude weaker intensity in comparison with the intense long-axis-polarized B_b band lying in the region of 220–225 nm. It is noteworthy that the La transition has no intrinsic chirality and therefore cannot contribute to the “CD stealing” mechanism. However, a minor contribution of ICD intensity from the Kuhn-Kirkwood coupled dipole model is theoretically possible.

3 Conclusions

In summary, a pair of enantiomers of a chiral metal free phthalocyanine with four peripherally attached binaphthyl substituents have been prepared and spectroscopically and structurally characterized. This represents one example of optically active phthalocyanine derivatives with the molecular structures of both enantiomers unambiguously elucidated by X-ray single crystal analysis, which therefore renders it possible to clarify the chirality of optically active phthalocyanines based on the experimentally revealed absolute molecular structures, confirming the previous assignments made on the basis of theoretical calculations.

4 Experimental Section

General Remarks: *n*-Pentanol was distilled from sodium. Column chromatography was carried out on silica gel (Merck, Kieselgel 60, 70–230 mesh) with the indicated eluents. Optically pure (*R*)- and (*S*)-2,2'-dihydroxy-1,1'-binaphthyl were obtained from Aldrich. All other reagents and solvents were used as received. 4,5-Dichlorophthalonitrile was prepared according to the published procedure.^[24]

¹H NMR spectra were recorded on a Bruker DPX 400 spectrometer in CDCl_3 . Spectra were referenced internally using the residual solvent resonances (δ 7.26 for ¹H NMR) relative to SiMe_4 . Electronic absorption spectra were recorded on a Hitachi U-4100 spectrophotometer. IR spectra

were recorded as KBr pellets using a Bruker Tensor 37 spectrometer with 2 cm^{-1} resolution. MALDI-TOF mass spectra were taken on a Bruker BIFLEX III ultrahigh resolution Fourier transform ion cyclotron resonance (FT-ICR) mass spectrometer with alpha-cyano-4-hydroxycinnamic acid as matrix. Elemental analyses were performed on an Elementar Vavio El III. Circular dichroism (CD) and magnetic circular dichroism (MCD) spectra were recorded using a Jasco J-725 spectrodichromometer and a Jasco electromagnet that produces a magnetic field of up to 1.09 T. Crystal data for (*R*)- and (*S*)-**1** were determined by X-ray diffraction analysis at 120 K using Oxford Diffraction Gemini E system with CuK α radiation $\lambda = 1.5418\text{ \AA}$, and details of the structure refinement are given in Table S2 (Supporting Information). CCDC-866210 and CCDC-866211 containing the supplementary crystallographic data for this paper can be obtained free of charge from the Cambridge Crystallographic Data Centre via www.ccdc.cam.ac.uk/data_request/cif. The structures of the (*R*)- and (*S*)-enantiomers of **1** were optimized by using the B3LYP functional of the G03W software package^[25] with 3-21G* basis sets. TD-DFT calculations were then carried out in a similar manner.

(*R*)- and (*S*)-benzo[*b*]dinaphtho[2,1-*e*:1',2'-*g*][1,4]-dioxocine-5,6-dicarbonitrile (2**)** A mixture of (*R*)/(*S*)-2,2'-dihydroxy-1,1'-binaphthyl (2.86 g, 10.0 mmol), 4,5-dichlorophthalonitrile (1.97 g, 10.0 mmol), and dry potassium carbonate (4.14 g, 30.0 mmol) in dry DMF (30 mL) was stirred at $80\text{ }^{\circ}\text{C}$ for 6 h under nitrogen. Then the reaction mixture was poured onto water (150 mL) and extracted with CHCl_3 (40 mL $\times$ 5). The combined organic solution was then washed with water (100 mL $\times$ 2) and dried with Na_2SO_4 . After evaporating the solvent, the residue was chromatographed on a silica gel column with CH_2Cl_2 /light petroleum ($V:V = 1:1$) as eluent. Evaporation of the solvent followed by recrystallization from CHCl_3 and MeOH gave 3.50 g (85%) of white microcrystals of the desired nitrile (*R*)/(*S*)-**2**. ^1H NMR (400 MHz, CDCl_3) δ : 8.36 (d, $J = 8.8\text{ Hz}$, 2H), 7.98 (d, $J = 8.4\text{ Hz}$, 2H), 7.71 (s, 2H), 7.56–7.50 (m, 4H), 7.44–7.39 (m, 4H); ^{13}C NMR (100 MHz, CDCl_3) δ : 152.4, 149.4, 132.1, 132.0, 131.4, 128.5, 128.3, 127.4, 126.6, 126.3, 125.1, 120.3, 114.6, 112.2.

(*R*)- and (*S*)-tetrakis(dinaphtho[1,2-*e*:1',2'-*g*]-1,4-(dioxocine)[2,3-*b*:2',3'-*k*:2'',3''-*t*:2''',3'''-*c*]phthalocyanine (1**)** A mixture of (*R*)/(*S*)-**2** (82.0 mg, 0.200 mmol) and lithium (3.0 mg, 0.42 mmol) in *n*-pentanol (4 mL) was heated to reflux under nitrogen for 2 h. After being cooled to room temperature, the resulting green solution was poured into methanol (100 mL) containing 2 mL of CH_3COOH . The precipitate was collected by filtration and chromatographed on a silica gel column using CHCl_3 as eluent. Repeated chromatography followed by recrystallization from CHCl_3 and *n*-hexane gave **1** as a green crystalline powder (32.0 mg, 40%). ^1H NMR (400 MHz, CDCl_3) δ : 9.29 (s, 4H), 8.62 (d, $J = 8.0\text{ Hz}$, 4H), 8.48 (d, $J = 8.0\text{ Hz}$, 4H), 7.97 (d, $J = 8.0\text{ Hz}$, 4H), 7.87 (d, $J = 8.0\text{ Hz}$, 4H), 7.84 (s, 4H), 7.71 (d, $J = 8.0\text{ Hz}$, 4H), 7.39–7.60 (m, 8H), 7.30–7.49 (m, 4H), 7.12–7.30 (m, 4H), 7.10 (d, $J = 4.0\text{ Hz}$, 4H), 6.90–7.00 (m, 4H), 6.86 (d, $J = 8.0\text{ Hz}$, 4H), -4.25 (s, 2H); ^{13}C NMR (100 MHz, CDCl_3) δ : 151.7, 151.3, 132.0, 131.3, 130.9, 129.9, 128.3, 127.2,

126.6, 126.3, 125.2, 121.5, 121.3, 116.0, 115.4. MS: Calcd. for $\text{C}_{112}\text{H}_{58}\text{N}_8\text{O}_8$ $[\text{M} + 3\text{H}]^+$ 1645.5; found m/z : 1645.1. Anal. calcd for (*R*)- $\text{C}_{112}\text{H}_{58}\text{N}_8\text{O}_8 \cdot 2\text{CH}_3\text{OH}$: C 80.17, H 3.89, N 6.56; found C 80.56, H 3.86, N 6.27 and for (*S*)- $\text{C}_{112}\text{H}_{58}\text{N}_8\text{O}_8 \cdot 2\text{CHCl}_3 \cdot 3\text{CH}_3\text{OH} \cdot 3\text{H}_2\text{O}$: C 69.23, H 3.72, N 5.52; found C 69.32, H 3.72, N 5.53.

References

- [1] *The Porphyrin Handbook*, Vols. 1–20, Eds.: Kadish, K. M.; Smith, K. M.; Guillard, R., Academic Press, San Diego, **2000** and **2003**.
- [2] (a) Ogoshi, H.; Mizutani, T. *Acc. Chem. Res.* **1998**, *31*, 81; (b) Simonneaux, G.; Maux, P. L. *Coord. Chem. Rev.* **2002**, *228*, 43; (c) Hembury, G. A.; Borovkov, V. V.; Inoue, Y. *Chem. Rev.* **2008**, *108*, 1.
- [3] (a) Furusho, Y.; Kimura, T.; Mizuno, Y.; Aida, T. *J. Am. Chem. Soc.* **1997**, *119*, 5267; (b) Mizuno, Y.; Aida, T.; Yamaguchi, K. *J. Am. Chem. Soc.* **2000**, *122*, 5278; (c) Mammanna, A.; D'Urso, A.; Lauceri, R.; Purrello, R. *J. Am. Chem. Soc.* **2007**, *129*, 8062; (d) Helmich, F.; Lee, C. C.; Schenning, A. P. H. J.; Meijer, E. W. *J. Am. Chem. Soc.* **2010**, *132*, 16753.
- [4] (a) Meunier, B. *Chem. Rev.* **1992**, *92*, 1411; (b) Collman, J. P.; Zhang, X.; Lee, V. J.; Uffelman, E. S.; Brauman, J. I. *Science* **1993**, *261*, 1404; (c) Collman, J. P.; Boulatov, R.; Sunderland, C. J.; Fu, L. *Chem. Rev.* **2004**, *104*, 561; (d) Lu, H.; Zhang, X. P. *Chem. Soc. Rev.* **2011**, *40*, 1899.
- [5] Cho, I.; Lim, Y. *Mol. Cryst. Liq. Cryst.* **1988**, *154*, 9.
- [6] (a) Nostrum, C. F.; Bosman, A. W.; Gelinck, G. H.; Picken, S. J.; Schouten, P. G.; Warman, J. M.; Schouten, A.-J.; Nolte, R. J. M. *Chem. Commun.* **1993**, 1120; (b) Chen, P.; Ma, X.; Liu, M. *Macromolecules* **2007**, *40*, 4780; (c) Lv, W.; Wu, X.; Bian, Y.; Jiang, J.; Zhang, X. *ChemPhysChem* **2009**, *10*, 2725.
- [7] (a) Kobayashi, N. *Coord. Chem. Rev.* **2001**, *219–221*, 99; (b) Kobayashi, N.; Kobayashi, Y.; Osa, T. *J. Am. Chem. Soc.* **1993**, *115*, 10994; (c) Kobayashi, N. *Chem. Commun.* **1998**, 487; (d) Kobayashi, N.; Higashi, R.; Titeca, B. C.; Lamote, F.; Ceulemans, A. *J. Am. Chem. Soc.* **1999**, *121*, 12018.
- [8] (a) Zhang, X.; Muranaka, A.; Lv, W.; Zhang, Y.; Bian, Y.; Jiang, J.; Kobayashi, N. *Chem. Eur. J.* **2008**, *14*, 4667; (b) Zhang, X.; Wang, Q.; Wu, L.; Lv, W.; Lu, J.; Bian, Y.; Jiang, J. *J. Phys. Chem. B* **2010**, *114*, 1233.
- [9] Lv, W.; Zhu, P.; Bian, Y.; Ma, C.; Zhang, X.; Jiang, J. *Inorg. Chem.* **2010**, *49*, 6628.
- [10] (a) Bian, Y.; Wang, R.; Jiang, J.; Lee, C.-H.; Wang, J.; Ng, D. K. P. *Chem. Commun.* **2003**, 1194; (b) Bian, Y.; Wang, R.; Wang, D.; Zhu, P.; Li, R.; Dou, J.; Liu, W.; Choi, C.-F.; Chan, H.-S.; Ma, C.; Ng, D. K. P.; Jiang, J. *Helv. Chim. Acta* **2004**, *87*, 2581; (c) Wang, R.; Li, Y.; Li, R.; Cheng, D. Y. Y.; Zhu, P.; Ng, D. K. P. *Inorg. Chem.* **2005**, *44*, 2114; (d) Wang, R.; Li, R.; Li, Y.; Zhang, X.; Zhu, P.; Lo, P.-C.; Ng, D. K. P.; Pan, N.; Ma, C.; Kobayashi, N.; Jiang, J. *Chem. Eur. J.* **2006**, *12*, 1475.
- [11] Zhou, Y.; Zhang, Y.; Wang, H.; Jiang, J.; Bian, Y.; Muranaka, A.; Kobayashi, N. *Inorg. Chem.* **2009**, *48*, 8925.
- [12] Wang, R.; Li, R.; Bian, Y.; Choi, C.-F.; Ng, D. K. P.; Dou, J.; Wang, D.; Zhu, P.; Ma, C.; Hartnell, R. D.; Arnold, D. P.; Jiang, J. *Chem. Eur. J.* **2005**, *11*, 7351.
- [13] (a) Kumar, J. K.; Oliver, J. S. *J. Am. Chem. Soc.* **2002**, *124*, 11307. (b) Liu, L.; Byeon, I. L.; Bahar, I.; Gronenborn, A. M. *J. Am. Chem. Soc.* **2012**, *134*, 4229; (c) Do, N. M.; Olivier, M. A.; Salisbury, J. J.; Wager, C. B. *Anal. Chem.* **2011**, *83*, 8677; (d) Rundlöf, T.; Mathiasson, M.; Bekiroglu, S.; Hakkarainen, B.; Bowden, T.; Arvidsson, T. *J. Pharm. Biomed. Anal.* **2010**, *52*, 645.
- [14] (a) Jiang, J.; Bao, M.; Rintoul, L.; Arnold, D. P. *Coord. Chem. Rev.* **2006**, *250*, 424 and references therein; (b) Dong, S.; Qi, D.; Zhang, Y.; Jiang, J.; Bian, Y. *Vib. Spectrosc.* **2011**, *56*, 245.
- [15] (a) Zhang, X.; Zhang, Y.; Jiang, J. *Vib. Spectrosc.* **2003**, *33*, 153; (b) Zhang, Y.; Ma, P.; Zhu, P.; Zhang, X.; Gao, Y.; Qi, D.; Bian, Y.; Kobayashi, N.; Jiang, J. *J. Mater. Chem.* **2011**, *21*, 6515.
- [16] Hückstädt, H.; Tutaß, A.; Göldner, M.; Cornelissen, U.; Homborg, H. Z. *Anorg. Allg. Chem.* **2001**, *627*, 485.
- [17] (a) Li, R.; Zhang, X.; Zhu, P.; Ng, D. K. P.; Kobayashi, N.; Jiang, J. *Inorg. Chem.* **2006**, *45*, 2327; (b) Wang, X.; Zhang, Y.; Sun, X.; Bian, Y.; Ma, C.; Jiang, J. *Inorg. Chem.* **2007**, *46*, 7136; (c) Bai, Z.; Gao, Y.; Zhu, P.; Bian, Y.; Jiang, J. *Inorg. Chem.* **2010**, *49*, 9005.

- [18] Kobayashi, N.; Muranaka, A.; Mack, J. *Circular Dichroism and Magnetic Circular Dichroism Spectroscopy for Organic Chemists*, Royal Society of Chemistry, London, **2011**.
- [19] Ough, E.; Nyokong, T.; Creber, K. A. M.; Stillman, M. J. *Inorg. Chem.* **1988**, *27*, 2724.
- [20] (a) Law, W.-F.; Liu, R. C. W.; Jiang, J.; Ng, D. K. P. *Inorg. Chim. Acta* **1997**, *256*, 147; (b) Sheng, N.; Li, R.; Choi, C.-F.; Su, W.; Ng, D. K. P.; Cui, X.; Yoshida, K.; Kobayashi, N.; Jiang, J. *Inorg. Chem.* **2006**, *45*, 3794.
- [21] (a) Gasyna, Z.; Kobayashi, N.; Stillman, M. J. *J. Chem. Soc., Dalton Trans.* **1989**, 2397; (b) Sibert, J. W.; Baumann, T. F.; Williams, D. J.; White, A. J. P.; Barrett, A. G. M.; Hoffman, B. M. *J. Am. Chem. Soc.* **1996**, *118*, 10487; (c) Montalban, A. G.; Baum, S. M.; Hoffman, A. G. M.; Barrett, B. M. *Dalton Trans.* **2003**, 2093; (d) Li, Z.; Lieberman, M. *Inorg. Chem.* **2001**, *40*, 932.
- [22] Zhang, Y.; Zhang, X.; Liu, Z.; Bian, Y.; Jiang, J. *J. Phys. Chem. A* **2005**, *109*, 6363.
- [23] Mason, S. F.; Seal, R. H.; Roberts, D. R. *Tetrahedron* **1974**, *30*, 1671.
- [24] Wöhrle, D.; Eskes, M.; Shigehara, K.; Yamada, A. *Synthesis* **1993**, 194.
- [25] Frisch, M. J.; Trucks, G. W.; Schlegel, H. B.; Scuseria, G. E.; Robb, M. A.; Cheeseman, J. R.; Montgomery, Jr., J. A.; Vreven, T.; Kudin, K. N.; Burant, J. C.; Millam, J. M.; Iyengar, S. S.; Tomasi, J.; Barone, V.; Mennucci, B.; Cossi, M.; Scalmani, G.; Rega, N.; Petersson, G. A.; Nakatsuji, H.; Hada, M.; Ehara, M.; Toyota, K.; Fukuda, R.; Hasegawa, J.; Ishida, M.; Nakajima, T.; Honda, Y.; Kitao, O.; Nakai, H.; Klene, M.; Li, X.; Knox, J. E.; Hratchian, H. P.; Cross, J. B.; Bakken, V.; Adamo, C.; Jaramillo, J.; Gomperts, R.; Stratmann, R. E.; Yazyev, O.; Austin, A. J.; Cammi, R.; Pomelli, C.; Ochterski, J. W.; Ayala, P. Y.; Morokuma, K.; Voth, G. A.; Salvador, P.; Dannenberg, J. J.; Zakrzewski, V. G.; Dapprich, S.; Daniels, A. D.; Strain, M. C.; Farkas, O.; Malick, D. K.; Rabuck, A. D.; Raghavachari, K.; Foresman, J. B.; Ortiz, J. V.; Cui, Q.; Baboul, A. G.; Clifford, S.; Cioslowski, J.; Stefanov, B. B.; Liu, G.; Liashenko, A.; Piskorz, P.; Komaromi, I.; Martin, R. L.; Fox, D. J.; Keith, T.; Al-Laham, M. A.; Peng, C. Y.; Nanayakkara, A.; Challacombe, M.; Gill, P. M. W.; Johnson, B.; Chen, W.; Wong, M. W.; Gonzalez, C.; Pople, J. A. *Gaussian 03*, Revision C.02, Gaussian, Inc., Wallingford CT, **2004**.

(Qin, X.)