α,β -不饱和酸多相不对称氢化反应中的钯粒径和载体酸性效应

陈春辉 展恩胜 李勇 申文杰*

(中国科学院大连化学物理研究所 催化基础国家重点实验室 大连 116023)

摘要 使用胶体沉积法制备了具有不同钯粒径、不同氧化物载体的负载型钯催化剂,系统地研究了 α,β -不饱和酸的多相不对称氢化反应中的钯粒径和载体效应。结果表明钯粒径仅影响反应的活性而与对映体选择性无关。这是由于在较小的钯粒子上存在较多的边、角等区域,而这些区域具有较高的双键加氢活性,因而在较小的粒子上具有较高的氢化反应速率但是粒径的变化并没有改变手性修饰剂与反应中间体的吸附模式。载体的酸性对反应的活性和对映体选择性都有促进作用,说明酸性载体有利于反应中间体的吸附。

关键词 α,β -不饱和酸; 不对称氢化; 钯粒径; 载体效应

Enantioselective Hydrogenation of α,β -Unsaturated Carboxylic Acids: Effects of Palladium Particle Size and Support Acidic Property

Chen, Chunhui Zhan, Ensheng Li, Yong Shen, Wenjie*

(State Key Laboratory of Catalysis, Dalian Institute of Chemical Physics, Chinese Academy of Sciences, Dalian 116023)

Abstract Effects of Pd particle size and support acidity on enantioselective hydrogenation of α,β -unsaturated carboxylic acids were systematically studied using Pd nanoparticles with different size immobilized on various oxides. Small Pd particles showed higher activity in the hydrogenation of (*E*)-2-methyl-2-pentenoic acid due to the larger fraction of edge sites which were more active in olefin hydrogenation; but they did not change the reaction mechanism and/or the adsorption mode of reaction intermediates. Similar correlations in the hydrogenation of (*E*)-2-methyl-2-butenic acid and 2-acetamidoacrylic acid further confirmed that the size of Pd particles only mediated the activity but did not alter the enantioselectivity. On the other hand, the activity and the enantioselectivity were strongly dependent on the acidity of the support. The TOF and the *ee* value followed the order $\text{TiO}_2 > \gamma\text{-Al}_2\text{O}_3 > \text{SiO}_2 > \text{CeO}_2$, suggesting that the acidic support favored the adsorption of the reaction intermediates.

Keywords α,β -unsaturated carboxylic acid; enantioselective hydrogenation; Pd particle size; oxide support; acidity

1 Introduction

Enantioselective hydrogenation of unsaturated organic compounds, commonly catalyzed by homogeneous metal complexes bearing chiral ligands, is the most efficient route for the synthesis of optical product.^[1-4] However, for practical utilization heterogeneous catalysts are preferred due to the advantages in catalyst easy handling, separation and reuse.^[5] The highly efficient enantioselective hydrogenation of ketones to optical alcohols over chirally modified metal catalysts has been well established in industry.^[6-11] However, the equally important enantioselective hydrogenation of α,β -unsaturated carboxylic acids was less studied.^[12,13] Chirally modified palladium catalysts, which were used in various enantioselective reactions,^[14-17] were shown to be effective for enantioselective hydrogenation of aryl-substituted α,β -unsaturated carboxylic acids with the *ee* values of more than 90%.^[18-20] Aryl substituent in the β -position of the substrate stabilized the reaction interme-

diates on Pd surface by preventing their isomerization.^[10] For normal α,β -unsaturated acids, however, the enantioselectivities are still much low, varying in the 20%~67% range.^[21-25] The main reason was that the isomerization of the alkenic acids through double-bond migration occurred easily and rapidly on Pd surface; the hydrogenation of these isomers produced opposite enantiomers, drastically lowering the enantioselectivity.^[26,27]

For most Pd catalysts, the size of the metal particles and the acidic or basic features of the oxide support remarkably affected the enantioselectivity, but the mechanism was less understood. The typical techniques for preparing oxide-supported Pd catalysts, mainly impregnation and deposition-precipitation, often resulted in non-uniform distributions of metal particles;^[28] this significant variation in Pd particle size sometimes caused controversial reaction performance.^[29-31] For example, an enantioselectivity of 65% in enantioselective hydrogenation of (*E*)- α -phenylcinnamic acid was obtained on a cinchonidine modified Pd/TiO₂

* E-mail: shen98@dicp.ac.cn

Received July 12, 2013; published September 13, 2013.

Project supported by the National Natural Science Foundation of China (No. 20921092).

项目受国家自然科学基金(No. 20921092)资助。

Figure 1 TEM images of the Pd nanoparticles (a~c) and the Pd/Al₂O₃ catalysts (a'~c'). The size distributions (a''~c'') were determined by counting approximately 500 particles

catalyst with Pd particle size of 2~3 nm; further increase in the particle size up to >6 nm sharply decreased the enantioselectivity (15%~40%).^[29,30] However, an enantioselectivity of 90% was achieved under the same reaction conditions but using another Pd/TiO₂ catalyst which contained large Pd particles (>25 nm).^[31]

In this work, we synthesized uniform Pd nanoparticles in aqueous solution and immobilized them onto oxide supports using a colloid-deposition method. The catalytic performance in enantioselective hydrogenation of α,β -unsaturated carboxylic acids was examined with respect to the size of Pd particles and the acidic properties of the oxide-supports.

2 Results and Discussion

2.1 Structural properties of the Pd catalysts

Figure 1 shows the TEM images of the Pd nanoparticles and the Pd/Al₂O₃ catalysts. The as-synthesized Pd

nanoparticles had uniform size distributions and spherical shapes with the aid of PVP that had been frequently used to fabricate uniform metal nanoparticles.^[32] The carbonyl groups of PVP coordinated to the surface Pd atoms of the growing crystals and effectively protected their aggregation.^[33] The Pd particles of 2 nm in size were obtained through the fast reduction of Na₂PdCl₄ in aqueous solution by *L*-ascorbic acid. The Pd nanoparticles of 9 nm were achieved with the addition of Cl⁻, which mediated the reduction rate of Pd²⁺ ions through the formation of [PdCl₄]²⁻ complex. The concentration of Pd²⁺ ion in the synthetic equation can be calculated according to the following equation:

$$c_{\text{PdCl}_n} = \beta_n \times [\text{Cl}] / (1 + \sum_{i=1}^n \beta_i \times [\text{Cl}])$$

Where c is the concentration of PdCl_{*n*} species, β is the sta-

bility constant. For example, adding 2.64 mmol KCl to the synthetic solution lowered the concentration of Pd^{2+} by 10^{10} times. However, larger Pd particles cannot be obtained by simply increasing the concentration of Cl^- . Chlorine anion, at higher concentrations, preferentially adsorbs on the (100) facets of Pd particles and ultimately generates irregular shapes.^[34] Therefore, a seeded growth method, which was successfully in preparing large and uniform metal particles,^[35] was adopted to prepare the large Pd nanoparticles (14 nm) by using the as-synthesized Pd particles of 9 nm as the seeds that greatly facilitated the growth of Pd particles.

In the oxide-supported Pd catalysts, as shown in Figure 2, the Pd nanoparticles were uniformly dispersed on the oxides and maintained their original sizes without apparent aggregation. Figure 3 shows the NH_3 -TPD profiles of the oxide-supports. An intense desorption of ammonia on TiO_2 , Al_2O_3 and SiO_2 occurred at about 400 K, indicating the weak acidic sites. However, only traceable amounts of NH_3 were detected on CeO_2 . Quantitative analyses identified that the acidity of the oxides followed the order $\text{TiO}_2 > \gamma\text{-Al}_2\text{O}_3 > \text{SiO}_2 > \text{CeO}_2$.

Figure 2 TEM images of the Pd/ Al_2O_3 (a), Pd/ SiO_2 (b), Pd/ TiO_2 (c) and Pd/ CeO_2 (d) catalysts containing Pd particles of 9 nm in size

2.2 Pd particle size effect

To examine the effect of the Pd particle size, Al_2O_3 was used as the support and the size of Pd particles varied in the range of 2~14 nm. The resulting Pd/ Al_2O_3 catalysts were then tested for enantioselective hydrogenation of (*E*)-2-methyl-2-pentenoic acid. The conversion of MPA increased as decreasing the size of Pd particles, showing an apparent size-dependent phenomenon (Figure 4). The intrinsic activity of the catalyst, expressed in turnover frequency (TOF) (Table 1), increased remarkably with decreasing the size of Pd particles. The TOF of the Pd particle of 2 nm (337 h^{-1}) was more than 4 times greater than that of the Pd particles of 14 nm (73 h^{-1}). Small particles

Figure 3 NH_3 -TPD profiles of TiO_2 (a), Al_2O_3 (b), SiO_2 (c) and CeO_2 (d)

contained larger fraction of edge and corner sites with low coordination numbers,^[36,37] these more active sites had a higher adsorption strength of the substrates than that of the plane sites and therefore showed a higher hydrogenation activity.^[38] To verify the possible influence of the remaining surfactant on the Pd particles, a commercial Pd/ Al_2O_3 catalyst was comparatively tested. The commercial catalyst was only slightly more active than the current Pd/ Al_2O_3 catalyst with a similar Pd loading, indicating that the residual surfactant on the Pd surface only had a marginal effect in the hydrogenation activity. This observation may be related to the efficient competition at the solid/liquid interface among the colloid stabilizer, the reaction substrate, the chiral modifier (cinchonidine) and possibly the cinchonidine-substrate intermediates.

Figure 4 MPA conversions on the Pd/ Al_2O_3 catalysts. Reaction conditions: 16.5 μmol Pd, 66 μmol cinchonidine, 1 mmol MPA, 1 mmol benzylamine and 10 mL ethanol at 303 K, 2 MPa H_2 pressure

Table 1 Enantioselective hydrogenation of MPA on the Pd/ Al_2O_3 catalysts^a

Catalyst	Pd/wt%	Size/nm	TOF ^b / h^{-1}	ee ^c /%
Pd-2	4.61	2.2	337	33
Pd-9	4.56	8.9	112	35
Pd-14	4.67	14.2	73	34
Pd/ Al_2O_3 ^d	5.00	≈ 3.0	≈ 350	38

^a Reaction conditions: 16.5 μmol Pd, 66 μmol cinchonidine, 1 mmol MPA, 1 mmol benzylamine and 10 mL ethanol at 303 K, 2 MPa H_2 pressure; ^b The TOF values were based on the number of Pd atoms on the surface; ^c ee values were obtained at full conversion; ^d the reference commercial Al_2O_3 (5% Pd, Alfa Aesar, "11713", $d \approx 3 \text{ nm}$, determined by TEM).

Concerning the enantioselectivity, it is interestingly observed that the *ee* value was almost independent of the size of the Pd particles, being about 35%. This is somewhat inconsistent with previous reports where the enantioselectivity varied significantly with the size of Pd particles.^[29-31] This discrepancy might be due to the non-uniform of particle sizes and surface structures in the previous Pd catalysts that were typically prepared by impregnation or deposition-precipitation. With such strategies, the Pd particles tended to have random size distributions, and the average size of these particles was usually determined by CO chemisorption. Here, the Pd/Al₂O₃ catalysts had very uniform Pd particles and therefore the variations in enantioselectivity can be straightforwardly associated with the size of Pd particle.

Enantioselective hydrogenations of (*E*)-2-methyl-2-butenic acid (MBA) and 2-acetamidoacrylic acid (AA) on the Pd/Al₂O₃ catalyst were comparatively tested to confirm this phenomenon. As illustrated in Figure 5, the enantioselectivities were 30% and 27%, respectively, being irrespective of Pd particle size in both cases. The origin of this effect might be traced back to the adsorption mode of the bulky cinchonidine-substrate intermediates on Pd particles. Theoretical calculations have predicted that a flat active site ensemble of approximately 20~25 atoms is necessary to accommodate this large complex.^[39] Small particles (≤ 2 nm) which have large fraction of edge and corner sites could not provide sufficient space to accommodate the bulky cinchonidine-substrate intermediates, leading to the formation of racemic products.^[40] For the current Pd/Al₂O₃ catalysts, even the small Pd nanoparticles (2 nm) were large enough to supply a stable adsorption of the CD-substrate intermediate as the large particles (8~14 nm), resulting in almost constant enantioselectivities.

Figure 5 Enantioselective hydrogenations of (*E*)-2-methyl-2-butenic acid (MBA) and 2-acetamidoacrylic acid (AA) on the Pd/Al₂O₃ catalysts. Reaction conditions: 16.5 μ mol Pd, 66 μ mol cinchonidine, 1 mmol substrate, 1 mmol benzylamine and 10 mL ethanol at 303 K, 2 MPa H₂ pressure.

To confirm the stability of the catalysts during the reaction, the Pd-9 catalyst that was subjected to enantioselective hydrogenation of MPA for 12 h was examined by TEM analysis. As shown in Figure 6, Pd particles of about 9 nm in size were still highly dispersed on alumina support without obvious change in size and shape. This suggests that the activity and the enantioselectivity are straightforwardly associated with the Pd particles.

Figure 6 TEM images of the Pd-9 catalyst after reaction for 12 h. Reaction conditions: 16.5 μ mol Pd, 66 μ mol cinchonidine, 1 mmol MPA, 1 mmol benzylamine and 10 mL ethanol at 303 K, 2 MPa H₂.

2.3 Influence of the oxide support

The effect of the oxide support was then examined by fixing the size of Pd particles of 9 nm. As shown in Table 2, the reaction performance was closely associated with the acidic properties of the oxides. Both the activity (TOF) and the enantioselectivity followed the order: TiO₂ > Al₂O₃ > SiO₂ > CeO₂. TiO₂ with large amounts of acidity offered the most promising reaction rate (144 h⁻¹) and enantioselectivity (39%) whereas CeO₂ with the lowest acidity showed much less activity (82 h⁻¹) and enantioselectivity (29%).

Table 2 Enantioselective hydrogenation of MPA on the Pd catalysts^a

Catalyst	Pd/wt%	Size/nm	$S_{\text{BET}}/(\text{m}^2\cdot\text{g}^{-1})$	Surface acidity/ ($\mu\text{mol}\cdot\text{g}^{-1}$)	TOF ^b /h ⁻¹	<i>ee</i> ^c /%
Pd-9/Al ₂ O ₃	1.95	8.9	120.9	156.4	117	35
Pd-9/SiO ₂	1.89	8.7	197.6	113.3	105	33
Pd-9/TiO ₂	1.91	8.6	54.0	213.5	144	39
Pd-9/CeO ₂	1.86	8.9	10.2	14.7	82	29

^a Reaction conditions: 16.5 μ mol Pd, 66 μ mol cinchonidine, 1 mmol MPA, 1 mmol benzylamine and 10 mL ethanol at 303 K, 2 MPa H₂ pressure. ^b The TOF values were based on the number of Pd atoms on the surface and measured at low conversion ($\approx 10\%$). ^c *ee* values were obtained at full conversion.

This result is in consistence with previous reports on several commercial Pd catalysts,^[23] but the Pd particle size effect was fully excluded. Here, the importance of the oxide acidity can be convincingly rationalized by fixing the size of Pd particles. The acidity of the oxide support affected the adsorption of the chiral modifier through an acid-base interaction. The chiral modifier (CD) is a typical organic base, and its quinoline ring interacted electronically not only with the Pd particle but also with the oxide support through an acid-base interaction during the reaction process. The strong acidity of TiO₂ favored a tight adsorption of cinchonidine, efficiently anchored the chiral modifier on the catalyst surface and consequently promoted the overall reaction efficiency.

3 Conclusions

Uniform Pd nanoparticles of 2~14 nm in size were successfully synthesized in aqueous solution. The resulting Pd/Al₂O₃ catalysts showed obvious size-dependent phenomenon in the reaction rate of enantioselective hydro-

genation of α,β -unsaturated carboxylic acids, but the enantioselectivity was almost independent of the size of Pd particles. This result demonstrated that small Pd particles contained a larger fraction of the edge sites which were more active for the hydrogenation reaction, but they did not alter the reaction mechanism and/or the adsorption mode of the reaction intermediates. Moreover, Pd nanoparticles supported on strong acidic support provided a higher TOF and *ee* value, indicating that strong acidic support favored the adsorption of the chiral modifier. This is an important supplement to the understanding of structural effect on enantioselective reactions on heterogeneous catalysts.

4 Experimental

4.1 Catalyst preparation

The Pd nanoparticles of 2 nm were prepared by aqueous-phase reduction of Na_2PdCl_4 . 16.0 mL aqueous solution containing 1 mmol PVP and 0.24 mmol *L*-ascorbic acid was heated to 353 K. After adding 4.0 mL aqueous solution containing 0.21 mmol Na_2PdCl_4 , the mixture was kept at 353 K for 3 h under stirring. The obtained Pd colloid was denoted as Pd-2. For the synthesis of Pd particles of 9 nm, KCl was applied as the coordinating ligand. 8.0 mL aqueous solution containing 1.0 mmol PVP, 0.36 mmol *L*-ascorbic acid, and 2.64 mmol KCl were mixed with 4.0 mL aqueous solution containing 0.21 mmol Na_2PdCl_4 at 353 K. After reaction for 3 h, Pd colloids of 9 nm (Pd-9) were produced. The Pd particles of 14 nm were synthesized via a seeded growth method. A aqueous solution (12 mL) containing 4.0 mL of the Pd-9 suspension, 0.14 mmol Na_2PdCl_4 , 0.66 mmol PVP, 0.24 mmol *L*-ascorbic acid, and 1.76 mmol KCl was reacted at 353 K for 3 h, yielding Pd colloids of 14 nm (Pd-14). These Pd particles were collected by centrifugation, washed with acetone and finally dispersed into ethanol.

The Pd/ Al_2O_3 catalysts with palladium loading of 5 wt% were prepared using a colloid-deposition method. The as-prepared Pd colloids and Al_2O_3 powder were put into ethanol and immersed in an ultrasonic bath for 3 h. The resultant solids were collected by filtration, washed with ethanol and water, and dried at 323 K overnight in vacuum. For comparison, the Pd nanoparticles of 9 nm were also deposited on SiO_2 , TiO_2 and CeO_2 . The loading of Pd on TiO_2 and CeO_2 was fixed at 2 wt% because of their low surface areas. The oxides are commercial available: Al_2O_3 (99.99%, *ca.* 160 $\text{m}^2\cdot\text{g}^{-1}$, Aladdin Chemistry), SiO_2 (99.8%, *ca.* 240 $\text{m}^2\cdot\text{g}^{-1}$, Aladdin Chemistry), TiO_2 (P25, 80% anatase and 20% rutile, *ca.* 80 $\text{m}^2\cdot\text{g}^{-1}$, Degussa AG), CeO_2 (99.95%, *ca.* 30 $\text{m}^2\cdot\text{g}^{-1}$, Aladdin Chemistry).

4.2 Catalyst characterization

TEM images were recorded on a Philips Tecnai G2 Spirit microscope operated at 120 kV. The specimen was prepared by ultrasonically dispersing the solid powder into ethanol and drops of the suspension were deposited onto a clean carbon-enhanced copper grid and then dried in air.

Pd content in the catalysts were determined by inductively coupled plasma atomic emission spectroscopy (ICP-AES), using a Leeman Plasma Spec (I) spectrometer.

N_2 adsorption-desorption isotherms were recorded at 77

K using a Nova 4200e instrument (Quantachrome). Before the measurement, the sample was degassed at 473 K for 6 h. The specific surface area was calculated following the Brunauer-Emmett-Teller (BET) method.

Temperature programmed desorption (TPD) of ammonia was conducted with a U-type quartz tubular reactor. 100 mg sample was pretreated with a 10 vol.% O_2/He mixture (40 mL/min) at 673 K for 1 h. After cooling down to 323 K, the sample was treated with a 10 vol.% NH_3/He mixture (30 mL/min) for 0.5 h. After purging with He for 0.5 h at 323 K, the sample was heated to 873 K at a rate of 5 K/min under He flow (30 mL/min). The desorbed NH_3 was detected by monitoring the signal at $m/e=16$ with a mass spectrometer (Omni star GSD 320).

4.3 Catalytic hydrogenation

Enantioselective hydrogenation of α,β -unsaturated carboxylic acids were carried out in a stainless steel autoclave with a 50 mL quartz liner. The typical reaction mixture contained 16.5 μmol Pd, 66.0 μmol cinchonidine, 1.0 mmol substrate, 1 mmol benzylamine and 10.0 mL ethanol at 303 K and 2.0 MPa of H_2 . Before the reaction, the mixture was stirred for 15 min and flushed with hydrogen for five times. The stirring speed was fixed at 600 r/min. After reaction for a certain period, the solid catalyst was filtered off and 50.0 μL undecane was added to the solution as the external standard. The products of (*E*)-2-methyl-2-pentenoic acid (MPA) and (*E*)-2-methyl-2-butenic acid (MBA) were directly analyzed using an off-line gas chromatography (Agilent 6890N) equipped with a β -cyclodextrin capillary column (Chirasil-Dex CB, Varian) and a flame ionization detector. The product of 2-acetamidocrylic acid (AA) was transformed into methyl ester using diazomethane ethereal solution. The enantiomeric excess was expressed as: $ee\% = (E_1 - E_2)/(E_1 + E_2) \times 100$, where E_1 and E_2 are the concentrations of the enantiomers. The reactions were repeated twice and the results were reproducible within $\pm 1\%$.

References

- [1] Yu, Z. K.; Jin, W. W.; Jiang, Q. B. *Angew. Chem., Int. Ed.* **2012**, *51*, 6060.
- [2] Xie, J. H.; Zhou, Q. L. *Acta Chim. Sinica* **2012**, *70*, 1427. (谢建华, 周其林, 化学学报, **2012**, *70*, 1472.)
- [3] Ma, X.; Li, W. F.; Fan, W. Z.; Tao, X. M.; Li, X. M.; Yao, Y.; Zhu, L. F.; Chen, H. H.; Xie, X. M.; Zhang, Z. G. *Chin. J. Org. Chem.* **2012**, *32*, 1353. (马欣, 李万方, 范为正, 陶晓明, 李晓明, 姚莹, 诸吕锋, 陈厚和, 谢小敏, 张兆国, 有机化学, **2012**, *32*, 1353.)
- [4] Chen, Q. A.; Ye, Z. S.; Duan, Y.; Zhou, Y. G. *Chem. Soc. Rev.* **2013**, *42*, 497.
- [5] Irfan, M.; Glasnov, T. N.; Kappe, C. O. *ChemSuschem* **2011**, *4*, 300.
- [6] Izumi, Y.; Imaida, M.; Fukawa, H.; Akabori, S. *Bull. Chem. Soc. Jpn.* **1963**, *36*, 21.
- [7] Orito, Y.; Imai, S.; Niwa, S. *J. Chem. Soc. Jpn.* **1979**, 1118.
- [8] Xiong, W.; Huang, Y. L.; Ma, H. X.; Chen, H.; Li, Y. Z.; Li, L. L.; Cheng, P. M.; Li, X. J. *Acta Chim. Sinica* **2003**, *61*, 922. (熊伟, 黄裕林, 马红霞, 陈华, 黎耀忠, 李蕾蕾, 程涛明, 李贤均, 化学学报, **2003**, *61*, 922.)
- [9] Xiong, W.; Huang, Y. Y.; Chen, H.; Li, X. J. *Acta Chim. Sinica* **2005**, *63*, 1927. (熊伟, 黄艳秋, 陈华, 李贤均, 化学学报, **2005**, *63*, 1927.)
- [10] Mallat, T.; Orglmeister, E.; Baiker, A. *Chem. Rev.* **2007**, *107*, 4863.
- [11] Jiang, H. Y.; Chen, H. *Acta Chim. Sinica* **2012**, *70*, 297. (蒋和雁, 陈华, 化学学报, **2012**, *70*, 297.)
- [12] Nitta, Y. *J. Syn. Org. Chem. Jpn.* **2006**, *64*, 827.
- [13] Tungler, A.; Sipos, E.; Hada, V. *Curr. Org. Chem.* **2006**, *10*, 1569.

- [14] Fujihara, H.; Tamura, M. *J. Am. Chem. Soc.* **2003**, *125*, 15742.
- [15] Jansat, S.; Gómez, M.; Philippot, K.; Muller, G.; Guiu, E.; Claver, C.; Castillón, S.; Chaudret, B. *J. Am. Chem. Soc.* **2004**, *126*, 1592.
- [16] Sawai, K.; Tatum, R.; Nakahodo, T.; Fujihara, H. *Angew. Chem., Int. Ed.* **2008**, *47*, 6917.
- [17] Ranganath, K. V. S.; Kloesges, J.; Schäfer, A. H.; Glorius, F. *Angew. Chem., Int. Ed.* **2010**, *49*, 7786.
- [18] Nitta, Y.; Watanabe, J.; Okuyama, T.; Sugimura, T. *J. Catal.* **2005**, *236*, 164.
- [19] Szöllösi, G.; Hermán, B.; Felföldi, K.; Fülöp, F.; Bartók, M. *Adv. Synth. Catal.* **2008**, *350*, 2804.
- [20] Szöllösi, G.; Hermán, B.; Szabados, E.; Fülöp, F.; Bartók, M. *J. Mol. Catal. A: Chem.* **2010**, *333*, 28.
- [21] Kun, I.; Török, B.; Felföldi, K.; Bartók, M. *Appl. Catal. A: Gen.* **2000**, *203*, 71.
- [22] Bisignani, R.; Franceschini, S.; Piccolo, O.; Vaccari, A. *J. Mol. Catal. A: Chem.* **2005**, *232*, 161.
- [23] Casagrande, A.; Franceschini, S.; Lenarda, M.; Piccolo, O.; Vaccari, A. *J. Mol. Catal. A: Chem.* **2006**, *246*, 263.
- [24] György, S.; Zsolt, M.; Mihály, B. *React. Kinet. Catal. Lett.* **2009**, *96*, 319.
- [25] Makra, Z.; Szöllösi, G.; Bartók, M. *Catal. Today* **2012**, *181*, 56.
- [26] Borszeky, K.; Mallat, T.; Baiker, A. *Catal. Lett.* **1999**, *59*, 95.
- [27] Solladié-Cavallo, A.; Hoernel, F.; Schmitt, M.; Garin, F. *J. Mol. Catal. A: Chem.* **2003**, *195*, 181.
- [28] Toebe, M. L.; van Dillen, J. A.; de Jong, Y. P. *J. Mol. Catal. A: Chem.* **2001**, *173*, 75.
- [29] Nitta, Y.; Kubota, T.; Okamoto, Y. *Bull. Chem. Soc. Jpn.* **2001**, *74*, 2161.
- [30] Nitta, Y.; Kubota, T.; Okamoto, Y. *J. Mol. Catal. A: Chem.* **2004**, *212*, 155.
- [31] Kubota, T.; Kubota, H.; Kubota, T.; Moriyasu, E.; Uchida, T.; Nitta, Y.; Sugimura, T.; Okamoto, Y. *Catal. Lett.* **2009**, *129*, 387.
- [32] Xia, Y.; Xiong, Y.; Lim, B.; Skrabalak, S. E. *Angew. Chem., Int. Ed.* **2009**, *48*, 60.
- [33] Xiao, C.; Ding, H.; Shen, C.; Yang, T.; Hui, C.; Gao, H. *J. Phys. Chem. C* **2009**, *113*, 13466.
- [34] Jin, M.; Liu, H.; Zhang, H.; Xie, Z.; Liu, J.; Xia, Y. *Nano Res.* **2011**, *4*, 83.
- [35] Murphy, C. J.; Sau, T. K.; Gole, A. M.; Orendorff, C. J.; Gao, J.; Gou, L.; Hunyadi, S. E.; Li, T. *J. Phys. Chem. B* **2005**, *109*, 13857.
- [36] Ma, R.; Semagina, N. *J. Phys. Chem. C* **2010**, *114*, 15417.
- [37] Crespo-Quesada, M.; Yarulin, A.; Jin, M.; Xia, Y.; Kiwi-Minsker, L. *J. Am. Chem. Soc.* **2011**, *133*, 12787.
- [38] Belelli, P. G.; Ferullo, R. M.; Castellani, N. *J. Surf. Sci.* **2010**, *604*, 386.
- [39] Bürgi, T.; Baiker, A. *Acc. Chem. Res.* **2004**, *37*, 909.
- [40] Hoxha, F.; van Vegten, N.; Urakawa, A.; Krumeich, F.; Mallat, T.; Baiker, A. *J. Catal.* **2009**, *261*, 224.

(Lu, Y.)