Pd/MgO: 一种基于芳香羧酸脱羧与卤代芳烃的交叉偶联反应体系的 可循环的多相催化剂

李召好^b 陈静^a 苏伟平^{*,a} 洪茂椿^a

(^a 中国科学院煤制乙二醇及相关技术重点实验室 结构化学国家重点实验室 中国科学院福建物质结构研究所
福州 350002)

(^b 洛阳师范学院化学化工学院 471022)

摘要 发展了钯多相催化剂 Pd/MgO (0.5 mol% Pd) 参与的芳基羧酸脱羧与卤代芳烃的偶联反应体系。在与溴代芳烃甚至氯代芳烃的偶联反应中, 缺电子和富电子的芳基羧酸均能进行脱羧, 并以高收率得到目标产物。该体系采用的负载型钯多相催化剂制备方法简单易行, 可多次循环使用, 能便捷地应用于脱羧偶联的有机合成反应。

关键词 钯; 脱羧; 芳基羧酸; 偶联; 多相催化

Pd/MgO: A Recyclable, Ligand-free Heterogeneous Catalyst for Decarboxylative Cross-Coupling of Arene Carboxylic Acids with Aryl Halides

Li, Zhaohao^b Chen, Jing^a Su, Weiping^{*,a} Hong, Maochun^a

(^a Key Laboratory of Coal to Ethylene Glycol and Its Related Technology, State Key Laboratory of Structural Chemistry, Fujian Institute of Research on the Structure of Matter, Chinese Academy of Sciences, Fuzhou 350002)

(^b College of Chemistry and Chemical Engineering, Luoyang Normal University, Luoyang 471022)

Abstract Decarboxylative coupling of arene carboxylic acids with aryl halides is achieved by using a ligand-free Pd/MgO (0.5 mol% Pd) heterogeneous catalyst system. Both electron-rich and electron-deficient arene carboxylic acids can be used as aryl sources to couple a variety of aryl bromides, even aryl chlorides in moderate-to-excellent yields. The establishment of heterogeneous catalysis for the decarboxylative cross-coupling along with the reusability of the heterogeneous catalyst should facilitate the practical application of this transformation in organic synthesis.

Keywords palladium; decarboxylation; carboxylic acid; cross-coupling; heterogeneous catalysis

1 Introduction

The biaryl motif is widely found in biologically active molecules and functional materials.^[1] Over the past decades, transition-metal catalyzed cross-coupling reactions of aryl halides with organometallic reagents have been developed into a powerful tool for construction of biaryl structures.^[2-4] Despite tremendous success in the development of this methodology, for example, establishment of mild reaction condition for deactivated aryl chlorides and tolerance of a wide range of functional groups, these traditional cross-coupling reactions suffer from an intrinsic drawback: the need for stoichiometric amount of expensive organometallic reagents that are usually prepared from sensitive precursors under rigorously anaerobic condition. To overcome this limitation, the development of new methodologies for biaryl synthesis has attracted intense interest. In this regard, a breakthrough by Steglich,^[5] Miura,^[6] Goossen^[7] and Forgiione^[8] is the metal-catalyzed

decarboxylative coupling reactions of carboxylic acids with aryl halides, in which carboxylic acids undergo decarboxylation and generate *in situ* aryl-metal intermediates as aryl sources and therefore replace organometallic reagents in traditional cross-coupling reactions. A related study by de Vries and Myers^[9] is the Pd-catalyzed decarboxylative Heck coupling reaction of carboxylic anhydrides or benzoic acids. Since these pioneering reports, significant advances have also been achieved in applying decarboxylation process to the direct functionalization of C—H bonds.^[10,11] The ready availability of carboxylic acids makes the decarboxylative cross-coupling reactions particularly attractive.

2 Results and discussion

Compared with homogeneous catalyst, heterogeneous catalyst has the following advantages:^[12] (i) easy separation from the reaction mixture; (ii) reusability in most

* E-mail: wpsu@fjirsm.ac.cn

Received March 11, 2014; published April 13, 2014.

Supporting information for this article is available free of charge via the Internet at <http://sioc-journal.cn>.

Project supported by the 973 Program (Nos. 2011CB932404, 2011CBA00501), the National Natural Science Foundation of China (No. 21103192) and the Key Project from Chinese Academy of Sciences.

项目受 973(Nos. 2011CB932404, 2011CBA00501)、国家自然科学基金(No. 21103192)和中科院重点项目资助。

cases. Consequently, heterogeneous catalysis is preferred over homogeneous catalysis in the synthesis on large scale. As such, the development of heterogeneous catalyst system for the decarboxylative cross-coupling reaction of carboxylic acids with aryl halides is important for the practical application of this reaction in organic synthesis. The heterogeneous catalysts for the traditional cross-coupling reactions have been well-documented.^[13] Since the proposed reaction pathway for Pd/Cu catalyzed decarboxylative coupling of benzoic acids with aryl halides is similar to that of the traditional cross-coupling reactions with respect to elemental steps involving Pd catalyst, the establishment of heterogeneous catalyst system for this decarboxylative coupling is plausible in principle. However, this goal represents a challenge for the following reason: because the labile aryl-Cu intermediate generated from Cu-promoted decarboxylation tends to be protonated, the undesired protodecarboxylation of carboxylic acids takes place when Cu-promoted decarboxylation step is faster than the heterogeneous Pd catalyst-promoted steps and transmetalation from Cu to Pd. Thus, the key to accessing the heterogeneous catalysis of this decarboxylative coupling is the identification of active heterogeneous catalyst for activation of aryl halides, as illustrated by the Pd/Cu catalyzed homogeneous process of the decarboxylative coupling in which bulky and electron-rich phosphine ligands were required to support a very active Pd catalyst. Herein, we report that the MgO-supported palladium catalyst, in combination with stoichiometric or catalytic amount of CuI, affects the decarboxylative coupling of both electron-deficient and electron-rich benzoic acids with aryl bromides or some activated aryl chlorides. The low catalyst loading (0.5 mol% calculated based on Pd) and the reusability of catalyst demonstrate the potential of this method for practical synthetic applications. To the best of our knowledge, no example of heterogeneous catalyst system for the decarboxylative coupling has been reported before this work.

The MgO support was prepared according to a literature procedure.^[14] When Palladium species were impregnated onto the MgO, X-ray photoelectron spectroscopy (XPS) of the Pd 3d core level showed a Pd_{5/2} line at a binding energy of 336.1 eV, which clearly indicated that the palladium species are in the +2 oxidation state (see Supporting Information).^[15] XRD patterns of the catalyst sample showed characteristic peaks corresponding to MgO, indicating a good maintenance of the crystallinity of MgO (see Supporting Information). The Pd species could not be discerned in the TEM images in accordance with the amorphous nature of the Pd species as suggested by the XRD analysis. The dispersion of Pd in Pd/MgO was 17.5% (see Supporting Information). Analyzing of nitrogen adsorption-desorption isotherm confirmed the catalyst sample showed a BET surface area of 14 m²·g⁻¹ and average pore size of 5.24 nm (see Supporting Information).

Initially, 2-nitrobenzoic acid and 4-bromotoluene were used as model substrates. Using Pd/MgO catalyst, we optimized the reaction conditions by screening reaction parameters such as Cu sources, solvents, bases and supports. CuI was proved to be the copper source of choice, and other Cu(I) salts including Cu₂O, CuOAc, CuCl and CuBr were observed to be less effective (Table 1, Entries 1~5). Since halide ions released from aryl halides can retard

Cu-mediated decarboxylation,^[7b,7i] increasing the amount of CuI from 50 mol% to 1 equiv. significantly improved the yield (Table 1, Entries 5, 6). The solvent was also a critical factor affecting the reaction outcome. A number of solvents such as DMF, DMA, DMSO and NMP were investigated and it turned out that DMF was more suitable solvent for this purpose than other solvents (Table 1, Entries 7~9). KOBu-*t* gave the best results among these bases screened, whereas using weaker bases generated protodecarboxylation product much more than that in the case of KOBu-*t* and therefore led to a significant decrease in yield of the desired product (Table 1, Entries 10, 11). We then initiated investigation by examining the catalytic performance of the solid palladium catalysts with a variety of supports since the interaction between palladium and support can exerts an effect on the activity of supported catalyst. These supported catalysts (palladium content of 0.5 wt%) were prepared by impregnating Pd onto the surface of supports and subsequent calcination treatment.^[14] Among these tested catalysts, Pd/MgO catalyst exhibited the best performance. As expected, protodecarboxylation of carboxylic acids occurred as a side reaction when the less active catalyst was used. For example, the Pd/SiO₂ catalyst gave a trace of the desired product with 70% of

Table 1 Optimization studies for decarboxylative coupling reaction^a

Entry	Catalyst ^b	Cu source	Base	Solvent	Yield ^c /%
1	Pd/MgO	50% Cu ₂ O	KOBu- <i>t</i>	DMF	8
2	Pd/MgO	100% CuOAc	KOBu- <i>t</i>	DMF	14
3	Pd/MgO	100% CuCl	KOBu- <i>t</i>	DMF	25
4	Pd/MgO	100% CuBr	KOBu- <i>t</i>	DMF	42
5	Pd/MgO	100% CuI	KOBu- <i>t</i>	DMF	94
6	Pd/MgO	50% CuI	KOBu- <i>t</i>	DMF	63
7	Pd/MgO	100% CuI	KOBu- <i>t</i>	DMA	56
8	Pd/MgO	100% CuI	KOBu- <i>t</i>	NMP	5
9	Pd/MgO	100% CuI	KOBu- <i>t</i>	DMSO	Trace
10	Pd/MgO	100% CuI	K ₂ CO ₃	DMF	49
11	Pd/MgO	100% CuI	K ₃ PO ₄	DMF	60
12	Pd/HAP	100% CuI	KOBu- <i>t</i>	DMF	63
13	Pd/HT	100% CuI	KOBu- <i>t</i>	DMF	69
14	Pd/Al ₂ O ₃	100% CuI	KOBu- <i>t</i>	DMF	51
15	Pd/SiO ₂	100% CuI	KOBu- <i>t</i>	DMF	28
16	Pd/MgO	—	KOBu- <i>t</i>	DMF	Trace
17	—	100% CuI	KOBu- <i>t</i>	DMF	Trace
18 ^d	Pd/MgO	100% CuI	KOBu- <i>t</i>	DMF	92

^a Reaction conditions: **1a** (0.2 mmol), **2a** (0.3 mmol), 0.5 wt% catalyst (0.5 mol%), base (0.2 mmol), solvent (2.0 mL), 150 °C, 20 h. ^b See Supporting Information for the catalyst preparation procedure. ^c Yields determined by GC analysis. ^d **2a** (0.24 mmol).

benzoic acid converted into protodecarboxylation product (Table 1, Entry 15). In the absence of Pd/MgO catalyst or CuI, the cross-coupling reaction did not proceed (Table 1, Entries 16, 17). The further experiment showed that the use of 1.2 equiv. of 4-bromotoluene afforded a yield comparable to that obtained with 1.5 equiv. of 4-bromotoluene.

With the optimized reaction conditions: the reaction of benzoic acids with 1.2 equiv. of aryl halides conducted in the 2 mL DMF at 150 °C in the presence of 1 equiv. of KOBu-*t* as the base, 1 equiv. of CuI as the additive and 0.5 mol% Pd/MgO (calculated based on palladium) as the catalyst, we evaluated the scope and limitation of the reaction (Table 2). Both electron-deficient and electron-rich aryl bromides smoothly underwent the cross-coupling reactions and produced the corresponding products in good yields (**3aa**~**3aj**). Sterically demanding substrate can also be coupled in excellent yield (**3ae**). By a slight modification, the established reaction conditions can also be applied to aryl chlorides, furnishing moderate to good yields (**3aj**~**3al**). An array of benzoic acids and heterocyclic carboxylic acids acted as suitable coupling partners (**3ba**~**3bj**). Electron-deficient benzoic acids provided synthetically useful yield. Among some electron-deficient benzoic acids successfully replaced the corresponding organometallic reagents that are problematic substrates in the traditional cross-coupling reactions due to their difficult synthesis and low reactivity, illustrating the advantage of the protocol for decarboxylative coupling reactions. Electron-rich benzoic acids such as 2-methoxy-benzoic acid observed to be less reactive than electron-deficient ones. However, the reactions of electron-rich heterocyclic carboxylic acids were efficient regardless of the presence or absence of the substituent ortho to carboxyl group (**3bg**~**3bj**). Interestingly, both *N*-methylindole-3-carboxylic acid and *N*-methylindole-2-carboxylic acid produced 2-arylindole, indication that C(3) to C(2) migration may happen to the metal complex intermediate generated from metal-promoted decarboxylation of *N*-methylindole-3-carboxylic acid.

The reusability of the catalyst was evaluated by employing the reaction 2-nitrobenzoic acid (**1a**) with 4-bromotoluene (**2a**) as a model. After the reaction, the catalyst was separated from the reaction mixture by centrifugation, thoroughly washed with dilute NH₃·H₂O and calcinated at 500 °C. The catalyst could be reused at least 3 times without any obvious decrease of catalytic performance. It's worth mentioning that the calcination activation was necessary for recovering the activity of the used catalyst. The used catalyst that was washed and dried in air was observed to lose catalytic activity and much more protodecarboxylation product was produced. XRD analysis revealed that Mg(OH)₂ phase appeared in the deactivated catalyst sample (Figure 1B) and its TEM image visualized typical whisker-like structure of the newly formed Mg(OH)₂ (Figure 2B).^[16] Upon calcination, the used catalyst regained its activity. XRD analysis showed that Mg(OH)₂ phase that could cause protodecarboxylation disappeared from the used catalyst sample after calcination treatment. The TEM image of this regenerated catalyst (Figure 2C) was very similar to that of the newly prepared catalyst (Figure 2A), no obvious aggregation of Pd on the support surface to form visible nanoparticles was observed,

Table 2 Representative decarboxylative coupling reactions catalyzed by 0.5 wt% Pd/MgO catalyst^a

$\text{ArCOOH} + \text{R}-\text{C}_6\text{H}_4-\text{X} \xrightarrow[\text{DMF, 150 } ^\circ\text{C}]{0.5 \text{ wt\% Pd/MgO, CuI, KOBu-}t} \text{R}-\text{C}_6\text{H}_4-\text{Ar}$ <p>X = Br, Cl 3aa ~ 3bj</p>			
Product	Yield/%	Product	Yield/%
3aa	87	3al	39 ^b
3ab	86	3ba	63
3ac	73	3bb	51
3ad	62	3bc	65
3ae	82	3bd	38
3af	57	3be	52
3ag	85	3bf	60
3ah	53	3bg	70
3ai	51	3bh	91 ^c

		Continued	
Product	Yield/%	Product	Yield/%
94 41 ^b		45
67 ^b		65

^a Reaction conditions: carboxylic acids (0.2 mmol), aryl bromides (0.24 mmol), 0.5 wt% Pd/MgO (0.5 mol%), CuI (0.2 mmol), KOBu-*t* (0.2 mmol), DMF (2 mL), 150 °C, 20 h, isolated yields. ^b Potassium 2-nitrobenzoate (0.2 mmol), aryl chlorides (0.24 mmol), CuI (0.01 mmol), DMF (2 mL), 150 °C, 20 h, isolated yields. ^c *N*-Methylindole-3-carboxylic acid as substrate.

only MgO particles were observed with the Pd confirmed by EDS analysis (see Supporting Information). Heterogeneous nature of the catalyst was also confirmed by the fact that the solid catalyst was hot removed at 39% yield under nitrogen in the reaction of **1a** with **2a**, and the filtrate was further reacted for 5 h. The above treatment of the filtrate gave no yield of **3a**. The result confirmed that the supported catalyst provided the high catalytic activity and not any leached palladium, although Pd concentration in the filtrate was about 1 ppm based on ICP results.

Figure 1 XRD pattern of the Pd/MgO catalyst.

(A) fresh catalyst, (B) used catalyst before calcination, (C) used catalyst after calcination

Figure 2 TEM images of the Pd/MgO catalyst.

(A) fresh catalyst, (B) used catalyst before calcination, (C) used catalyst after calcination

3 Conclusion

In summary, we have described for the first time a heterogeneous catalyst for the decarboxylative cross-coupling of aryl halides with arene carboxylic acids. Both electron-deficient benzoic acids and electron-rich heteroaromatic carboxylic acids can be used as arylating reagents to couple a broad range of aryl halides including some aryl chlorides. The establishment of recyclable, ligand-free heterogeneous catalyst represents an advance in the development of new catalytic methods for the decarboxylative cross-coupling reactions. The effect of support on the performance of the supported catalyst points out a promising way to accessing a highly efficient, general heterogeneous catalyst for this type of cross-coupling reactions. Our current efforts are directed towards this target.

References

- [1] (a) Hajduk, P. J.; Bures, M.; Praestgaard, J.; Fesik, S. W. *J. Med. Chem.* **2000**, *43*, 3443; (b) Horton, D. A.; Bourne, G. T.; Smythe, M. L. *Chem. Rev.* **2003**, *103*, 893; (c) Bringmann, G.; Price Mortimer, A. J.; Keller, P. A.; Gresser, M. J.; Garner, J.; Breuning, M. *Angew. Chem.* **2005**, *117*, 5518; *Angew. Chem., Int. Ed.* **2005**, *44*, 5384; (d) Baudoin, O. *Angew. Chem.* **2007**, *119*, 1395; *Angew. Chem., Int. Ed.* **2007**, *46*, 1373; (e) Zhang, Z.-Y.; Zheng, J.; Du, Q.-W.; Zhang, W.; Li, Y.-Q. *Chin. J. Chem.* **2012**, *30*, 1543; (f) Zhou, C.; Li, Y.-M.; Lu, Y.; Zhang, R.; Jin, K.; Fu, X.-M.; Duan, C.-Y. *Chin. J. Chem.* **2013**, *31*, 1269; (g) Cai, H.-T.; Li, D.-D.; Liu, Z.; Wang, G.-W. *Acta Chim. Sinica* **2013**, *71*, 717.
- [2] For recent reviews, see: (a) Hassan, J.; Sévignon, M.; Gozzi, C.; Schulz, E.; Lemaire, M. *Chem. Rev.* **2002**, *102*, 1359; (b) Littke, A. F.; Fu, G. C. *Angew. Chem.* **2002**, *114*, 4350; *Angew. Chem., Int. Ed.* **2002**, *41*, 4176; (c) Christmann, U.; Vilar, R. *Angew. Chem.* **2005**, *117*, 370; *Angew. Chem., Int. Ed.* **2005**, *44*, 366; (d) Nicolaou, K. C.; Bulger, P. G.; Sarlah, D. *Angew. Chem.* **2005**, *117*, 4516; *Angew. Chem., Int. Ed.* **2005**, *44*, 4442; (e) Kantchev, E. A. B.; O'Brien, C. J.; Organ, M. G. *Angew. Chem.* **2007**, *119*, 2824; *Angew. Chem., Int. Ed.* **2007**, *46*, 2768; (f) Martin, R.; Buchwald, S. L. *Acc. Chem. Res.* **2008**, *41*, 1461; (g) Fu, G. C. *Acc. Chem. Res.* **2008**, *41*, 1555.
- [3] Tsuji, J. In *Palladium Reagents and Catalysis, New Perspectives for the 21st Century*, John Wiley & Sons, Ltd., **2004**.
- [4] Bräse, S.; de Meijere, A. In *Metal-Catalyzed Cross-Coupling Reactions*, 2nd ed., Vol. 1, Eds.: de Meijere, A.; Diederich, F., Wiley-VCH, Weinheim, **2004**.
- [5] Peschko, C.; Winkhofer, C.; Steglich, W. *Chem. Eur. J.* **2000**, *6*, 1147.
- [6] (a) Okazawa, T.; Satoh, T.; Miura, M.; Nomura, M. *J. Am. Chem. Soc.* **2002**, *124*, 5286; (b) Nakano, M.; Tsurugi, H.; Satoh, T.; Miura, M. *Org. Lett.* **2008**, *10*, 1851; (c) Miyasaka, M.; Fukushima, A.; Satoh, T.; Hirano, K.; Miura, M. *Chem. Eur. J.* **2009**, *15*, 3674; (d) Miyasaka, M.; Hirano, K.; Satoh, T.; Miura, M. *Adv. Synth. Catal.* **2009**, *351*, 2683.
- [7] (a) Goossen, L. J.; Deng, G.; Levy, L. M. *Science* **2006**, *313*, 662; (b) Goossen, L. J.; Rodriguez, N.; Melzer, B.; Linder, C.; Deng, G.; Levy, L. M. *J. Am. Chem. Soc.* **2007**, *129*, 4824; (c) Goossen, L. J.; Rudolphi, F.; Oppel, C.; Rodriguez, N. *Angew. Chem.* **2008**, *120*, 3085; *Angew. Chem., Int. Ed.* **2008**, *47*, 3043; (d) Goossen, L. J.; Rodriguez, N.; Goossen, K. *Angew. Chem.* **2008**, *120*, 3144; *Angew. Chem., Int. Ed.* **2008**, *47*, 3100; (e) Goossen, L. J.; Zimmermann, B.; Knauber, T. *Angew. Chem.* **2008**, *120*, 7211; *Angew. Chem., Int. Ed.* **2008**, *47*, 7103; (f) Goossen, L. J.; Rodriguez, N.; Linder, C. *J. Am. Chem. Soc.* **2008**, *130*, 15248; (g) Goossen, L. J.; Zimmermann, B.; Linder, C.; Rodriguez, N.; Lange, P. P.; Hartung, J. *Adv. Synth. Catal.* **2009**, *351*, 2667; (h) Goossen, L. J.; Linder, C.; Rodriguez, N.; Lange, P. P. *Chem. Eur. J.* **2009**, *15*, 9336; (i) Goossen, L. J.; Rodriguez, N.; Lange, P. P.; Linder, C. *Angew. Chem.* **2010**, *122*, 1129; *Angew. Chem., Int. Ed.* **2010**, *49*, 1111; (j) Goossen, L. J.; Lange, P. P.; Rodriguez, N.; Linder, C. *Chem. Eur. J.* **2010**, *16*, 3906.
- [8] (a) Forgione, P.; Brochu, M.-C.; St-Onge, M.; Thesen, K. H.; Bailey, M. D.; Bilodeau, F. *J. Am. Chem. Soc.* **2006**, *128*, 11350; (b) Bilo-

- deau, F.; Brochu, M.-C.; Guimond, N.; Thesen, K. H.; Forgione, P. *J. Org. Chem.* **2010**, *75*, 1550.
- [9] (a) Stephan, M. S.; Teunissen, A. J. J. M.; Verzijl, G. K. M.; Vries, J. G. de *Angew. Chem.* **1998**, *110*, 688; *Angew. Chem., Int. Ed.* **1998**, *37*, 662; (b) Myers, A. G.; Tanaka, D.; Mannion, M. R. *J. Am. Chem. Soc.* **2002**, *124*, 11250; (c) Tanaka, D.; Myers, A. G. *Org. Lett.* **2004**, *6*, 433; (d) Tanaka, D.; Romeril, S. P.; Myers, A. G. *J. Am. Chem. Soc.* **2005**, *127*, 10323.
- [10] (a) Becht, J.-M.; Catala, C.; Le Drian, C.; Wagner, A. *Org. Lett.* **2007**, *9*, 1781; (b) Becht, J.-M.; Le Drian, C. *Org. Lett.* **2008**, *10*, 3161; (c) Duan, Z.; Ranjit, S.; Zhang, P.; Liu, X. *Chem.-Eur. J.* **2009**, *15*, 3666; (d) Shang, R.; Fu, Y.; Wang, Y.; Xu, Q.; Yu, H.-Z.; Liu, L. *Angew. Chem.* **2009**, *121*, 9514; *Angew. Chem., Int. Ed.* **2009**, *48*, 9350; (e) Wang, Z.; Ding, Q.; He, X.; Wu, J. *Tetrahedron* **2009**, *65*, 4635; (f) Hu, P.; Kan, J.; Su, W.; Hong, M. *Org. Lett.* **2009**, *11*, 2341; (g) Shang, R.; Xu, Q.; Jiang, Y.-Y.; Wang, Y.; Liu, L. *Org. Lett.* **2010**, *12*, 1000; (h) Jia, W.; Jiao, N. *Org. Lett.* **2010**, *12*, 2000.
- [11] For decarboxylative C-H activation of organic substrates, see: (a) Voutchkova, A.; Coplin, A.; Leadbeater, N.; Crabtree, R. H. *Chem. Commun.* **2008**, *47*, 6312; (b) Wang, C.; Piel, I.; Glorius, F. *J. Am. Chem. Soc.* **2009**, *131*, 4194; (c) Cornella, J.; Lu, P.; Larrosa, I. *Org. Lett.* **2009**, *11*, 5506; (d) Zhang, F.; Greaney, M. F. *Angew. Chem.* **2010**, *122*, 2828; *Angew. Chem., Int. Ed.* **2010**, *49*, 2768; (e) Xie, K.; Yang, Z.; Zhou, X.; Li, X.; Wang, S.; Tan, Z.; An, X.; Guo, C.-C. *Org. Lett.* **2010**, *12*, 1564; (f) Zhou, J.; Hu, P.; Zhang, M.; Huang, S.; Wang, M.; Su, W. *Chem.-Eur. J.* **2010**, *16*, 5876.
- [12] (a) Wagner, M.; Köhler, K.; Djakovitch, L.; Weinkauff, S.; Hagen, V.; Muhler, M. *Top. Catal.* **2000**, *13*, 319; (b) Corma, A.; Garcia, H. *Top. Catal.* **2008**, *48*, 8.
- [13] (a) Pröckl, S. S.; Kleist, W.; Gruber, M. A.; Köhler, K. *Angew. Chem.* **2004**, *116*, 1917; *Angew. Chem., Int. Ed.* **2004**, *43*, 1881; (b) Yin, L.; Liebscher, J. *Chem. Rev.* **2007**, *107*, 133; (c) Lee, D.-H.; Kim, J.-H.; Jun, B.-H.; Kang, H.; Park, J.; Lee, Y.-S. *Org. Lett.* **2008**, *10*, 1609; (d) Wan, Y.; Wang, H.; Zhao, Q.; Klingstedt, M.; Terasaki, O.; Zhao, D. *J. Am. Chem. Soc.* **2009**, *131*, 4541; (e) Komáromi, A.; Novák, Z. *Chem. Commun.* **2008**, 4968; (f) Choi, M.; Lee, D.-H.; Na, K.; Yu, B.-W.; Ryoo, R. *Angew. Chem.* **2009**, *121*, 3727; *Angew. Chem., Int. Ed.* **2009**, *48*, 3673; (g) Jin, M.-J.; Lee, D.-H. *Angew. Chem.* **2010**, *112*, 1137; *Angew. Chem., Int. Ed.* **2010**, *49*, 1119.
- [14] Pillai, U. R.; Sahle-Demessie, E. *Green Chem.* **2004**, *6*, 161.
- [15] Sheng, Z.; Wu, Z.; Liu, Y.; Wang, H. *Catal. Commun.* **2008**, *9*, 1941.
- [16] (a) Kantam, M. L.; Pal, U.; Sreedhar, B.; Bhargava, S.; Iwasawa, Y.; Tada, M.; Choudary, B. M. *Adv. Synth. Catal.* **2008**, *350*, 1225; (b) Narske, R. M.; Klabunde, K. J.; Fultz, S. *Langmuir* **2002**, *18*, 4819.

(Zhao, C.)