高性能的二维层状材料硫化钨界面层的有机太阳能电池

马春燕 傅伟飞 黄国伟 陈红征* 徐明生*

(浙江大学硅材料国家重点实验室 高分子科学与工程学系 杭州 310027)

摘要 化学剥离的硫化钨二维层状材料在经过紫外臭氧处理后用作有机太阳能电池的空穴传输层, 可以显著提高电池器件的光电转化效率至8.37%; 作为空穴传输层, 硫化钨二维层状材料可以与经典的空穴传输材料PEDOT:PSS相媲美. 利用X射线光电子能谱(XPS)、拉曼光谱(Raman)、原子力显微镜(AFM)对硫化钨的结构和形貌进行分析. 结果表明, 紫外臭氧处理过后, 氧原子能填充硫化钨因锂插层剥离而产生的硫空位, 减少它的缺陷, 并且使其部分被氧化, 从而改善硫化钨的电学性能.

关键词 二维层状材料; 硫化钨; 有机太阳能电池; 空穴传输层; 高性能

Two-Dimensional WS₂ Sheets as Interfacial Layer for High-Performance Organic Solar Cells

Ma, Chunyan Fu, Weifei Huang, Guowei Chen, Hongzheng* Xu, Mingsheng*

(State Key Laboratory of Silicon Materials, Department of Polymer Science and Engineering, Zhejiang University, Hangzhou 310027)

Abstract Two-dimensional layered WS₂ sheets is used as the hole extraction layer (HEL) in organic solar cells (OSCs). We find that UV-ozone treatment of the chemically exfoliated WS₂ sheets can significantly improve the device performance of the OSCs with the power conversion efficiency (PCE) of about 8.37%, which is comparable to the OSCs with the standard PEDOT:PSS as the HEL. We attribute the improvement to the incorporation of oxygen into the lattice of the WS₂ sheets. The oxygen incorporation reduces the lattice vacancies of WS₂ sheets and makes the WS₂ partially oxidized and consequently improves the electrical properties of the WS₂ sheets.

Keywords two-dimensional layered materials; WS₂; organic solar cells; hole extraction layer; high-performance

1 Introduction

Graphene-like two-dimensional (2D) materials^[1] such as transition metal dichalcogenides (TMDs) are the current subject of intense research because of their unique electronic, optical and chemical properties. These features make them possess great potentials for various applications such as for hydrogen evolution^[2,3] and photovoltaics.^[4] 2D TMDs such as MoS₂ and WS₂ layers have been employed as active layers for solar cells, however, the power conversion efficiency (PCE) is most lower than 4.0%.^[5] In particular, the 2D TMD materials were reported to only absorb about 5.0% of incident sunlight,^[6] which suggests that the 2D TMDs are nearly transparent.

In recent years, organic solar cells (OSCs) have attracted great interest due to many advantages,^[7] including molecular level design of active materials, easy fabrication of large-area and light-weight as well as potentially low-cost. And the reported PCE of OSCs is up to 10%.^[8] High-performance OSCs comprise several interfaces^[9]

between two adjoining materials at which the separation of the photogenerated charge carriers occurs and which facilitate carriers transport and collection. In state-of-the-art OSCs, a layer of PEDOT:PSS is commonly used as a standard anode interfacial material, due to its high conductivity and suitable work function (*ca.* 5.1 eV) for efficient hole extraction and exceptional solution processability. However, the high acidity and the hygroscopic features of PEDOT:PSS hinder the long-term stability of the devices.^[10]

Recently, we have reported that the employment of 2D MoS₂ sheets as the anodic interfacial layer in OSCs generates a PCE of about 7.64%^[4,11] comparable to the counterpart device with PEDOT:PSS and our OSCs with the MoS₂ sheets are stable.^[12] Normally, both MoS₂ and WS₂ exhibit *n*-type characteristics but with different band structures.^[13] Accordingly, the OSCs with WS₂ sheets may exhibit different properties from the devices with MoS₂ sheets. Here we report the using of chemically exfoliated 2D WS₂ as the hole extraction layer (HEL) can achieve high-performance

* E-mail: msxu@zju.edu.cn (MSX); hzchen@zju.edu.cn (HZC)

Received April 10, 2015; published June 1, 2015.

Project supported by Zhejiang Provincial Natural Science Foundation of China (Youth Talent Program: R4110030), the Program for New Century Excellent Talents in University (No. NCET-12-0494), the Research Fund for the Doctoral Program of Higher Education (No. 20130101110123) and the Program for 14th China-Japan S&T Cooperation (No. 2013DFG52800).

项目受浙江省自然科学基金(杰出青年基金项目: R4110030)、教育部新世纪优秀人才支持计划(No. NCET-12-0494)、高等学校博士学科点专项科研基金(No. 20130101110123)、科技部政府间国际合作项目(No. 2013DFG52800)资助。

OSCs with the PCE of about 8.37% through UV-ozone treatment of the WS₂ layer.

2 Results and discussion

We synthesized the 2D WS₂ sheets by lithium intercalation (ce-WS₂) and exfoliation followed by exhaustive dialysis. The detailed process can be found in our previous work.^[4] The successful synthesis of WS₂ is evidenced by Raman characterization (Figure 1a). Two prominent peaks emerged at about 353.0 and 415.0 cm⁻¹, corresponding to the in-plane E_{2g}¹ and out-of-plane A_{1g} modes of WS₂,^[14] respectively. The ce-WS₂ sheets have a thickness of about 1.0 nm and lateral dimensions of about 300~400 nm depicted by the cross-sectional line profile (inset in Figure 1b) based on atomic force microscope (AFM) measurement, suggesting single layer of the ce-WS₂ sheets. We also investigated the atomic structures of the ce-WS₂ sheets by high-resolution transmission electron microscope (TEM). This further (Figure 1c, 1d) reveals defects such as vacancies due to the absence of atoms in the structure and lattice distortion of the ce-WS₂ sheets, which is not a surprise by considering the method used for the synthesis.^[15]

The device configuration of our OSCs is depicted in Figure 2a. The device is comprised of an active blend of poly[[4,8-bis[(2-ethylhexyl)oxy]benzo[1,2-*b*:4,5-*b'*]dithiophene-2,6-diyl][3-fluoro-2-[(2-ethylhexyl)carbonyl]thieno[3,4-*b*]thiophenediyl]] (PTB7) as donor and [6,6]-phenyl-C71-butyric acid methyl ester (PC₇₁BM) as acceptor. We used 2D WS₂ sheets as the HEL (Figure 2a), which was prepared by a multiple-step of spin-coating from a 2 mg/mL solution of the ce-WS₂ sheets. Also, we examine the effect of UV-ozone treatment of the 2D WS₂ sheets (O-ce-WS₂) on the performance of the OSCs because we

found that UV-ozone treatment can significantly improve the device performance of the OSCs with 2D MoS₂ sheets as the HEL.^[14]

The photocurrent-voltage (*J-V*) curves of the OSCs fabricated using the ce-WS₂ and O-ce-WS₂ layers are shown in Figure 2b, the relevant parameters are summarized in Table 1. The OSC with ce-WS₂ as the HEL has a PCE of 5.27% with an open circuit voltage (*V*_{OC}), short-circuit current (*J*_{SC}), and fill factor (FF) of 0.66 V, 11.98 mA•cm⁻², and 0.667, respectively. By comparison, the device which used O-ce-WS₂ as the HEL exhibits a significant enhancement of the PCE to 8.37% (58.8% enhancement) with *V*_{OC}, *J*_{SC}, and FF of 0.74 V, 16.54 mA•cm⁻², and 0.684, respectively. This efficiency is only slightly lower than the solar cells with the standard PEDOT:PSS (8.94%) as the HEL. We believe that it is possible to further enhance the device performance by optimizing the manufacture process of the 2D WS₂ HEL layer.

Table 1 Performance of the OSC devices with PEDOT:PSS, ce-WS₂, and O-ce-WS₂ as hole extraction layers, respectively, under AM 1.5G illumination (100 mW•cm⁻²)

Hole extraction layer	<i>V</i> _{OC} /V	<i>J</i> _{SC} /(mA•cm ⁻²)	FF/%	PCE/%
PEDOT:PSS	0.75	16.23	73.4	8.94
ce-WS ₂	0.66	11.98	66.7	5.27
O-ce-WS ₂	0.74	16.54	68.4	8.37

To figure out the underlying reasons for the improvement by UV-ozone treatment, we investigated the phase composition of the 2D WS₂ sheets and possible change of chemical composition of the sheets. Similar to the MoS₂ sheets,^[16] the ce-WS₂ sheets consist of a mixture of two

Figure 1 (a) Raman spectra of ce-WS₂ and O-ce-WS₂ sheets; (b) AFM image of ce-WS₂ sheets with inset showing the cross-sectional line profile of the ce-WS₂ sheets; (c) Top-view high resolution TEM (HRTEM) image of ce-WS₂ sheets. The white dash-circles highlight dislocations and distortions of the crystals; (d) Side-view HRTEM image of a few-layer ce-WS₂ nanosheet, revealing discontinuous crystal fringes along the sheet edges

Figure 2 (a) and (b) Chemical structures of PTB7 and PC₇₁BM used in our solar cells; (c) *J*-*V* characteristics and (d) external quantum efficiency (EQE) spectra of the OSC devices with PEDOT:PSS, ce-WS₂, and O-ce-WS₂ as the HEL, respectively, under AM 1.5G illumination (100 mW·cm⁻²)

distinct phases (prismatic 2H and octahedral 1T) (Figure 3a~3c), and the ce-WS₂ sheets are dominant by 1T phase. The S_{2p} core level does not show obvious change after the UV-ozone treatment (Figure 3b). This indicates that the UV-ozone treatment has not an effect on the phase composition of the ce-WS₂ sheets and thus the enhancement of the device performance is not associated with the phase transition. The S/W atomic ratio of the ce-WS₂ is 1.5, as many S vacancies resulted from the Li intercalation process and are revealed by the high-resolution TEM observation, and the ratio was deviated to 1.4 after the UV-ozone treatment. We observe change in the W_{5p} and W_{4f} core level spectra (Figure 3c). The appearance of a peak at about 36.0 eV indicates the formation of W⁶⁺ state.^[17] It is estimated that about 7.8% W⁴⁺ had been oxidized to W⁶⁺ state in the O-ce-WS₂ sample.

Moreover, it is found that the O_{1s} core level has a significant variation after the UV-ozone treatment (Figure 3d). The O_{1s} peak was convoluted to two peaks at 532.7 and 530.7 eV, which are assigned to adsorbed oxygen and lattice oxygen,^[4] respectively. As listed in Table 2, the atomic concentration of lattice oxygen is increased from 9.0% to 22.6%. The dramatic increase of lattice oxygen concentration and higher oxidized W⁶⁺ states indicate the formation of W—O bonds. In addition, the decrease in the S/W ratio after the UV-ozone treatment suggests that O atoms replaced a portion of S atoms in the sheets. These results strongly demonstrate that WO₃ and WO₂ may be generated after the UV-ozone treatment. To confirm it, we carried out Raman spectrum investigation. As shown in Figure 1a, compared to the ce-WS₂ sheets, three new peaks at 127.0 cm⁻¹, 175.0 cm⁻¹, and 273.0 cm⁻¹ appeared in the O-ce-WS₂ sheets. The 127.0 cm⁻¹ and 175.0 cm⁻¹ peaks are the characteristic peaks of WO₂ phase, and the peak at

273.0 cm⁻¹ is assigned to the W-O-W bending mode of WO₃.^[18] The formation of WO₂ and WO₃ elucidates that the O incorporation into the lattice of WS₂ sheets after the UV-ozone treatment. The occurrence of oxidation of the ce-WS₂ sheets after the UV-ozone treatment is strikingly different from the case of MoS₂ where no detectable oxidation was present.^[4] Despite the incorporation of oxygen into the lattice of WS₂ sheets, the peak shape and the position of 353.0 cm⁻¹ and 415.0 cm⁻¹ peaks are not changed, suggesting the UV-ozone treatment can hardly make variation to the lattice structure of the ce-WS₂ sheets.

The incorporation of oxygen into the WS₂ lattice could reduce S vacancies in the WS₂ sheets and replace some of the S atoms which are implied by the reduced S/W ratio. The reduction of defects in the 2D WS₂ and the change of chemical compositions may influence electrical properties of the 2D WS₂-based films. Because interface plays an important role in device performance of OSCs, we measured the work function (WF) of the ce-WS₂ and the O-ce-WS₂ films by ultraviolet photoelectron spectroscopy (UPS) (Figure 3e). The WF of the WS₂ film increased from about -4.70 eV to -4.90 eV after the UV-ozone treatment. It is well known that *V*_{oc} is normally governed by the energy levels of the donor and acceptor materials. The contact barrier between the WF of ce-WS₂ and the HOMO of PTB7 limits the build-up of *V*_{oc}.

Table 2 Atomic percentage concentrations of the ce-WS₂ and O-ce-WS₂ samples

Sample	W ⁴⁺	W ⁶⁺	S	O _{lattice}	O _{adsorbed}
ce-WS ₂	31.2%	—	46.1%	9.0%	13.7%
O-ce-WS ₂	28.3%	2.4%	41.9%	22.6%	4.9%

Figure 3 (a) Whole XPS spectra of ce-WS₂ and O-ce-WS₂. (b, c and d) XPS spectra showing the S_{2p}, W_{5p}, W_{4f} and O_{1s} core level peaks of ce-WS₂ and O-ce-WS₂. (e) Ultraviolet photoemission spectra (UPS) of ce-WS₂, O-ce-WS₂, and PEDOT:PSS deposited on ITO substrates. (f) Energy diagram of PTB7:PC₇₁BM active layer sandwiched between ITO anode and Al cathode utilizing ce-WS₂ and O-ce-WS₂ as the HEL, respectively

And this poor electrical contact could seriously deteriorate the device performance. The shift of the Fermi level to the valence band of the WS₂ after the UV-ozone treatment is beneficial for the electrical contact with the donor material. As a result, the V_{oc} was increased and this led to improvement of the PCE of the OSCs with the O-ce-WS₂ layer. Furthermore, compared to the OSCs with the ce-WS₂ HEL, the photocurrent of the device with the O-ce-WS₂ layer was enhanced significantly as shown in the external quantum efficiency (EQE) spectra (Figure 2c), which is con-

sistent with the change in J_{sc} . This enhancement in current is attributed to the incorporation of oxygen in the WS₂ layer and the better match of energy levels between the WS₂ and ITO electrode (PTB7) (Figure 3f). Finally, these effects facilitate the charge carrier transport and improve carrier injection at the interfaces and collection by the ITO anode.

We also explored the effect of thickness of WS₂ films on the OSC device performance. We simply controlled the thickness of WS₂ films by changing the spin-coating times of WS₂ solution (Figure S1). From $J-V$ curves (Figure S2)

and relevant parameters of the OSCs (Table S1), we can see that as the WS₂ films thickness increased, the device performance was firstly improved but then became worse. We find that the optimal thickness is about 2~3 nm of the WS₂ films by taking the coverage and series resistance of the film into consideration.

3 Conclusions

We have shown that 2D WS₂ sheets can be used as a HEL layer for high-performance OSCs. The PCE of OSCs with 2D WS₂ HEL is about 8.37%, comparable to the state-of-art PEDOT:PSS. We found that UV-ozone treatment of the pristine WS₂ layer can greatly improve device performance of the OSCs. The treatment resulted in incorporation of oxygen into the lattice of WS₂ and reduction of lattice vacancies as well as partial oxidation of the WS₂. Consequently, the UV-ozone treatment changed the electrical properties of the WS₂ layer and thus improved the device performance of the OSCs.

4 Experimental Section

Chemically exfoliated WS₂ nanosheets were synthesized through Li intercalation. 0.2 g pristine WS₂ crystals (Sigma-Aldrich) were immersed in 2 mL of 2.2 mol/L butyllithium solution in hexane (Sigma-Aldrich) for 2 d. The Li_xWS₂ was filtrated and washed with hexane to remove excess lithium and organic residues. Exfoliation was achieved immediately by ultrasonically Li_xWS₂ in water (10 mg/mL) for 1 h. Exfoliated WS₂ solution was then dialyzed for 3 d, followed by 3500 r/min centrifugation to remove any unexfoliated aggregates. To prepare O-ce-WS₂, the ce-WS₂ ultrathin films were exposed to 10 min UV-ozone treatment.

Prior to device fabrication, the ITO substrates were cleaned by sonication using detergent, deionized water, acetone, and isopropanol sequentially for every 15 min followed by 10 min of ultraviolet ozone treatment. Then PEDOT:PSS (Baytron P AI4083) was spin-coated onto the cleaned ITO and annealed in air at 140 °C for 15 min. The ce-WS₂ was spin-coated onto ITO for 3 times from a 1 mg/mL aqueous solution without further annealing. Then the substrates were transferred into a glovebox for spin coating of PTB7:PC₇₁BM active layer with the thickness of about 90 nm. Poly[(9,9-bis(3'-(*N,N*-dimethylamino)-propyl)-2,7-fluorene)-alt-2,7-(9,9-dioctylfluorene)] (PFN) was deposited as electron transport layer to extract electron to the cathode. Subsequently, samples were loaded into a vacuum deposition chamber (background pressure $\approx 5 \times 10^{-4}$ Pa) to deposit 120 nm thick aluminum cathode with a shadow mask (device area of 4 mm²). The *J-V* curves were measured with Keithley 236 measurement source units at room temperature in air. The photocurrent was measured under a calibrated solar simulator (Abet 300 W) at 100 mW·cm⁻², and the light intensity was calibrated with a standard photovoltaic reference cell. External quan-

tum efficiency (EQE) spectrum was measured with Stanford lock-in amplifier 8300 unit.

TEM images were taken by a FEI TECNAI G2 F20-TWIN TEM operated at 200 kV. The AFM images were taken by a Veeco Multimode atomic force microscopy in the tapping mode. Raman spectra were recorded on inVia Raman microscope. XPS and UPS measurements were conducted using an ESCALAB 250Xi (Thermo) system.

References

- [1] Xu, M. S.; Liang, T.; Shi, M. M.; Chen, H. Z. *Chem. Rev.* **2013**, *113*, 3766.
- [2] Cai, Y.; Yang, X.; Liang, T.; Dai, L.; Ma, L.; Huang, G. W.; Chen, W. X.; Chen, H. Z.; Su, H. X.; Xu, M. S. *Nanotechnology* **2014**, *25*, 465401.
- [3] Xie, J. F.; Zhang, H.; Li, S.; Wang, R. X.; Sun, X.; Zhou, M.; Zhou, J. F.; Lou, X. W.; Xie, Y. *Adv. Mater.* **2013**, *25*, 5807.
- [4] Yang, X.; Fu, W. F.; Liu, W. Q.; Hong, J. H.; Cai, Y.; Jin, C. H.; Xu, M. S.; Wang, H. B.; Yang, D. R.; Chen, H. Z. *J. Mater. Chem. A* **2014**, *2*, 7727.
- [5] Wi, S. J.; Kim, H.; Chen, M.; Nam, H.; Guo, J.; Meyhofer, E.; Liang, X. G. *ACS Nano* **2014**, *8*, 5270.
- [6] Bernardi, M.; Palummo, M.; Grossman, J. C. *Nano Lett.* **2013**, *13*, 3664.
- [7] (a) Cheng, P.; Shi, Q. Q.; Zhan, X. W. *Acta Chim. Sinica* **2015**, *73*, 252. (程沛, 史钦钦, 占肖卫, 化学学报, **2015**, *73*, 252.); (b) Li, J. J. *J. Mater. Chem. A* **2013**, *1*, 2379; (c) Li, Y. F. *Acc. Chem. Res.* **2012**, *45*, 723; (d) Zhang, Z. G.; Li, Y. F. *Sci. China Chem.* **2015**, *58*, 192.
- [8] (a) Liu, Y. S.; Chen, C. C.; Hong, Z. R.; Gao, J.; Yang, Y.; Zhou, H. P.; Dou, L. T.; Li, G.; Yang, Y. *Sci. Rep.* **2013**, *3*, 3356; (b) Zhang, S. Q.; Ye, L.; Zhao, W. C.; Yang, B.; Wang, Q.; Hou, J. H. *Sci. China Chem.* **2015**, *58*, 248; (c) Chen, J. D.; Cui, C. H.; Li, Y. Q.; Zhou, L.; Ou, Q. D.; Li, C.; Li, Y. F.; Tang, J. X. *Adv. Mater.* **2015**, *27*, 1035.
- [9] (a) Ye, S. Y.; Liu, Z. W.; Bian, Z. Q.; Huang, C. H. *Acta Chim. Sinica* **2015**, *73*, 193. (叶森云, 刘志伟, 卞祖强, 黄春辉, 化学学报, **2015**, *73*, 193.); (b) Zuo, L. J.; Jiang, X. X.; Yang, L. G.; Xu, M. S.; Nan, Y. X.; Yan, Q. X.; Chen, H. Z. *Appl. Phys. Lett.* **2011**, *99*, 183306.
- [10] Liu, J.; Xue, Y. H.; Gao, Y. X.; Yu, D. S.; Durstock, M.; Dai, L. M. *Adv. Mater.* **2012**, *24*, 2228.
- [11] Yang, X.; Liu, W. Q.; Xiong, M.; Zhang, Y. Y.; Liang, T.; Yang, J. T.; Xu, M. S.; Ye, J.; Chen, H. Z. *J. Mater. Chem. A* **2014**, *2*, 14798.
- [12] Liu, W. Q.; Yang, X.; Zhang, Y. Y.; Xu, M. S.; Chen, H. Z. *RSC Adv.* **2014**, *4*, 32744.
- [13] Kang, J.; Tonggay, S.; Zhou, J.; Li, J. B.; Wu, J. Q. *Appl. Phys. Lett.* **2013**, *102*, 012111.
- [14] Zhang, X.; Qiao, X. F.; Shi, W.; Wu, J. B.; Jiang, D. S.; Tan, P. H. *Chem. Soc. Rev.* **2015**, *44*, 2757.
- [15] (a) Golub, A. S.; Zubavichus, Y. V.; Slovokhotova, Y. L.; Novikov, Y. N. *Russian Chem. Rev.* **2003**, *72*, 123; (b) Chow, P. K.; Jacobs-Gedrim, R. B.; Gao, J.; Lu, T. M.; Yu, B.; Terrones, H.; Koratkar, N. *ACS Nano* **2015**, *9*, 1520.
- [16] Voiry, D.; Yamaguchi, H.; Li, J. W.; Silva, R.; Alves, D. C.; Fujita, T.; Chen, M. W.; Asefa, T.; Shenoy, V. B.; Eda, G.; Chhowalla, M. *Nat. Mater.* **2013**, *12*, 850.
- [17] (a) Khudorozhko, G. F.; Asanov, I. P.; Mazalov, L. N.; Kravtsova, E. A.; Parygina, G. K.; Fedorov, V. E.; Mironov, J. V. *J. Electron. Spectrosc. Relat. Phenom.* **1994**, *68*, 199; (b) Chen, T. Y.; Chang, Y. H.; Hsu, C. L.; Wei, K. H.; Chiang, C. Y.; Li, L. J. *Int. J. Hydrogen Energy* **2013**, *38*, 12302.
- [18] Liu, F.; Li, L.; Mo, F. Y.; Chen, J.; Deng, S. Z.; Xu, N. S. *Cryst. Growth Des.* **2010**, *10*, 5193.

(Cheng, F.)