壳聚糖固载氧化亚铜催化 C—O 和 C—N 偶联反应

钱存卫* 朱文倩 刘俊龙 王雪敏 仇立干*

(盐城师范学院化学与环境工程学院 盐城 224051)

摘要 制备了四种壳聚糖固载的铜盐催化剂, 以这四种催化剂尝试催化 C—O 和 C—N 的偶联反应, 实验结果显示, 壳聚糖固载的氧化亚铜可以高效催化芳基卤代烃与酚及含氮杂环的偶联反应, 且该方法的底物适应性广. 实验结果还显示, 该催化剂具有易回收、可重复利用的优点, 且多次重复利用后该催化剂的催化活性未明显减弱.

关键词 壳聚糖@Cu₂O; 合成; 催化; 偶联反应

Chitosan@Cu₂O as A Facile, Efficient and Reusable Catalyst for Ligand-Free C—O and C—N Coupling

Qian, Cunwei* Zhu, Wenqian Liu, Junlong Wang, Xuemin Qiu, Ligan*

(School of Chemical and Environmental Engineering, Yancheng Teachers College, Yancheng 224051)

Abstract The coupling reactions of phenols and nitrogen heterocycles with aryl halide were catalyzed by a highly active, readily available and easily recoverable heterogeneous Cu catalyst which was prepared by simply stirring an suspension of chitosan in solvent with copper compound. The result showed that chitosan@Cu₂O catalyst catalyzed the coupling reactions of aryl halides with phenols and nitrogen heterocycles to readily give the corresponding products in moderate to excellent yields. The highly active catalyst can be reused many times without losing its catalytic activity.

Keywords chitosan@Cu catalyst; synthesis; catalyze; Cross-coupling

1 Introduction

N-Arylazoles and aryl ethers are valuable compounds in organic synthesis, pharmaceutical, or biological areas.^[1,2] One of the most common methods for their preparation is the Ullmann-type coupling reaction.^[3] On account of the problems associated with this noteworthy reaction such as long reaction time, high temperature (>200 °C) and stoichiometric amount of copper required as catalyst, organic chemists made persevering efforts to set the stage for satisfactory reaction conditions to overcome this downside. In the past years, significant advances have been achieved for the copper-catalyzed synthesis of *N*-arylazoles and aryl ethers by use of the ligands explored.^[4] With the carefully selected combinations of a catalytic amount of copper sources, bases and ligands, aryl bromides and aryl iodides had been reported to couple with phenols and imidazoles with excellent yields under mild conditions.^[5~16] Although these homogeneous copper-catalysts were successful for coupling reactions, they had some inherent limitations such

as corrosion, toxicity, difficulty in catalyst handling and separation from the reaction system and the recycling of solid waste. These shortcomings also limit their massive applications in industrial fields. Immobilizing the copper catalyst on a heterogeneous support is one of the main strategies to circumvent the aforementioned problems.^[17] Therefore, various heterogeneous supports have been applied to immobile types of copper catalysts to improve these coupling reactions, such as polysaccharides,^[18] graphite,^[19,20] silica,^[21] magnetic materials,^[22,23] maghemite^[24] and functionalized MWCNTs.^[25] Among these supports, recently, chitosan (CS) has attracted significant attention owing to its green and essential roles in transition metal catalyzed reactions.^[26] Several groups have reported the catalytic activity of chitosan-supported metal complexes used as catalysts for C—C bond forming reactions such as the Suzuki cross-coupling reaction (CS-supported Pd catalyst),^[27] Henry reaction (CS-supported Ti catalyst),^[28] hydroformylation reaction (CS-supported Rh catalyst)^[29], for C—N and C—S bonds forming reactions

* Corresponding authors. E-mail: qiancunwei@163.com; chemistry_wmy@163.com

Received December 2, 2018; revised April 4, 2019; published online April 16, 2019.

Project supported by the Natural Science Foundation of the Jiangsu Higher Education Institutions of China (No. 14JKD150009) and the Key Projects of Innovation and Entrepreneurship Training Program for College Students in Jiangsu Province (No. 201710324003Z).

(CS-supported Cu catalyst).^[30–33] As far as we know, there are very few examples available involving it in copper-catalyzed arylation of phenols and azoles. Herein we report that a series of CS-supported Cu catalysts were prepared and applied in arylations of phenols and azoles under ligand-free conditions.

2 Results and discussion

The investigation was initiated by using the coupling of bromobenzene and phenol as a model reaction. Initially we evaluated the catalytic efficiency of different catalysts (**A**, **B**, **C** and **D**) for the *O*-arylation of phenol with bromobenzene. As shown in Table 1 (Entries 1~4), catalyst **A** (CS@Cu₂O) showed better catalytic potency than catalyst **B**, **C** and **D** for the coupling of bromobenzene with phenol. Screening a range of solvent showed DMF to be much more efficacious than other solvents (such as toluene, CH₃CN and DMSO) (Table 1, Entries 1 vs 5~8). To know the effect of bases on the outcome of the reaction, different bases were employed in the coupling reaction and it was observed that K₃PO₄ was the most effective base (Table 1, Entries 1 and 9~13). Therefore K₃PO₄ was used in subsequent reactions as the base. For further optimization of the reaction conditions, increasing yields of the coupling product were observed by simply increasing the dosage of K₃PO₄ to 3.0 equiv (Table 1, Entry 14). As previously reported,^[11] the use of 2.0 equiv. of phenol was propitious to the increasement of yields, and resulted in 95% yield (Table 1, Entry 15). It was that the coupling reaction of phenol

(2.0 mmol) with bromobenzene (1 mmol) gave the best yield in the presence of 0.5 mol% Cu₂O(CS@Cu₂O) and 300 mol% of K₃PO₄ as base in DMF at 120 °C under an Ar atmosphere.

The scope of the copper-catalyzed C—O bond formation was explored by using a variety of aryl bromides or aryl chlorides with substituted phenols under the optimized conditions. The results are listed in Table 2. As shown in Table 2, the coupling reactions were performed well for all the aryl bromides examined with excellent yields. As previously reported,^[11] aryl chlorides displayed lower reactivity than aryl bromides in the coupling reactions (Table 2). As summarized in Table 2, less active aryl chlorides were also successfully coupled with various phenols in good yields. The results clearly revealed that an electron-withdrawing group in the aryl chlorides favored the coupling reactions, however an electron-releasing group in the aryl chlorides went against the coupling reactions. For example, 4-chlorotoluene could be coupled with various phenols to give the products in 61%~69% yields (Table 2, Entries 4 and 5), yet *p*-chloroacetophenone afforded the corresponding products in 68%~76% yields (Table 2, Entries 6~7). The results revealed that the *O*-arylation of electron-rich phenols with aryl chlorides only resulted in good product yields (69%~74%) (Table 2, Entries 1, 3 and 4). The *O*-arylation of 4-chlorophenol with aryl chlorides gave good product yields (61%~68%) (Table 2, Entries 5 and 7), because substituent group (Cl) only possess a weak electron-withdrawing ability. The coupling of 2-naphthol with aryl chlorides was found to proceed in good yields (Table 2, Entry 2).

Because the development of an effective catalytic system for the C—N coupling of *N*-heterocycles (*i.e.* imidazole, 1,2,4-triazole, benzimidazole and indole) is still far from being satisfactory, this optimized conditions also were employed in this reaction. The results are summarized in Table 3. We were delighted to find that the *N*-arylation of *N*-heterocycles with various aryl iodides proceeded smoothly to give the corresponding products in moderate to excellent yields (Table 3, Entries 1~9 and 13~15). The results showed that the electron-rich aryl halides went against the C—N coupling of *N*-heterocycles with various aryl iodides (Table 3, Entries 1~3 vs 4~9). Whereas the coupling of *N*-heterocycles with 4-bromobenzonitrile gave excellent product yields (87%~93%), because substituent group (CN) possesses an electron-withdrawing ability (Table 3, Entries 10~12). As illustrated in Table 3, benzimidazole and indole seemed to be more difficult to react with aryl iodides compared to imidazole and 1,2,4-triazole. The result showed that the reaction of benzimidazole and indole with various aryl iodide gave the corresponding products in moderate to good yields (Table 3, Entries 3, 6, 7 and 9). The *N*-arylation of various *N*-heterocycles and 2-iodotoluene gave only moderate product yields (50%~65%) (Table 3, Entries 13~15), which might be attributable to the influence of steric hindrance. As previously reported,^[11] aryl bromides

Table 1 *O*-Arylation of phenol with bromobenzene: optimization of the reaction conditions^a

Catalyst: **A** CS@Cu₂O, **B** CS@Cu(OAc)₂, **C** CS@CuSO₄, **D** CS@CuI

Entry	Catalyst	Solvent	Base	Yield ^b /%
1	A	DMF	K ₃ PO ₄	61
2	B	DMF	K ₃ PO ₄	48
3	C	DMF	K ₃ PO ₄	40
4	D	DMF	K ₃ PO ₄	37
5	A	CH ₃ CN	K ₃ PO ₄	38
6	A	DMSO	K ₃ PO ₄	58
7	A	Dioxane	K ₃ PO ₄	40
8	A	Toluene	K ₃ PO ₄	18
9	A	DMF	Et ₃ N	23
10	A	DMF	Na ₂ CO ₃	23
11	A	DMF	NaAcO	24
12	A	DMF	Na ₃ PO ₄	43
13	A	DMF	K ₂ CO ₃	50
14 ^c	A	DMF	K ₃ PO ₄	82
15 ^{c,d}	A	DMF	K ₃ PO ₄	95

^a General reaction conditions: 1.5 mmol of phenol, 1.0 mmol of bromobenzene, 1 mol% [Cu], 2.0 mmol of potassium phosphate, 1 mL of anhydrous solvent. ^b Isolated yield. ^c 3.0 mmol of potassium phosphate. ^d 2 mmol of phenol.

Table 2 CS@Cu₂O-catalyzed coupling reaction of aryl bromide/chloride with phenols^a

Entry	Aryl halide	X	Phenol	Product	Yield ^b /%
1		Br			95
		Cl			73
2		Br			90
		Cl			66
3		Br			88
		Cl			74
4		Br			98
		Cl			69
5		Br			87
		Cl			61
6		Br			95
		Cl			76
7		Br			92
		Cl			68

^a Unless otherwise stated. General reaction conditions: 2.0 mmol of phenol, 1.0 mmol of ArBr, 0.5 mol% CS@Cu₂O, 3.0 mmol of K₃PO₄, 0.5 mL of anhydrous DMF under Ar atmosphere for 18 h. ^b Isolated yield.

displayed lower reactivity than aryl iodides in the coupling reactions (Table 3).

To explore the reusability of CS@Cu₂O, the coupling reaction of phenol with chlorobenzene was chosen as a model reaction. As shown in Figure 1, CS@Cu₂O are recyclable without obvious loss of activity. In each cycle, the catalyst was recovered by filtration, washed with ethylacetate (3~5 mL) and then dried under reduced pressure. After CS@Cu₂O was recovered fifth times, its copper content was determined to be 1.82 mmol/g, which was almost equal to that of the newly prepared catalyst. These result clearly reveals the heterogeneous nature of the catalyst.

3 Conclusions

In conclusion, a simple, general and efficient procedure is described for the cross-coupling of nitrogen and oxygen nucleophiles with aryl halide to readily give the corresponding products in good to excellent yields and with a wide range of functional group tolerance under ligand-free conditions. This catalyst is air-stable, inexpensive and easy to prepare and easy to recover by simple filtration. The reusability of this catalyst is high and the catalyst can be reused four times without significant decrease in its catalytic activity. Further applications of this catalyst to other transformations are currently under investigation.

Table 3 CS@Cu₂O-catalyzed reactions of *N*-heterocyclic amines with aryl bromide/iodides^a

Entry	Aryl halide	X	Azole	Product	Yield ^b /%
1		Br I			88 91
2		Br I			34 87
3		Br I			33 71
4		Br I			52 86
5		Br I			22 83
6		Br I			48 68
7		Br I			37 56
8		Br I			27 74
9		Br I			16 64
10		Br			87

Continued

Entry	Aryl halide	X	Azole	Product	Yield ^b /%
11		Br			93
12		Br			88
13		Br I			24 65
14		Br I			21 55
15		Br I			19 50

^a Unless otherwise stated. General reaction conditions: 2.0 mmol of *N*-heterocyclic amines, 1.0 mmol of ArBr, 0.5 mol% CS @ Cu₂O, 3.0 mmol of K₃PO₄, 0.5 mL of anhydrous DMF under Ar atmosphere for 18 h. ^b Isolated yield.

Figure 1 Reusability of CS@Cu₂O in coupling reaction of chlorobenzene with phenol

4 Experimental section

4.1 Materials and methods

Reagents were obtained from commercial suppliers and used without further purification unless otherwise noted. All reactions were carried out in reaction tube under argon atmosphere. Thin layer chromatography (TLC) was performed using Qingdao silica gel (silica gel GF254). TLC plates were analyzed by ultraviolet (UV) light. ¹H NMR and ¹³C NMR spectra were measured on a Bruker AV 400

MHz using CDCl₃ or DMSO as solvent and TMS as internal standard. Melting points were measured with an X-5 micro-melting point apparatus and are uncorrected. Fourier transform infrared (FT-IR) spectra of all samples were recorded using a Bruker Vertex 80. The thermal stability of the samples was evaluated by thermogravimetric analysis (Mettler Toledo TGA /SDTA851E, Switzerland) under an nitrogen (N₂) atmosphere over the temperature range of 30~800 °C in flowing N₂ at a heating rate of 5 °C • min⁻¹. Morphologies and element content these catalysts were investigated by a Nova NanoSEM 450 scanning electron microscopy (SEM) and AZtec X-Max^N 80 energy-dispersive spectrometer (EDS). The powder X-ray diffraction (XRD) patterns of the samples were recorded by a BRUKER D8 ADVANCE X-ray diffractometer using Cu Kα radiation. X-ray photoelectron spectroscopic (XPS) experiment was performed on a Thermo scientific ESCALAB 250Xi electron spectrometer. The Cu amount contents of these catalysts was estimated by inductively coupled plasma atomic emission spectrometry (ICP-AES) using perkin-Elmer optima 8000 dv.

4.2 Catalyst preparation

CS supported copper salts (CuSO₄ and Cu(OAc)₂) were synthesized according to the following procedure: the catalyst was prepared by suspending chitosan in an aqueous solution of CuSO₄ and Cu(OAc)₂ for 3 h under neutral

conditions at 50 °C. After adsorption of the copper, the solid was preconditioned by washing thoroughly to remove any loose Cu compounds and dried under vacuum at 50 °C overnight to give the chitosan@copper catalyst.

Preparation of CS@CuI: The chitosan (1 g) was dispersed in 15 mL of methanol by stirring at room temperature for 15 min. In another beaker, a solution of $\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$ (0.125 g in 15 mL of methanol) was prepared and this solution was added dropwise into the above suspension under stirring. The mixture was stirred at room temperature for 5 h. Then, the reaction mixture was filtrated and the resulting solid was washed with methanol several times to remove impurities and dried. In the next stage, the obtained blue solid was dispersed in 15 mL of methanol by stirring at room temperature and a solution of NaI (1.5 mmol in 15 mL of methanol) was added dropwise into this mixture under stirring. The reaction mixture was stirred at room temperature for 5 h. Afterward, the solid product was isolated by filtration and washed with methanol several times to remove impurities and dried at room temperature.

Preparation of CS@Cu₂O: 0.1 g of Cu₂O nanoparticle and 1 g of chitosan were then dispersed in the above 20 mL of toluene and sonicated to obtain a uniform suspension. The suspension was vigorously stirred by means of ultrasonic at room temperature for 60 min to ensure enough Cu₂O nanoparticle adsorbed on the surface of chitosan. After stirring, products were collected by filtration, washed with alcohol several times, and finally dried under vacuum at 50 °C overnight to give the chitosan@Cu₂O.

4.3 Characterization of catalysts

Catalysts have been characterized by FT-IR, TG, XRD, SEM and ICP-AES. As shown in Figure 2, the pure chitosan powder exhibited characteristic absorption bands of O—H and N—H stretching vibrations at 3446 cm^{-1} . For the CS@copper catalysts, the peak at 3437~3415 cm^{-1} becomes sharper and stronger compared to chitosan. The peaks at around 1074, 1389, 1638, and 2877~2925 cm^{-1} correspond to C—O, C—N, N—H, and C—H stretching models of the chitosan molecules, respectively. The FT-IR of the copper catalysts demonstrated that NH₂ and OH coordinate with the metal Cu. The catalysts were also characterized by TG to study their thermal behavior and stability at elevated temperatures. As shown in Figure 3, the TG curves of all CS@copper catalysts involve three mass loss stages during thermal decomposition. Importantly, the TG showed that these catalysts were stable up to 200 °C, suggesting that their high thermal stability allows them to be compatible with most organic reactions. As shown in Figure 4, no signals pertaining to the copper metal were detected by XRD, which is similar to previous reports.^[31] The SEM analysis showed that Cu₂O nanoparticles were spherical and the average diameter of the Cu₂O nanoparticles was about 300~400 nm, which was consistent with specifications of Cu₂O nanoparticles purchased (Figure 5a). CuI nanoparticles take on nanorod shape in the SEM picture, its length is about 150 nm and its diameter is about

20 nm (Figure 5c). The SEM analysis showed that the av-

Figure 2 FT-IR spectra of CS@Cu₂O (A), CS@Cu(OAc)₂ (B), CS@CuI (C) and CS@CuSO₄ (D)

Figure 3 TG Image of (A), CS@Cu(OAc)₂ (B), CS@CuI (C) and CS@CuSO₄ (D)

Figure 4 X-ray diffraction of CS@Cu₂O (A), CS@Cu(OAc)₂ (B), CS@CuI (C) and CS@CuSO₄ (D)

erage diameter of Cu(OAc)₂ and CuSO₄ nanoparticles was about 10 nm and the dispersion of Cu particles was very good (Figures 5b and 5d). Also, various elements in the structures of CS@Cu₂O, CS@Cu(OAc)₂, CS@CuI and CS@CuSO₄ were characterized by energy dispersive X-ray

spectroscopy (EDS) obtained from SEM analysis. As can be seen from Figure 5, carbon, nitrogen, oxygen and copper are present in all synthesized catalysts. In addition, catalyst **C** contains iodine and catalyst **D** contains sulfur. The above elements determined by EDS are consistent with the composition of the prepared catalysts. As shown in the XPS diagram of CS@Cu₂O, in the newly prepared CS@Cu₂O, copper(I) is almost the only form of copper (Figure 6). The copper loading levels of CS@Cu₂O, CS@Cu(OAc)₂, CS@CuI and CS@CuSO₄ measured by ICP-AES were 1.85, 1.93, 1.82, and 1.98 mmol·g⁻¹, respectively. The used CS@Cu₂O was also characterized by infrared spectroscopy. The results are shown in Figure 7. Compared to the infrared spectra of CS@Cu₂O, strong absorption peaks were observed at 1592 and 1464 cm⁻¹ of recovered CS@Cu₂O, which indicating that a small amount of reactants or products were adsorbed on the catalyst. Finally, the surface morphology of used CS@Cu₂O and valence state of copper were also characterized. As shown in Figure 8, the surface morphology of used CS@Cu₂O has changed due to repeated use, and the Cu₂O nanoparticles have changed from spherical to flaky. Although copper(I) is still the main form of copper, the content of copper(II) has increased significantly for the same reason.

Figure 5 Surface morphology and EDS of CS@Cu₂O (A), CS@Cu(OAc)₂ (B), CS@CuI (C) and CS@CuSO₄ (D)

Figure 6 XPS analysis of CS@Cu₂O

Figure 7 FT-IR spectra of CS@Cu₂O and used CS@Cu₂O

Figure 8 Surface morphology (a) and XPS analysis (b) of recycled CS@Cu₂O

4.4 Thermal filtration experiment

Thermal filtration experiment is usually an important test method to detect the heterogeneity of catalyst.^[32] The heterogeneity of CS@Cu₂O was studied by using *O*-arylation of phenol with bromobenzene as template. Firstly, the catalyst was removed by filtration after the reaction proceeded at 110 °C for 2 h, and the filtrate was further heated for 16 h under the same conditions. GC analysis showed that 23% yield was obtained after 2 h of reaction and 25% yield was obtained after 18 h of reaction. Clearly, no appreciable reaction took place after removal of the catalyst. The above experimental results distinctly showed that no active species leached into the liquid phase and provides direct evidence for the heterogeneity of the present catalyst system.

4.5 Catalytic test

Typical representative experimental procedure: CS@Cu₂O ([Cu]=1 mol%), 2-naphthol (2.0 mmol, 288 mg) and K₃PO₄ (638 mg, 3.0 mmol) were added to a screw-capped Schlenk tube under argon. The tube was then evacuated and backfilled with argon (three cycles). Chlorobenzene (1 mmol, 0.10 mL) and dry DMF (0.5 mL) were added by syringe at room temperature. The reaction mixture was stirred at needed temperature (110 °C) for 18 h. The reaction mixture was allowed to reach room temperature and then diluted with dichloromethane and H₂O (5 mL/5 mL). The catalyst was obtained by filtration and washed with 5 mL of ethylacetate. The organic layer was collected, then removed *in vacuo*, and the residue was purified by column chromatography on silica gel to afford the desired product.

Diphenylether:^[6] Colorless liquid; ¹H NMR (400 MHz, CDCl₃) δ: 6.99~7.01 (m, 4H), 7.07~7.11 (m, 2H), 7.30~7.34 (m, 4H).

4-Methoxy-diphenylether:^[24] Colorless liquid; ¹H NMR (400 MHz, CDCl₃) δ: 3.82 (s, 3H), 6.90~6.93 (m, 2H), 6.97~7.09 (m, 5H), 7.31~7.35 (m, 2H).

2-Naphthyl phenylether:^[11] Pale yellow colored solid; m.p. 45~48 °C; ¹H NMR (400 MHz, CDCl₃) δ: 7.17~7.25 (m, 3H), 7.35~7.38 (m, 1H), 7.43~7.55 (m, 5H), 7.78 (d, *J*=8 Hz, 1H), 7.90~7.91 (m, 2H).

4-Methyl-diphenylether:^[6] Colorless liquid; ¹H NMR (400 MHz, CDCl₃) δ: 2.41 (s, 3H), 6.90~6.92 (m, 2H), 6.96 (d, *J*=8.0 Hz, 2H), 7.02~7.05 (m, 1H), 7.10 (d, *J*=8.4 Hz, 2H), 7.28 (t, *J*=8.4 Hz, 2H).

4-Methyl-4'-methoxy-diphenylether:^[33] White solid; m.p. 45~46 °C; ¹H NMR (400 MHz, CDCl₃) δ: 2.30 (s, 3H), 3.77 (s, 3H), 6.84 (d, *J*=8 Hz, 4H), 6.94 (d, *J*=8.4 Hz, 2H), 7.08 (d, *J*=8.4 Hz, 2H).

4-Chloro-4'-methyl diphenylether:^[34] Colorless liquid; ¹H NMR (400 MHz, CDCl₃) δ: 2.29 (s, 3H), 6.85 (d, *J*=8.4 Hz, 4H), 7.09 (d, *J*=8 Hz, 2H), 7.21 (d, *J*=8.4 Hz, 2H).

1-(4'-Phenoxyphenyl)ethenone:^[8] Pale yellow solid; m.p. 52~53 °C; ¹H NMR (400 MHz, CDCl₃) δ: 2.57 (s, 3H), 7.00 (d, *J*=8.4 Hz, 2H), 7.07 (d, *J*=8.0 Hz, 2H), 7.20

(t, *J*=7.2 Hz, 1H), 7.40 (t, *J*=7.6 Hz, 2H), 7.94 (d, *J*=8.4 Hz, 2H).

4-Chloro-4'-acetyldiphenylether:^[34] Pale yellow solid; m.p. 66~67 °C; ¹H NMR (400 MHz, CDCl₃) δ: 2.58 (s, 3H), 6.98~7.02 (m, 4H), 7.35 (d, *J*=8.4 Hz, 2H), 7.95 (d, *J*=8.4 Hz, 2H).

1-Phenyl-1*H*-imidazole:^[35] Pale yellow oily liquid; ¹H NMR (DMSO-*d*₆, 400MHz) δ: 8.27(s, 1H), 7.76 (s, 1H), 7.68~7.65 (m, 2H), 7.55~7.51 (m, 2H), 7.39~7.35 (m, 1H), 7.13 (s, 1H).

1-Phenyl-1*H*-1,2,4-triazole:^[35] Yellow solid; m.p. 46~47 °C; ¹H NMR (DMSO-*d*₆, 400MHz) δ: 9.31 (s, 1H, N=CHN), 8.25 (s, 1H), 7.88 (d, *J*=8.4Hz, 2H, PhH), 7.59~7.55(m, 2H, PhH), 7.43~7.41(m, 1H, PhH).

1-Phenyl-1*H*-benzo[d]imidazole:^[36] Pale yellow oily liquid; ¹H NMR (CDCl₃, 400MHz) δ: 7.98 (s, 1H), 7.78~7.76 (m, 1H), 7.71~7.61 (m, 5H, PhH), 7.53~7.49 (m, 1H), 7.37~7.30 (m, 2H, PhH).

1-(*p*-Tolyl)-1*H*-imidazole:^[35] Pale yellow oily liquid; ¹H NMR (DMSO-*d*₆, 400MHz) δ: 8.23 (s, 1H), 7.71 (s, 1H), 7.53 (d, *J*=7.2 Hz, 2H), 7.32 (m, *J*=7.6 Hz, 2H), 7.10 (s, 1H), 2.345 (s, 3H).

1-(*p*-Tolyl)-1*H*-1,2,4-triazole:^[35] Yellow solid; m.p. 65~67 °C; ¹H NMR (CDCl₃, 400MHz) δ: 8.51 (s, 1H), 8.091 (s, 1H), 7.551 (d, *J*=8.4 Hz, 2H), 7.304 (d, *J*=8.0 Hz, 2H), 2.416 (s, 3H).

1-(*p*-Tolyl)-1*H*-benzo[d]imidazole:^[36] Pale yellow oily liquid; ¹H NMR (DMSO-*d*₆, 400MHz) δ: 8.53 (s, 1H), 7.81~7.79 (m, 1H), 7.59~7.54 (m, 3H), 7.42 (d, *J*=8.0 Hz, 2H), 7.35~7.31 (m, 2H), 2.41 (s, 3H).

1-(*p*-Tolyl)-1*H*-indole:^[35] Yellow oily liquid; ¹H NMR (DMSO-*d*₆, 400MHz) δ: 7.66 (d, *J*=7.6 Hz, 1H), 7.58~7.56 (m, 1H), 7.52 (d, *J*=8.0Hz, 1H), 7.47~7.44 (m, 2H), 7.38~7.34 (m, 2H), 7.20~7.10 (m, 2H), 6.69~6.68 (m, 1H), 2.38 (s, 3H).

1-(4-Methoxyphenyl)-1*H*-1,2,4-triazole:^[37] Yellow solid; m.p. 119~121 °C; ¹H NMR (DMSO-*d*₆, 400 MHz) δ: 8.46 (s, 1H), 8.09 (d, 1H), 7.57 (d, *J*=9.2 Hz, 2H), 7.02 (d, *J*=9.2 Hz, 2H), 3.87 (s, 3H).

1-(*p*-Methoxyphenyl)-1*H*-benzo[d]imidazole:^[38] Yellow solid; m.p. 93~95 °C; ¹H NMR (DMSO-*d*₆, 400 MHz) δ: 8.48 (s, 1H), 7.79~7.77 (m, 1H), 7.59 (d, *J*=8.8 Hz, 2H), 7.53~7.51 (m, 1H), 7.34~7.20 (m, 2H), 7.18 (d, *J*=8.8 Hz, 2H), 3.85 (s, 3H).

4-(1*H*-imidazol-1-yl)benzonitrile:^[39] Yellow solid; m.p. 145~147 °C; ¹H NMR (CDCl₃, 400 MHz) δ: 7.88 (s, 1H), 7.46~7.75 (m, 4H), 7.27 (s, 1H), 7.21 (d, *J*=8.0 Hz, 1H).

4-(1*H*-1,2,4-triazol-1-yl)benzonitrile:^[40] Yellow solid; m.p. 158~160 °C; ¹H NMR (CDCl₃, 400 MHz) δ: 8.67 (s, 1H), 8.16 (s, 1H), 7.88~7.81 (m, 4H).

4-(1*H*-Benzo[d]imidazol-1-yl)benzonitrile:^[41] Yellow solid; m.p. 159~161 °C; ¹H NMR (CDCl₃, 400 MHz) δ: 8.17 (s, 1H), 7.89~7.92 (m, 3H), 7.71~7.68 (m, 2H), 7.60~7.57 (m, 1H), 7.41~7.37 (m, 2H).

1-(*o*-Tolyl)-1*H*-imidazole:^[36] Pale yellow oily liquid; ¹H NMR (CDCl₃, 400MHz) δ: 1H NMR (CDCl₃, 400 MHz) δ: 7.56 (s, 1H), 7.31~7.28 (m, 2H), 7.25~7.22 (m, 2H),

7.19~7.15 (m, 2H), 2.12 (s, 3H)

1-(*o*-Tolyl)-1*H*-1,2,4-triazole:^[42] Yellow oily liquid; ¹H NMR (CDCl₃, 400 MHz) δ : 8.27 (s, 1H), 8.13 (s, 1H), 7.43~7.27 (m, 4H), 2.24 (s, 3H).

1-(*o*-Tolyl)-1*H*-benzo[d]imidazole:^[36] Yellow oily liquid; ¹H NMR (CDCl₃, 400 MHz) δ : 7.98 (s, 1H), 7.893 (d, *J*=8.0 Hz, 1H), 7.45~7.43 (m, 2H), 7.38~7.29 (m, 4H), 7.144 (d, *J*=7.6 Hz, 1H), 2.11 (s, 3H).

Supporting Information. The Supporting Information is available free of charge via the Internet at <http://sioc-journal.cn/>.

References

- [1] For reviews, see:
 - (a) Lindley, J. *Tetrahedron* **1984**, *40*, 1433.
 - (b) Theil, F. *Angew. Chem. Int. Ed.* **1999**, *38*, 2345.
 - (c) Sawyer, J. S. *Tetrahedron* **2000**, *56*, 5045.
 - (d) Thomas, A. W.; Ley, S. V. *Angew. Chem. Int. Ed.* **2003**, *42*, 5400.
 - (e) Kunz, K.; Scholz, U.; Ganzer, D. *Synlett* **2003**, *15*, 2428.
 - (f) Beletskaya, I. P.; Cheprakov, A. V. *Coord. Chem. Rev.* **2004**, *248*, 2337.
- [2] For selected examples of medicinally important diaryl ethers, see:
 - (a) Jung, M. E.; Rohloff, J. C. *J. Org. Chem.* **1985**, *50*, 4909.
 - (b) Singh, S. B.; Pettit, G. R. *J. Org. Chem.* **1990**, *55*, 2797.
 - (c) Deshpande, V. E.; Gohkhale, N. J. *Tetrahedron Lett.* **1992**, *33*, 4213.
 - (d) Evans, D. A.; DeVries, K. M. In *Glycopeptide Antibiotics, Drugs and the Pharmaceutical Sciences*, Ed.: Nagarajan, R., Marcel Dekker, New York, **1994**, p. 63.
 - (e) Zenitani, S.; Tashiro, S.; Shindo, K.; Nagai, K.; Suzuki, K.; Imoto, M.; Gerfelin, A. J. *Antibiot* **2003**, *56*, 617.
 - (f) Cristau, P.; Vors, J. P.; Zhu, J. *Tetrahedron* **2003**, *59*, 7859.
 - (g) Qian, C. W.; Pang, Y.; Fang, D.; Zong, Q. *Chin. J. Pestic. Sci.* **2013**, *15*, 44 (in Chinese).
- [3] (a) Ullmann, F. *Dtsch. Ber. Chem. Ges* **1904**, *37*, 853.
(b) Ullmann, F. *Dtsch. Ber. Chem. Ges.* **1903**, *36*, 2382.
- [4] (a) Mann, G.; Hartwig, J. F. *Tetrahedron Lett.* **1997**, *46*, 8005.
(b) Palucki, M.; Wolfe, J. P.; Buchwald, S. L. *J. Am. Chem. Soc.* **1996**, *118*, 10333.
(c) Mann, G.; Hartwig, J. F. *J. Am. Chem. Soc.* **1996**, *118*, 13109.
(d) Aranyos, A.; Old, D. W.; Kiyomori, A.; Wolfe, J. P.; Sadighi, J. P.; Buchwald, S. L. *J. Am. Chem. Soc.* **1999**, *121*, 4369.
(e) Mann, G.; Hartwig, J. F. *J. Org. Chem.* **1997**, *62*, 5413.
(f) Palucki, M. J.; Wolfe, P.; Buchwald, S. J. *Am. Chem. Soc.* **119**, 3395.
(g) Widenhoefer, R. A.; Zhong, H. A.; Buchwald, S. L. *J. Am. Chem. Soc.* **1997**, *119*, 6787.
- [5] Marcoux, J. F.; Doye, S.; Buchwald, S. L. *J. Am. Chem. Soc.* **1997**, *119*, 10539.
- [6] Ma, D.; Cai, Q. *Org. Lett.* **2003**, *5*, 3799.
- [7] Chen, Y. J.; Chen, H. H. *Org. Lett.* **2006**, *8*, 5609.
- [8] Rao, H.; Jin, Y.; Fu, H.; Jiang, Y.; Zhao, Y. *Chem.-Eur. J.* **2006**, *12*, 3636.
- [9] Wolter, M.; Nordmann, G.; Job, G. E.; Buchwald, S. L. *Org. Lett.* **2002**, *4*, 973.
- [10] Gujadhur, R. K.; Bates, C. G.; Venkataraman, D. *Org. Lett.* **2001**, *3*, 4315.
- [11] Qian, C.; Zong, Q.; Fang, D. *Chin. J. Chem.* **2012**, *30*, 199.
- [12] Qian, C.; Xu, S.; Fang, D.; Zong, Q. *Chin. J. Chem.* **2012**, *30*, 1881.
- [13] Buck, E.; Song, Z.; Tschaen, D.; Dormer, P. G.; Volante, R. P.; Reider, P. J. *Org. Lett.* **2002**, *4*, 1623.
- [14] Lv, X.; Bao, W. J. *Org. Chem.* **2007**, *72*, 3863.
- [15] Qian, C.; Qin, L.; Zong, Q.; Wu, L.; Fang, D. *Bull. Korean Chem. Soc.* **2013**, *34*, 3915.
- [16] Qian, C.; Lv, W.; Zong, Q.; Wang, M.; Fang, D. *Chin. Chem. Lett.* **2014**, *25*, 337.
- [17] Gawande, M. B.; Goswami, A.; Felpin, F.; Asefa, T.; Huang, X.; Silva, R.; Zou, X.; Zboril, R. R.; Varma, S. *Chem. Rev.* **2016**, *116*, 3722.
- [18] Zhao, H.; Xu, J.; Wang, T. *Appl. Catal. A: Gen.* **2015**, *502*, 188.
- [19] Honraedt, A.; Le Callonnec, F.; Le Grogne, E.; Fernandez, V.; Felpin, F.-X. *J. Org. Chem.* **2013**, *78*, 4604.
- [20] Mondal, P.; Sinha, A.; Salam, N.; Roy, A. S.; Jana, N. R.; Islam, S. M. *RSC Adv.* **2013**, *3*, 5615.
- [21] Hajipour, A. R.; Dordahan, F.; Rafiee, F.; Mahdavi, M. *Appl. Organomet. Chem.* **2014**, *28*, 809.
- [22] Nador, F.; Volpe, M. A.; Alonso, F.; Radivoy, G. *Tetrahedron* **2014**, *70*, 6082.
- [23] Baig, R. B. N.; Varma, R. S. *Chem. Commun.* **2012**, *48*, 2582.
- [24] Sharma, R. K.; Gaur, R.; Yadav, M.; Rath, A. K.; Pechousek, J.; Petr, M.; Zboril, R.; Gawande, M. B. *ChemCatChem* **2015**, *7*, 3495.
- [25] Gopiraman, M.; Ganesh Babu, S.; Khatri, Z.; Kai, W.; Kim, Y. A.; Endo, M.; Karvembu, R.; Kim, I. S. *Carbon* **2013**, *62*, 135.
- [26] (a) Carlo, G. Di; Curulli, A.; R. Toro, G.; Bianchini, C.; De Caro, T.; Padeletti, G.; Zane, D.; Ingo, G. M. *Langmuir* **2012**, *28*, 5471.
(b) Yang, Y.-H.; Cui, J.-H.; Zheng, M.-T.; Hu, C.-F.; Tan, S.-Z.; Xiao, Y.; Yang, Q.; Liu, Y.-L. *Chem. Commun.* **2012**, *48*, 380.
- [27] Hardy, J. J. E.; Hubert, S.; Macquarrie, D. J.; Wilson, A. J. *Green Chem.* **2004**, *6*, 53.
- [28] Kadib, A. E.; Molvinger, K.; Bousmina, M.; Brunel, D. *Org. Lett.* **2010**, *12*, 948.
- [29] Makhubela, B. C. E.; Jardine, A.; Smith, G. S. *Green Chem.* **2012**, *14*, 338.
- [30] Baig, R. B. N.; Varma, R. S. *Green Chem.* **2013**, *15*, 1834.
- [31] Shen, C.; Xu, J.; Yu, W.; Zhang, P. *Green Chem.* **2014**, *16*, 3007.
- [32] Collins, G.; Schmidt, M.; O'Dwyer, C.; McGlacken, G.; Holmes, J. *ACS Catal.* **2014**, *4*, 3105.
- [33] Marcoux, J.; Doye, S.; Buchwald, S. J. *Am. Chem. Soc.* **1997**, *119*, 10539.
- [34] Takashi, M.; Fumitoshi, Y.; Masanori, S.; Kenji, K.; Hiroaki, S.; Masami, S.; Tsutomu, F. *Synlett* **2009**, 2457.
- [35] Li, Z.; Meng, F.; Zhang, J.; Xie, J.; Dai, B. *Org. Biomol. Chem.* **2016**, *14*, 10861.
- [36] Jan kova, K.; Jedinak, L.; Volna, T.; Canka, P. *Tetrahedron* **2018**, *74*(5): 606.
- [37] Kantam, M. L.; Venkanna, G. T.; Sridhar, C.; Sreedhar, B.; Choudary, B. M. *J. Org. Chem.* **2006**, *71*, 9522.
- [38] Zhang, Z. J.; Mao, J. C.; Zhu, D.; Wu, F.; Chen, H. L.; Wan, B. S. *Tetrahedron* **2006**, *62*, 4435.
- [39] Zhang, X.; Xia, A.; Chen, H.; Liu, Y. *Org. Lett.* **2017**, *19*(8), 2118.
- [40] Yin, W.; Wang, C.; Huang, Y. *Org. Lett.* **2013**, *15*(8), 1850.
- [41] Hosseini-Sarvari, M.; Razmi, Z. *RSC Adv.* **2014**, *4*, 44105.
- [42] Shelke, G. M.; Rao, V. K.; Jha, M.; Cameron, T. S.; Kumar, A. *Synlett* **2015**, 26(3), 404.

(Li, L.; Fan, Y.)