过渡金属催化的环丙烯聚合反应研究

张泽鹏^{a,b} 郜云鹏^a 陈树峰^{*,b} 王剑波^{*,a}^(a) 北京大学化学与分子工程学院 生物有机与分子工程教育部重点实验室 北京分子科学国家中心 北京 100871)^(b) 内蒙古大学化学化工学院 内蒙古自治区精细有机合成重点实验室 呼和浩特 010021)

摘要 环丙烯是一类最小的不饱和环状化合物, 其在有机化学中是十分重要的合成中间体, 同时在高分子聚合中也是一类独特的单体. 尽管环丙烯的研究大部分集中于有机化学领域, 近年来有关过渡金属催化的环丙烯聚合反应也逐渐引起了人们的兴趣. 综述了环丙烯聚合反应的研究进展, 主要包括加成聚合和开环复分解聚合(ROMP)两类聚合反应, 并从聚合物合成方法学的角度对于该领域的未来发展进行了展望.

关键词 环丙烯; 过渡金属催化; 加成聚合; 开环复分解聚合

Transition-Metal-Catalyzed Polymerization of Cyclopropenes

Zhang, Zepeng^{a,b} Gao, Yunpeng^a Chen, Shufeng^{*,b} Wang, Jianbo^{*,a}^(a) Beijing National Laboratory of Molecular Sciences (BNLMS) and Key Laboratory of Bioorganic Chemistry and Molecular Engineering of Ministry of Education, College of Chemistry and Molecular Engineering, Peking University, Beijing 100871)^(b) Inner Mongolia Key Laboratory of Fine Organic Synthesis, Department of Chemistry and Chemical Engineering, Inner Mongolia University, Hohhot 010021)

Abstract As the smallest unsaturated cyclic compounds in nature, cyclopropenes serve as important synthetic intermediates in organic chemistry as well as unique monomers in polymerization. While cyclopropenes are mostly explored in the domain of organic chemistry, the polymerization reaction of cyclopropenes has gradually attracted the attentions of chemists in recent years. The research progress of cyclopropene polymerization is reviewed, including addition polymerization and ring-opening metathesis polymerization (ROMP), and prospects for the future development of this field from the perspective of polymer synthesis methodology.

Keywords cyclopropene; transition-metal catalysis; addition polymerization; ring-opening metathesis polymerization

1 Introduction

Synthetic polyolefins have been the largest volume class and most significant commercial polymers since the discovery of the Ziegler-Natta catalyst in 1950s. In the past decades, the methods for manufacturing new (co)polymers catalyzed by transition-metal catalysts for various applications, has become a trend in modern synthetic polymer science.^[1-4] Nowadays, polyolefins used as the advanced materials as plastics and membranes and so on can be prepared from simple α -olefins, non-conjugated dienes and cyclic olefins. In particular, norbornene (NBE) and its derivatives are a type of the cyclic olefinic monomers having the strained character, which have been intensively employed through varied polymerization reactions to form

polymers. These polymers hold the property desired for manufacturing the gas separation membranes, liquid-crystalline materials and so on.^[5-6]

The needs for developing novel polymer materials have stimulated further study by finding new polymerization way using the other strained cyclic olefinic monomers. In this context, cyclopropenes (CPEs) are the smallest hydrocarbon ring compounds featuring the C—C double bond inside. They show high reactivity moreover the diverse reaction patterns, owing to the ring strain (≈ 226 kJ/mol).^[7-9] The CPEs can undergo several reactions when catalyzed by the transition-metals,^[10] including the metal carbene-resulted reactions,^[11-14] C—C double bond functionalization^[15-16] and cycloadditions.^[17-18] These reaction patterns of the CPEs are useful showing of the tool-box

* Corresponding authors. E-mail: wangjb@pku.edu.cn; shufengchen@imu.edu.cn

Received October 16, 2020; revised November 8, 2020; published online November 28, 2020.

Project supported by the National Natural Science Foundation of China (No. 91956104) and the Beijing Outstanding Young Scientist Program (No. BJJWZYJH01201910001001).

国家自然科学基金(No. 91956104)和北京市高等学校卓越青年科学家计划(No. BJJWZYJH01201910001001)资助项目.

means expanded in the organic synthetic chemistry.

However, the use of the CPEs in polymerization is still in infancy. So far two pathways were reported by addition polymerization and ring-opening metathesis polymerization (ROMP) (Scheme 1), in which selection of the ways depends on the catalysts applied, and therefore polymers were generated with distinctive polymer main chain structures. The Pd(II) catalysts were firstly reported to polymerize CPEs through addition polymerization, generating the polymers containing cyclopropane moiety in the backbone. More recently, the Rh(I)-catalyzed polymerization of CPEs has been present. On the other hand, earlier studies showed the ROMP of CPEs by using the Schrock-type catalyst systems and recent explorations were more based on the Grubbs-type catalysts. In light of the importance by using the CPEs of the unique ring-straining character as the cyclic olefinic monomer for manufacturing the novel types of the polymers, it is necessary to have a summary focusing on developments of the polymerization methods and the structure identification of the polymers gained in correlation with the property of potential in application in this area. In this context, two important polymerization pathways resulted from the use of the different metal catalysts will be introduced in separate sections, with the emphasis on the monomers employed, the catalyst designation, polymerization process, and the reaction mechanisms.

Scheme 1 Polymerization of cyclopropenes (CPEs)

2 Addition polymerization of cyclopropenes

The driving force for the addition-polymerization of CPEs is derived from the release of ring strain energy gained from converting a π -bond into an σ -bond. The backbone of the resulting polymer thus consists of fully saturated and rigid C3 building blocks. The polymerization of unsubstituted CPE is easy to trigger due to the spontaneous reaction of the thermally unstable monomer.^[19] As for substituted CPEs, the early report showed that the treatment of 1-methylcyclopropene **1** with non-chelated Pd(II) complexes including PdCl_2 , $[\text{Pd}(\eta^3\text{-allyl})\text{Cl}]_2$ and $\text{PdCl}_2((\text{C}_6\text{H}_5)\text{CN})_2$ afforded dimers, along with oligomeric and polymeric ring-opening by-products (Scheme 2, a).^[20] Later, it was observed that the reaction of 3,3-dimethylcyclopropene **2** mediated by Pd(0) complex gave cyclodimers and cyclotetramers (Scheme 2, b).^[21-23]

In 1996, the first example of addition polymerization of monomer **2** was reported, in which a cationic divalent pal-

Scheme 2 Formation of dimer and oligomers with palladium complexes

ladium bearing nitrogen-containing bidentate ligand was employed as the catalyst (Scheme 3).^[24] This catalytic system generated the polymeric products with molecular weight exceeding 10.0 kDa. It was observed that the chelating ligands with greater steric bulk were not favorable for the polymerization, while monomers with smaller substituents were easier to undergo insertion in the process of propagation. Interestingly, the NMR spectra indicated that the polymer structure consisted of 1,2-*cis*-linked C3 repeating units, suggesting that the polymer was partially stereoregular. Based on those observations, the same group^[25] has proposed a mechanism for the polymerization, which involves coordination and insertion as shown in Scheme 3. Meanwhile, comparing the effects of catalysts on polymerization demonstrated that the use of Pd(II) compounds chelated by bisoxazoline ligand could afford

Scheme 3 Palladium-catalyzed addition polymerization of CPEs

the polymer with a molecular weight exceeding 54.0 kDa. The glass and melt transition temperatures T_g and T_m of the resulting polymer are relatively higher. However, these molecular weight values calculated from the initial ratios of monomer to catalyst ($[M]/[C]$) are higher than the theoretical values, suggesting that the chain propagation is relatively faster than initiation and the polymerization process is un-controlled.

In 2014, Nozaki and co-workers^[26] reported that addition polymerization of 3,3-diarylcyclopropenes **3** could be initiated by arylrhodium(I) species (Scheme 4). Notably, the Rh(I) catalyst undergoes 1,4-migration after the insertion of CPE, thereby generating the main chain structure consisting of alternating aryl and cyclopropane units. The steric hindrance and the electronic effects of aryl substituents significantly affect the reaction yield, molecular weight and the rate of 1,4-migration. It is also worth noting that the polymer shows higher solubility than the poly-CPEs synthesized by palladium catalysis due to the dissimilar main structure. However, this polymerization process is uncontrollable, and the substrate scope is relatively narrow.

Scheme 4 Rhodium-catalyzed polymerization via 1,4-rhodium migration

3 Ring-opening metathesis polymerization of cyclopropenes

Ring-opening metathesis polymerization (ROMP) has been extensively explored as an effective tool for generating unsaturated polymers consisting of flexible backbones by using either Schrock-type or Grubbs-type catalysts. ROMP of CPEs follows the general pathway as shown in Scheme 5. First, the metal carbene catalyst coordinates with the π -bond of CPE. Subsequently, $[2+2]$ cycloaddition leads to a fused, highly-strained metallo-bicyclic species, which undergoes ring-opening to form the unsaturated backbone of the polymeric product. In this section, we discuss the ROMP of CPEs according to the type of catalytic systems in Scheme 5.

3.1 Schrock-type catalysts

As strained cyclic olefins, norbornenes have been typically explored as monomers in ROMP. To explore other

Scheme 5 ROMP of CPEs and its general mechanism

types of polymerizable strained cyclic olefins, CPEs have also been investigated in ROMP. In 2006, Schrock and co-workers^[27] reported the first ROMP of 3-methyl-3-phenylcyclopropene **4** using achiral Mo initiators (Scheme 6). By the analysis of the NMR spectrum, it became clear that a new alkylidene unit resembling the catalytic initiator species was generated in the polymerization process. The resulting polymers were isolated in high yields and with narrow polymer dispersity index (PDI). These characteristics are consistent with the feature of living polymerization. The NMR spectra of the polymers also showed that the resulting polymers was linked by *trans* double bonds. Density functional theory (DFT) calculation provided a rationale for the formation of *trans* double bonds of the polymeric products.^[28] In addition, it was observed that the block copolymers of **4** and 2,3-dicarbomethoxynorbornadiene could be obtained with narrow PDI, providing further proof for the livingness of this polymerization.

Scheme 6 Mo-catalyzed ROMP of CPEs

In general, controlling stereoselectivity in polymerization is challenging but crucial for the synthesis of polymers with desired properties. In 2008, Schrock and co-workers^[29] achieved a highly tactic *trans*-selective polymerization of **4** through enantiomorphic site control. The initiators bearing biphenolate or binaphtholate ligands were applied and it was found that highly *trans* linkages were formed, according to the characteristic IR absorptions near 980 cm^{-1} .

In 2010, Schrock group^[30] reported that using their newly designed monoaryloxidepyrrolide (MAP) catalysts (**Mo2** and **Mo3**) bearing a stereogenic metal center, ROMP can be achieved in a *cis*-selective and syndiospecific manner (Scheme 7). The controlling feature of these initiators is distinct from the above-mentioned chain end or

enantiomorphic site control. As shown in Scheme 7, the reaction using MAP catalysts has two features: (i) upon the five-coordinated molybdacycle is formed, the intermediate configuration transforms from tetrahedron to trigonal bipyramid; (ii) the stereochemistry at the metal center inverts as a consequence of ring opening. The controlled attacking direction on CNO face (the plane composed of the C, N and O atoms from MAP catalyst), as well as the inversion of the chiral center of metal together leads to this stereogenic control of the metal center. Based on the structures produced with the same initiators in polymerization of NBE, the authors suggested that the polymer produced with **Mo1** as the initiator has a *cis*, *isotactic* structure (methyl shift of δ 30.0) and the polymer produced with **Mo2** as the initiator has a *cis*, *syndiotactic* structure (methyl shift of δ 32.0), as compared with the *trans* polymer prepared with **Mo4** as the initiator (methyl shift of δ 27.5). No regular structure was obtained when **Mo3** was employed as the initiator at 20 °C, whereas *cis*, *syndiotactic*-polymer formed at -78 °C.

Scheme 7 Control of tacticity in Mo-catalyzed ROMP of CPEs

The mechanistic details have been proposed as shown in Scheme 8. Enantiomorphic site control allows for the for-

mation of isotactic sequence with **Mo1** as the initiator. In contrast, stereogenic metal control promotes syndiotactic-selective pathway with **Mo2** and **Mo3** as the initiators. The structural difference between **Mo2** and **Mo3** is the relative bulk of imido ligand and phenolate ligand. **Mo2** has a larger phenolate ligand, leading to *syn* (pointing towards the imido group) initiation and propagation with the methyl face of the monomer attacking the metal *trans* to the pyrrolide. As the result, *cis*-double bonds are generated upon ring opening. The *syn* and *anti*-isomers of **Mo3** convert rapidly at 20 °C, thus demolishing the stereo-regulation of the propagation process. At -78 °C, this isomerization is prevented, ensuring the possibility for stereocontrol. In contrast to **Mo2**, the imido ligand is larger than the phenolate ligand in **Mo3**. The initial [2+2] step is *anti*-selective, rendering a *trans*- α chain end and an *anti*-alkylidene center. Due to the steric bulk of the imido group, the addition of CPE insertion remains *anti*-selective, namely, pointing to the same direction with propagating polymer chain, which results in *cis*-selective chain growth. For both initiators, the attacking direction of monomer alters with the inversion of the chiral metal center regularly, which guarantees the syndiotactic chain growth. The

Scheme 8 Proposed mechanism of Mo-catalyzed ROMP of CPEs

proposed structures and mechanisms herein are consistent with those for the ROMP of NBE.

3.2 Grubbs-type catalysts

For practical synthetic applications, it is inevitable that the catalysts or initiators are required not only exhibiting high efficiency and selectivity, but also having good functional group tolerance, robustness toward air and moisture as well as degree of polymerization (DP). The Mo carbenes are in general sensitive towards air, whereas the Grubbs-type catalysts are relatively stable and have greater functional group tolerance, as compared with the Schrock-type catalysts. Thus, the Grubbs-type catalysts have also been explored in the synthesis of vinyl-polymers with CPEs as the monomers in recent few years.

In 2008, the ROMP of CPEs with 1st, 2nd, 3rd Grubbs catalysts was reported (Scheme 9).^[31] Based on the ROMP of CPE **4**, Binder and co-workers synthesized the homologous poly(isobutylene) polymers **6** via a ROMP/hydrogenation strategy. The polymers **6** may be used as compatibilizers, showing the thermal hybrid properties of both polyisobutylene and high-density polyethylene. They suggested that the ring-opened vinyl-polymers **5** could be obtained using the 2nd and 3rd Grubbs catalysts in a living manner. Although the kinetic investigation of polymerization process has been conducted to show the living nature of polymerization, it is still a less rigorous judgment due to the relatively broad dispersity of the polymer products. Moreover, the block copolymerization of dicarboxylic

Scheme 9 ROMP of **4** and block copolymerization using Grubbs catalysts

substituted NBE **7** and CPE **4** has also been achieved using the 3rd Grubbs catalysts.^[32]

In contrast to the traditional Grubbs catalysts, Mauduit and co-workers^[33] have recently developed a *Z*-selective olefin metathesis ruthenium catalyst **9**, which allowed for the production of highly *cis*, *syndiotactic*-selective vinyl-polymers similar to those obtained by the above-mentioned Mo-based catalysts (Scheme 10). This catalyst was also designed from the readily accessible *N*-heterocyclic carbene (NHC) ligand.

Scheme 10 *Z*-selective ROMP of CPE **4**

On the other hand, Luh and co-workers^[34] reported an *E*-selective polymerization with a newly designed CPE monomer **10** in 2019 (Scheme 11). By using 1st and 2nd Grubbs catalysts, both linear and cyclic polymers were obtained, respectively, along with the formation of a dimer by-product **11**. The ratio of **11** to *E*-polymer was approximately 1 : 3. A mechanism has been proposed to rationalize the formation of *E*-polymer and dimer **11**. Upon the first ring-opening of cyclopropene, the product **A** may undergo two possible processes to generate either *Z* or *E* double bonds (intermediates **B** and **D**). In the case that a *Z*-double bond forms, ring closure metathesis from **B** follows, giving the cyclohexadiene derivative **C** and regenerating Ru carbene. If an *E*-double bond is generated (intermediate **D**), chain growth continues. Interestingly, these two competing processes ensure that the double bonds in the backbone of the generated polymer all have *E* configuration.

In addition to the above-mentioned ROMP of **4** and **10**, a variety of the ROMP based on other substituted CPE monomers have also emerged in the past few years. Xia and co-workers have systematically explored the ROMP of various 1,1-disubstituted or 1,2-disubstituted CPEs. In 2016, they^[35] reported the controlled ROMP of 1,2-disubstituted CPEs **12a**~**12f** using 3rd generation Grubbs catalyst (Scheme 12). Unexpectedly, the ROMP of **12d** and **12f** could not afford the corresponding polymers due to the decomposition of the catalyst upon adding the monomers. It was supposed that these results might be attributed to the generation of the labile/acidic doubly allylic 1-proton, leading to the failure of polymerization. In addition, they observed that **12a** with benzoic ester or **12e** with phenyl carbonate showed faster rate than their aliphatic counterparts in ROMP, suggesting the significant electronic effects on the polymerization. Moreover, block copolymers could be obtained with low PDI, under careful timing

Scheme 11 Z-selective ROMP of CPE **10**

Scheme 12 Controlled ROMP of **12a**~**12h** using the 3rd Grubbs catalyst

conditions in order to avoid undesired termination of ω -chain end.

In 2015, the first example of living alternating ring-opening metathesis polymerization (AROMP) was reported

ed by Xia and co-workers,^[36] using a designed CPE **13** monomer and cyclopentene (Scheme 13). With 3rd generation Grubbs catalyst, homo polymerization of either **13** or low-strain cyclic olefins was effectively inhibited. However, in the copolymerization with two types of monomers, the ruthenium carbene intermediate generated from the ring-opening of CPE **13** can selectively react with low-strain cyclic olefins in ROMP, allowing the alternating ring-opening metathesis polymerization to proceed. The alternating sequence was observed from NMR spectrum and MALDI-TOF mass spectrometry. The characteristics of living polymerization were also demonstrated by its first order kinetics. The high M_n and low PDI of this living AROMP are attributed to the prohibition of chain transfer and fast single addition in chain growth.

Scheme 13 Controlled ROMP of **13** using the 3rd Grubbs catalyst

Since the ruthenium carbene intermediate generated from the ring-opening of CPE **13** does not proceed further [2 + 2] cycloaddition with another CPE **13**, the same group^[37] proposed a strategy of chain-end functionalization on living ROMP polymers using CPEs **13** (Scheme 14).

Scheme 14 End-capping for ROMP using CPE **13**

Interestingly, the polymerization is still possible after the addition of CPEs. Therefore, this strategy not only can attain end-capping, but also can be utilized for further functionalization, which provides potential opportunities for applications, such as the targeting in biological system.

More recently, the strategy is expanded to the substrate of low-strain cyclic olefins bearing degradable groups. The same group^[38] reported the synthesis of degradable polyacetals and polyketals (Scheme 15). The resulting polymers could be degraded with the treatment of trifluoroacetic acid. Again, using the CPEs **13** that have the unique char-

acteristic to undergo exclusive single addition, thus allowing living AROMP, is the key for the success of such strategy.

Scheme 15 Synthesis of degradable polymers using AROMP

In order to further control the polymer structures, the precise placement of single monomer units in living ROMP was explored by the same group^[39] using CPE (Scheme 16). First, the efficiency of reinitiating the ROMP of NBE from a CPE end-capped poly-NBE was inspected. It was observed that only about half of the CPE-capped PNBE chains was reinitiated due to a strong reversible coordination interaction with the closest backbone olefin. In order to completely reinitiate the chain end, relatively labile ligand 3-bromopyridine was added and the reaction temperature was reduced to $-30\text{ }^{\circ}\text{C}$. Under such conditions, the reaction afforded the block polymer with narrow PDI and the expected M_n . A series of polymers with different branched architectures were synthesized using this method. Moreover, to illustrate the utility of multiple CPE single additions for even more complex multiblock polymer, an NBE triblock copolymer was synthesized by adding different CPEs sequentially after polymerizing a block of poly-NBE. The structure of the triblock copolymer is verified by the NMR spectra, MALDI-TOF MS as well as gel permeation chromatography (GPC).

Scheme 16 Precise placement of CPE and NBE in ROMP

Continuous efforts were made to elucidate the polymerization behavior of different substituted CPEs. CPEs **14a**, **14b** and CPEs **15a**, **15b** were inspected in the ring-opening metathesis using 3rd generation Grubbs catalyst (Scheme 17).^[40] Depending on the substituents, these CPEs either

undergo living homo-addition polymerization or single-addition. It was observed that termination could be avoided in the propagation process when **14a** or **14b** were used as the monomers, resulting in a living homo polymerization. However, the reaction with **15a** or **15b** only gave single addition products. **15a** could undergo AROMP with cyclohexene. Interestingly, switching **15a** to a more electron-rich aliphatic ester substituted CPE **15b** led to a failure of AROMP with cyclohexene, and only single addition occurred. It was proposed that the reactivity difference between **14** and **15** was mainly attributed to the difference of steric repulsions in the $[2+2]$ cycloaddition process, which was supported by DFT calculation. Whereas the failure of **15b** for AROMP as compared with **15a** may be due to a strongly chelated Ru alkylidene upon ring opening of CPE. DFT calculation suggests that more electron-rich aliphatic ester substituted CPE **15b** can stabilize the *O*-chelated alkylidene intermediate better, thus leading to a 17.6 kJ/mol higher barrier for the AROMP of **15b** than benzoate-ester-substituted **15a**.

Scheme 17 Effect of the structure on the reactivity

To further study the effect of substituents on ROMP of CPEs, the difference of polymerization reactivities for a series of 1,1-disubstituted 1-methylcyclopropenes were compared by Xia and co-workers^[41] (Scheme 18). It was observed that 1-methyl-1-carboxylate CPE **16** underwent single addition for direct end functionalization same as **13**, **15a** and **15b**, while 1-methyl-1-carboxymethyl carbonate CPE **17** led to living homo-polymerization same as **14a** and **14b**. Moreover, as shown in Scheme 12, the reaction of 1,2-disubstituted CPEs **12a**~**12f** with 3rd generation Grubbs catalyst leads to controlled polymerization. Besides, the polymerization rate for the ROMP of **14a** was faster than that of **14b**, owing to the stronger coordination of **14b** with Ru catalyst. These results indicate that the reactivity of CPEs is significantly affected by steric and electronic feature of the C1 substituents. Thus, steric hindrance and/or chelation interactions at the Ru carbene center can inhibit propagation and stabilize chain end in ROMP.

Controlled/living polymerization

Single addition

Scheme 18 Comparison of polymerization patterns of different CPEs

4 Conclusion and outlook

From this review, it becomes apparent that CPEs have found significant applications in transition-metal-catalyzed polymerizations. So far there are only rare reports of the addition polymerization of CPEs, and these reactions are featured by uncontrolled activity and affording the polymers with low molecular weight. Therefore, there are still challenges on the addition polymerization of CPEs, aiming for the design of novel controlled methodology to obtain polymers with desired molecular weight, distribution and well-defined substructure. Besides, the polymers bearing rigid cyclopropane units in the backbone prepared by the addition polymerization may have potential applications in developing new materials. For instance, the rigid backbone polymer can regulate its glass transition temperature by adjusting the length of the upper side chain, making it applicable in the field of flexible, stretchable electronic materials. Moreover, the skeleton of polymer bearing the cyclopropane structure may form aperture structure in the microstructure, which may have potential applications in the field of membrane adsorption and separation.

Compared with the addition polymerization of CPEs, CPEs have been extensively explored as monomers in ROMP. Recent developments in ROMP of CPEs have generated a range of functional polymers with different backbone structures and properties. With the accumulation of research data, the relationship between CPE structure and polymerization reactivity has gradually become clear. However, some challenging issues remain in the field. It is still difficult to control the stereoregularity of polymers with desired microstructure.^[42] It is also necessary to expand the scope of the CPE monomers bearing various functional groups for ROMP. To find practical applications of the polymers obtained from the ROMP of CPEs through monomer design or post-functionalization will be an important topic in the future. For example, the generated linear polymers with double bonds in the main chain can be modified by various methods such as hydrogenation, cyclopropanation and so on. Polar groups can be introduced

to the side chain of the block polymer to improve polymer performance, or to the end group to label the polymer for biological detection. Besides, the polymers bearing more flexible and less hydrophobic backbones than the polyN-BEs may be advantageous for developing elastomeric materials. In addition, sequence-controlled polymerization via ROMP of cyclopropenes open up new opportunities for controlling the structure, self-assembly, and macroscopic properties of polymeric materials.

References

- [1] Stgrzel, M.; Mihan, S.; Mulhaupt, R. *Chem. Rev.* **2016**, *116*, 1398.
- [2] Chen, C. *Nat. Rev. Chem.* **2018**, *2*, 6.
- [3] Tan, C.; Chen, C. *Angew. Chem., Int. Ed.* **2019**, *58*, 7192.
- [4] Mu, H.; Pan, L.; Song, D.; Li, Y. *Chem. Rev.* **2015**, *115*, 12091.
- [5] Bermeshev, M. V.; Chapala, P. P. *Prog. Polym. Sci.* **2018**, *84*, 1.
- [6] Ma, S.; Cai, Y.; Tu, Y.; Guan, Y.; Chen, X. *Polym. Chem.* **2016**, *7*, 3520.
- [7] Rubin, M.; Rubina, M.; Gevorgyan, V. *Chem. Rev.* **2007**, *107*, 3117.
- [8] Zhu, Z.-B.; Wei, Y.; Shi, M. *Chem. Soc. Rev.* **2011**, *40*, 5534.
- [9] Vicente, R. *Synthesis* **2016**, *48*, 2343.
- [10] Vicente, R. *Chem. Rev.* **2021**, *121*, 162.
- [11] Zhang, H.; Wang, K.; Wang, B.; Yi, H.; Hu, F.; Li, C.; Zhang, Y.; Wang, J. *Angew. Chem., Int. Ed.* **2014**, *53*, 13234.
- [12] Zhang, H.; Wang, B.; Wang, K.; Xie, G.; Li, C.; Zhang, Y.; Wang, J. *Chem. Commun.* **2014**, *50*, 8050.
- [13] Zhang, H.; Wang, B.; Yi, H.; Zhang, Y.; Wang, J. *Org. Lett.* **2015**, *17*, 3322.
- [14] Wang, B.; Yi, H.; Zhang, H.; Sun, T.; Zhang, Y.; Wang, J. *J. Org. Chem.* **2018**, *83*, 1026.
- [15] Dian, L. Y.; Marek, I. *Chem. Rev.* **2018**, *118*, 8415.
- [16] Dian, L. Y.; Marek, I. *ACS Catal.* **2020**, *10*, 1289.
- [17] Cheng, Q. Q.; Deng, Y. M.; Lankelma, M.; Doyle, M. P. *Chem. Rev.* **2017**, *46*, 5425.
- [18] Li, P.; Zhang, X.; Shi, M. *Chem. Commun.* **2020**, *56*, 5457.
- [19] Wiberg, K. B.; Bartley, W. J. *J. Am. Chem. Soc.* **1960**, *82*, 6375.
- [20] Weigert, F. J.; Baird, R. L.; Shapley, J. R. *J. Am. Chem. Soc.* **1970**, *92*, 6630.
- [21] Binger, P.; McMeeking, J.; Schuchardt, U. *Chem. Ber.* **1980**, *113*, 2372.
- [22] Binger, P.; Schuchardt, U. *Chem. Ber.* **1981**, *114*, 1649.
- [23] Binger, P.; Büch, H. M.; Benn, R.; Mynott, R. *Angew. Chem., Int. Ed. Engl.* **1982**, *21*, 62.
- [24] Rush, S.; Reinmuth, A.; Risse, W. *J. Am. Chem. Soc.* **1996**, *118*, 12230.
- [25] Rush, S.; Reinmuth, A.; Risse, W. *Macromolecules* **1997**, *30*, 7375.
- [26] Shintani, R.; Iino, R.; Nozaki, K. *J. Am. Chem. Soc.* **2014**, *136*, 7849.
- [27] Singh, R.; Czekelius, C. R.; Schrock, R. *Macromolecules* **2006**, *39*, 1316.
- [28] Meena, J. S.; Thankachan, P. P. *Comput. Theor. Chem.* **2013**, *1024*, 1.
- [29] Singh, R.; Schrock, R. R. *Macromolecules* **2008**, *41*, 2990.
- [30] Flook, M. M.; Gerber, L. C. H.; Debelouchina, G. T.; Schrock, R. R. *Macromolecules* **2010**, *43*, 7515.
- [31] Binder, W. H.; Kurzhals, S.; Pulamagatta, B.; Decker, U.; Pawar, G. M.; Wang, D.; Kühnel, C.; Buchmeiser, M. R. *Macromolecules* **2008**, *41*, 8405.
- [32] Binder, W. H.; Pulamagatta, B.; Kurzhals, O. K. S.; Barqawi, H.; Tanner, S. *Macromolecules* **2009**, *42*, 9457.
- [33] Dumas, A.; Tarrieu, R.; Vives, T.; Roisnel, T.; Dorcet, V.; Baslé, O.; Mauduit, M. *ACS Catal.* **2018**, *8*, 3257.
- [34] Peng, J.-J.; Panda, B.; Satyanarayana, K.; Yang, H.-R.; Huang, S.-L.; Huang, M. J.; Chen, C.-h.; Lai, G.; Lai, Y.-Y.; Luh, T.-Y. *Macromolecules* **2019**, *52*, 7749.
- [35] Elling, B. R.; Su, J. K.; Xia, Y. *Chem. Commun.* **2016**, *52*, 9097.

- [36] Elling, B. R.; Xia, Y. *J. Am. Chem. Soc.* **2015**, *137*, 9922.
[37] Elling, B. R.; Xia, Y. *ACS Macro Lett.* **2018**, *7*, 656.
[38] Elling, B. R.; Su, J. K.; Xia, Y. *ACS Macro Lett.* **2020**, *9*, 180.
[39] Elling, B. R.; Su, J. K.; Feist, J. D.; Xia, Y. *Chem* **2019**, *5*, 2691.
[40] Su, J. K.; Jin, Z.; Xia, Y. *Angew. Chem., Int. Ed.* **2019**, *58*, 17771.
[41] Su, J. K.; Lee, S. Y.; Elling, B. R.; Xia, Y. *Macromolecules* **2020**, *53*, 5833.
[42] For a recent example of Grubbs-type *cis*-selective living ROMP, see: Song, J. A.; Peterson, G. I.; Bang, K. T.; Ahmed, T. S.; Sung, J. C.; Grubbs, R. H.; Choi, T. L. *J. Am. Chem. Soc.* **2020**, *142*, 10438.

(Cheng, F.)