分子筛负载铜水相催化 α,β -不饱和化合物的共轭硼化反应

严 沅^{a,b} 周丽洁^{a,b} 韩 彪^{a,b} 张瑶瑶^{*,a}
李博解^{*,a} 汪连生^a 朱 磊^{*,a,b,c}

(^a 湖北工程学院化学与材料科学学院 湖北孝感 432000)

(^b 湖北大学材料科学与工程学院 武汉 430062)

(^c 华中科技大学生物无机化学与药物湖北省重点实验室 武汉 430074)

摘要 有机硼化物是一类重要的有机合成中间体. 以分子筛负载铜为催化剂, 在水相中温和的条件下, 实现 α,β -不饱和化合物的共轭硼化反应, 建立了一种制备 β -硼取代化合物的直接有效的新方法. 该方法操作简单, 底物普适性好, 适用于不同类型取代的底物, 均以较高收率得到目标产物. 催化剂在反应结束后可通过离心分离回收, 循环使用 7 次后依然保持较高的催化反应活性.

关键词 分子筛负载铜; α,β -不饱和化合物; 水相; 回收再利用

Zeolite Immobilized Copper Catalyzed Conjugate Borylation of α,β -Unsaturated Compounds in Aqueous Media

Yan, Feng^{a,b} Zhou, Lijie^{a,b} Han, Biao^{a,b} Zhang, Yaoyao^{*,a}
Li, Bojie^{*,a} Wang, Liansheng^a Zhu, Lei^{*,a,b,c}

(^a School of Chemistry and Materials Science, Hubei Engineering University, Xiaogan, Hubei 432000)

(^b School of Materials Science and Engineering, Hubei University, Wuhan 430062)

(^c Hubei Key Laboratory of Bioinorganic Chemistry & Materia Medica, Huazhong University of Science and Technology, Wuhan 430074)

Abstract An eco-friendly zeolite immobilized copper catalyzed conjugate borylation of α,β -unsaturated compounds which was accomplished in aqueous media under mild conditions was reported. This method provided a direct and efficient pathway to achieve an important class of β -borylated compounds. Desired products were obtained in good to excellent yields with broad substrate scope. The advantages of this newly developed method include operational simplicity, mild conditions, good functional group tolerance and recyclability of catalyst. Remarkably, this zeolite supported copper catalyst could be recovered easily by simple centrifugation and reused for seven times without any significant decrease of catalytic activity.

Keywords zeolite immobilized copper; α,β -unsaturated compound; aqueous media; recycle and reuse

1 Introduction

Organoboron compounds performed as versatile and important building blocks in synthetic methodologies.^[1] The most prominent examples are Suzuki-Miyaura coupling,^[2] Petasis reaction,^[3] oxidation,^[4] allylboration,^[5] ho-

mologation,^[6] 1,2-migration,^[7] carbonylation,^[8] amine synthesis,^[9] and many others.^[10] The introduction of boron groups has been demonstrated to have significant influence on the biological activities of compounds.^[11] Numbers of drugs contain boron functional groups, such as dutog-
liptin,^[12] bortezomib^[13] and ixazomib (Figure 1).^[14] In this

* Corresponding authors. E-mail: lei.zhu@hbeu.edu.cn; yaoyaozhang@hbeu.edu.cn; bojie.li@hbeu.edu.cn

Received November 11, 2020; revised November 17, 2020; published online January 7, 2021.

Project supported by the National Natural Science Foundation of China (No. 21774029), the Natural Science Foundation of Hubei Province (Nos. 2019CFB237, 2019CFB354), the Young and Middle-Aged Science and Technology Innovation Team Project in Higher Education Institutions of Hubei Province (No. T201816), the Natural Science Foundation of Xiaogan City (Nos. XGKJ201910047, XGKJ2020010053), the "Chutian Scholar" Program of Hubei Province and the High-Level Master's Thesis Cultivation Project of Hubei Engineering University.

国家自然科学基金(No. 21774029)、湖北省自然科学基金(Nos. 2019CFB237, 2019CFB354)、湖北省高等学校优秀中青年科技创新团队计划项目(No. T201816)、孝感市自然科学计划(Nos. XGKJ201910047, XGKJ2020010053)、湖北省“楚天学者”计划和湖北工程学院高水平硕士学位论文培育资助项目。

context, the research on efficient methodologies for the synthesis of organoboron compounds gained impetus in recent years. Among them, addition of bis(pinacolato)diboron (B_2pin_2 , **1**) to α,β -unsaturated compounds has attracted more attention because this protocol could provide a direct and powerful tool for the constructions of C—B bonds.^[15] Subsequently, the scope of metal catalysts for this β -borylation of α,β -unsaturated olefins was extended to Pd,^[16] Pt,^[17] Ni,^[18] Rh^[19] and Zn.^[20] Transition metal free methods were also reported.^[21] Notably, after pioneering works of Hosomi^[22] and Miyaara,^[23] Cu-catalyzed β -borylations have been widely explored because copper is green, cheap and abundant. Based on Cu(I) catalysis, conjugate β -borylation of α,β -unsaturated olefins was reported by groups of Yun,^[24] Hoveyda,^[25] Fernández,^[26] and others.^[27] However, Cu(I)-catalyzed procedures must be performed in anhydrous organic solvents. Moreover, these reactions require presence of a strong base and alcohol as proton additive to accelerate the reaction rate. In contrast, Cu(II) catalysis is much easier to handle and could be performed in aqueous media. Because of these unique advantages, Cu(II) catalysis strategies were further developed by Santos,^[28] Časar,^[29] Kobayashi^[30] and our group.^[31] While significant advances have been achieved, new borylation methods with simple operation and sustainable low-cost catalysts are still in high demand.

Figure 1 Biological compounds containing boron functional groups

On the other hand, copper species immobilized on supports were proved to be efficient heterogeneous catalysts in various transformations.^[32] Xu^[33] disclosed that carbon black supported Cu could catalyze borylation of α,β -unsaturated ketones in toluene with methanol as additive. In our previous work,^[34] we have demonstrated that chitosan/poly(vinyl alcohol) composite film supported copper nanoparticles were capable to catalyze such β -borylation process in aqueous media without any additive. Currently, synthesis in aqueous media became more popular because it's less hazardous and less toxic based on the principles of green chemistry.^[35] Thus, we intend to explore new types of catalyst which could be utilized in aqueous media. We conceived zeolite, a cheap and abundant material, may also be served as solid support to anchor

copper active species because zeolite-Cu catalysts have been widely used in oxidations,^[36] carbonylation,^[37] amide formation,^[38] Chan-Lam cross-coupling^[39] and aryl acetylene homocoupling.^[40] To the best of our knowledge, almost no examples of C—B bond formation catalyzed by using zeolite-Cu catalyst have been reported. Hence, we herein reported copper immobilized on zeolite as a simple prepared, highly active and recyclable catalyst for the boron conjugate additions of α,β -unsaturated acceptors in aqueous media.

2 Results and discussion

To test our hypothesis, chalone **2a** was initially selected as the standard substrate in the coupling reaction with bis(pinacolato)diboron (**1**). The zeolite immobilized Cu catalyst (Zeolite-Cu) was prepared in a simple way following known procedures.^[41] To extend the applicability of our method, a one pot strategy of borylation followed by oxidation was tested as the model reaction (Table 1). The study showed that this reaction has a very strong solvent effect. The reaction almost didn't proceed in aprotic solvents like toluene, diethyl ether and tetrahydrofuran (THF) (Table 1, Entries 1~3). Proton source is essential to accelerate the reaction rate and promote the protonation step in the whole catalytic cycle.^[42] Protic solvents, methanol and ethanol gave much better results (Table 1, Entries 4, 5). To

Table 1 Optimization of reaction conditions^a

Entry	Catalyst	Solvent (V : V)	Yield ^b /%
1	Zeolite-Cu	Toluene	NR ^c
2	Zeolite-Cu	Et ₂ O	NR ^c
3	Zeolite-Cu	THF	Trace
4	Zeolite-Cu	EtOH	69
5	Zeolite-Cu	MeOH	71
6	Zeolite-Cu	H ₂ O	37
7 ^d	Zeolite-Cu	H ₂ O	48
8	Zeolite-Cu	THF/H ₂ O (1 : 3)	77
9	Zeolite-Cu	THF/H ₂ O (3 : 1)	66
10	Zeolite-Cu	THF/H ₂ O (1 : 1)	97
11 ^e	Zeolite-Cu	THF/H ₂ O (1 : 1)	84
12	Zeolite + CuCl ₂ ·2H ₂ O	THF/H ₂ O (1 : 1)	42
13	—	THF/H ₂ O (1 : 1)	NR ^c
14 ^f	Zeolite-Cu	THF/H ₂ O (1 : 1)	95

^a Reaction conditions: substrate **2a** (0.2 mmol), B_2pin_2 **1** (1.2 equiv.), catalyst (5 mg), solvent (2 mL), room temperature, air. ^b Isolated yield of product. ^c NR=no reaction. ^d Zeolite-Cu (7.5 mg) was used. ^e Zeolite-Cu (2.5 mg) was used. ^f Performed under Ar atmosphere.

our delight, the Zeolite-Cu catalyst could work in pure water and give the desired product in 37% yield (Table 1, Entry 6). The yield slightly increased when a higher catalyst loading was used (Table 1, Entry 7). In order to further improve the reactivity, we carried out this reaction in aqueous media, a mixture of tetrahydrofuran and water. After screening different combinations in aqueous media (Table 1, Entries 8~10), the β -hydroxyl product **3a** was successfully isolated in 97% yield via two sequential steps (Table 1, Entry 10). A comparable result could be achieved when only half amount of zeolite-Cu was applied as the catalyst (Table 1, Entry 11). It indicated that the prepared Zeolite-Cu catalyst was highly active during the borylation process. When zeolite and copper salt were added separately to the reaction, the yield of product dramatically decreased (Table 1, Entry 12). This result suggested the complex which *in situ* generated by zeolite and copper was not sufficient to catalyze the reaction. In addition, no conversion was observed in absence of catalyst (Table 1, Entry 13) and inert atmosphere was not necessary (Table 1, Entry

14). Thus, the optimized conditions were determined as to run the reaction in THF/H₂O (*V*:*V*=1:1) under air, using Zeolite-Cu as catalyst (Table 1, Entry 10).

With the optimized conditions in hand, the substrate scope of α,β -unsaturated acceptors was further investigated and the results were summarized in Table 1. Chalcones bearing with various substituents at 4-position including both electron-donating and electron-withdrawing functional groups all proceeded smoothly to give corresponding products in good to excellent yields (**3a**~**3g**). Bromo derived substrate (**3e**) resulted in a little lower yield than other halogens, probably due to the decreased solubility of starting ketone. Similar phenomenon was also found for substrates **3n** and **3p**. A better yield was achieved for *meta*-bromo substituted substrate (**3h**). Next, the derivatives of phenyl ketone part were examined, satisfactory results were obtained in all cases (**3i**~**3l**). Disubstituted chalcones were also well-tolerated and the corresponding products were isolated in moderate to good yields (**3m**~**3s**). Remarkably, 4,4'-dimethoxychalcone was almost converted quantitate-

Table 1 Substrate scope of α,β -unsaturated acceptors^{a,b}

^a Reaction conditions: substrate **2** (0.2 mmol), B₂pin₂ **1** (1.2 equiv), Zeolite-Cu 5 mg (2.5 mol% Cu), in THF/H₂O (1 mL/1 mL), room temperature, 12 h, air. ^b Isolated yields.

ively (**3q**). This reaction showed a promising activity when the substrates contain naphthalene or thiophene structures (**3t** ~ **3u**). Besides chalcone derivatives, borylation of α,β -unsaturated ketones having aliphatic-aromatic motifs were also demonstrated to be effective (**3w** ~ **3y**). Steric hindrance have less effect on the reactivity in substrate **3z**. Interestingly, 1,4-addition product was obtained selectively when $\alpha,\beta,\gamma,\delta$ -dienones were used as substrates (**3aa**, **3ab**). Meanwhile, accompanied 1,6-addition byproduct was not detected by crude NMR analysis. Notably, cinnamionitrile was suitable substrate under our optimized conditions (**3ac**). When R^2 are alkyl groups, the reaction also performed well to give desired products (**3ad**, **3ae**) in satisfied yields which further extended the substrate scope of this reaction. Thus, we have demonstrated that quite a broad range of α,β -unsaturated acceptors could be borylated effectively, catalyzed by Zeolite-Cu catalyst in aqueous media under mild conditions.

For further expansion of the practical application of this method, the Zeolite-Cu catalyzed β -borylation of **2m** and **2f** were carried out in 5 mmol scale, and the corresponding products **3m** and **3f** were isolated in gram-scale in similar yields to which obtained in small scale reactions (Scheme 1).

Scheme 1 Gram scale synthesis of **3m** and **3f**

As the zeolite immobilized copper catalyst performed as a heterogeneous catalyst in the β -borylation of α,β -unsaturated acceptors, it's very easy to separate the catalyst from the resulted reaction mixture. Simple centrifugation was efficient to drive the Zeolite-Cu catalyst to the bottom and no additional extraction was required. The representative experimental phenomena were shown in Figure 2, selecting chalcone **2a** as an example. It's obvious that the solid and liquid phase get well separation after centrifuga-

tion. The catalyst could be recovered from the solid phase while product **3a** was further purified and isolated from the liquid phase. This kind of operation simplicity makes our newly developed method much easier for practical application compared with others.

Figure 2 Centrifugation of the reaction mixture obtained from the reaction of chalcone **2a** with **B₂pin₂** **1**

Catalyst reusability is an important factor to evaluate the value of heterogeneous catalyst which also meets the requirement of green chemistry. As mentioned before, we have realized the easy recovery of Zeolite-Cu catalyst after one single reaction. We also measured the X-ray diffraction (XRD) and transmission electron microscope (TEM) images of Zeolite-Cu catalyst before and after the reaction. No obvious difference was observed, which indicated that this catalyst was stable enough to keep its original structure during the reaction. Thus, we turned to check the recyclability of our catalyst. After the reaction of **2a** and **1**, the Zeolite-Cu catalyst was recovered by centrifugation and dried at 45 °C overnight for next use. Remarkably, Zeolite-Cu catalyst showed excellent activities even after being used for seven cycles, as shown in Figure 3. In each cycle, fresh substrate and boron reagent were reacted under standard conditions by using recovered catalyst. In addition, almost no detectable copper leaching was observed in the liquid phase as illustrated by ICP analysis. This result strongly suggested that the Zeolite-Cu was a highly active and recyclable heterogeneous catalyst for the borylation of α,β -unsaturated acceptors.

Figure 3 Recycle and reuse of Zeolite-Cu catalyst

Based on the above results and previous reports,^[28,30,42] a plausible reaction mechanism was proposed as shown in Scheme 2. The Zeolite-Cu complex **A** reacts with **B₂pin₂** in aqueous solution to give key Cu^{II} intermediate **B**. Then

α,β -unsaturated carbonyl compounds are activated by **B** and boron addition may take place via a six member ring transition state **C** to afford **D**. The obtained Cu^{II} enolate **D** is immediately protonated by H_2O to give desired products, β -borylated compounds. Then complex **A** is regenerated after the protonation step.

Scheme 2 Plausible mechanism

3 Conclusions

In conclusion, a new β -borylation strategy towards α,β -unsaturated acceptors using easily prepared zeolite immobilized copper catalyst was developed. This reaction could be carried out in aqueous media under mild conditions. A wide range of functional groups were well tolerated under optimized conditions and desired products were all obtained in moderate to good yields. Remarkably, the Zeolite-Cu catalyst could be easily recovered and reused for seven cycles without any significant decrease of activity. This protocol provides a new green and sustainable method for the introduction of boron group into α,β -unsaturated compounds. The advantages of this newly developed method include simple operation, availability and recyclability of catalyst, mild conditions and good functional group compatibility.

4 Experimental section

4.1 Instruments and reagents

Nuclear magnetic resonance (NMR) spectra were recorded on a Bruker Avance III 400 MHz spectrometer (Karlsruhe, Germany), operating at 400 MHz for ^1H NMR and 100 MHz for ^{13}C NMR in CDCl_3 unless otherwise noted. CDCl_3 is served as the internal standard (δ 7.26) for ^1H NMR and (δ 77.0) for ^{13}C NMR. Purification of products was accomplished using flash column chromatography on silica gel (200~300 mesh). The weight percentage and metal leaching of copper were determined by inductively coupled plasma-optical emission spectroscopy (ICP-OES)

(PerkinElmer, Waltham, USA) analysis. All necessary reagents were purchased from commercial suppliers and used without further purification. The solvents were commercially available dry solvents, which were distilled appropriately under an argon atmosphere or were stored over molecular sieves prior to use.

4.2 Procedure for the preparation of zeolite-Cu catalyst

Zeolite immobilized Cu catalyst was prepared by the literature reported method.^[40] Zeolite Na-Y ($n_{\text{Si}}/n_{\text{Al}}=2.0$) was added into 1.0 mol/L NH_4Cl and exchanged at 80 $^\circ\text{C}$ for 4 h. This process was repeated for four times and the obtained zeolite NH_4Y was washed with distilled water. The zeolite NH_4Y as a powder was dried at 110 $^\circ\text{C}$ for 12 h before next use. In a 50 mL round bottom flask, NH_4Y zeolite (1.0 g) and $\text{CuCl}_2\cdot 2\text{H}_2\text{O}$ (0.52 g) were added into deionized water (30 mL). After stirring for 12 h at room temperature, the mixture was filtered to give $\text{Cu(II)-NH}_4\text{Y}$ zeolite which was then dried overnight at 110 $^\circ\text{C}$. Resulted sample was further deaminated and dehydrated on a vacuum line at 400 $^\circ\text{C}$ for 5 h to give the corresponding Zeolite-Cu catalyst. The copper loading of Zeolite-Cu catalyst was found to be 1.01 mmol/g determined by ICP-OES.

4.3 General procedure for zeolite-Cu catalyzed borylation of α,β -unsaturated acceptors in aqueous media

In a centrifuge tube, THF (1.0 mL) and H_2O (1.0 mL) were successively added to a mixture of Zeolite-Cu (5.0 mg, 2.5 mol%) and B_2pin_2 (**1**) (60.9 mg, 0.24 mmol) under air. The reaction mixture was stirred for 1 h at room temperature, followed by successive addition of substrate **2** (0.2 mmol). After stirring for 12 h at room temperature, the reaction mixture was filtered and the filtrate was extracted with EtOAc (20 mL $\times$ 3). The combined organic phase was concentrated under reduced pressure and the residue was dissolved in THF (3 mL) and H_2O (2 mL). Excess amount of $\text{NaBO}_3\cdot 4\text{H}_2\text{O}$ (244 mg) was then added and the mixture was stirred at room temperature for 4 h. The aqueous layer was extracted with EtOAc (20 mL $\times$ 3), and the combined organic layers were dried over anhydrous Na_2SO_4 . After concentrated under reduced pressure, the crude mixture was purified by flash column chromatography (petroleum ether/ EtOAc , $V:V=4:1\sim 10:1$) to afford the desired product **3**.

3-Hydroxy-1,3-diphenylpropan-1-one (**3a**):^[30a] Colorless oil, yield 97% (43.9 mg). ^1H NMR (400 MHz) δ : 7.97 (d, $J=7.0$ Hz, 2H), 7.61~7.57 (m, 1H), 7.49~7.44 (m, 4H), 7.41~7.43 (m, 2H), 7.33~7.29 (m, 1H), 5.37 (t, $J=6.1$ Hz, 1H), 3.65 (br, 1H), 3.39~3.37 (m, 2H); ^{13}C NMR (100 MHz) δ : 200.1, 142.9, 136.4, 133.6, 128.7, 128.5, 128.1, 127.6, 125.7, 70.0, 47.3.

3-Hydroxy-1-phenyl-3-(*p*-tolyl)propan-1-one (**3b**):^[34] Colorless oil, yield 94% (45.1 mg). ^1H NMR (400 MHz) δ : 7.97 (d, $J=7.0$ Hz, 2H), 7.61~7.57 (m, 1H), 7.49~7.56 (m, 2H), 7.21~7.47 (m, 2H), 7.19~7.21 (m, 2H), 5.34~5.30 (m, 1H), 3.60 (s, 1H), 3.43~3.32 (m, 2H), 2.37 (s,

3H); ^{13}C NMR (100 MHz) δ : 200.1, 140.0, 137.3, 136.5, 133.5, 129.2, 128.6, 128.1, 125.6, 69.8, 47.3, 21.1.

3-(4-Fluorophenyl)-3-hydroxy-1-phenylpropan-1-one (**3c**):^[34] Colorless oil, yield 93% (45.4 mg). ^1H NMR (400 MHz) δ : 7.96~7.94 (m, 2H), 7.61~7.57 (m, 1H), 7.49~7.39 (m, 4H), 7.03~7.08 (m, 2H), 5.34 (t, $J=6.0$ Hz, 1H), 3.72 (br, 1H), 3.35 (d, $J=6.0$ Hz, 2H); ^{13}C NMR (100 MHz) δ : 200.0, 163.4, 160.9, 138.7, 138.6, 136.4, 133.7, 128.7, 128.1, 127.44, 127.36, 115.4, 115.2, 69.4, 47.3.

3-(4-Chlorophenyl)-3-hydroxy-1-phenylpropan-1-one (**3d**):^[30a] Colorless oil, yield 84% (43.8 mg). ^1H NMR (400 MHz) δ : 7.96 (d, $J=7.0$ Hz, 2H), 7.62 (t, $J=7.4$ Hz, 1H), 7.50~7.58 (m, 2H), 7.39~7.34 (m, 4H), 5.34 (dd, $J=7.8$, 4.3 Hz, 1H), 3.66 (s, 1H), 3.35~3.33 (m, 2H); ^{13}C NMR (100 MHz) δ : 200.0, 141.4, 136.4, 133.8, 133.3, 128.74, 128.68, 128.1, 127.1, 69.4, 47.2.

3-(4-Bromophenyl)-3-hydroxy-1-phenylpropan-1-one (**3e**):^[34] yield 67% (40.7 mg), white solid; m.p. 100~102 °C (lit.^[42a] 98~100 °C); ^1H NMR (400 MHz) δ : 7.95 (d, $J=7.0$ Hz, 2H), 7.58~7.62 (m, 1H), 7.51~7.45 (m, 4H), 7.31~7.33 (m, 2H), 5.32 (dd, $J=7.4$, 4.8 Hz, 1H), 3.68 (s, 1H), 3.38~3.28 (m, 2H); ^{13}C NMR (100 MHz) δ : 199.9, 141.9, 136.3, 133.8, 131.6, 128.7, 128.1, 127.5, 121.4, 69.4, 47.2.

3-Hydroxy-1-phenyl-3-(4-(trifluoromethyl)phenyl)propan-1-one (**3f**):^[34] Colorless oil, yield 76% (44.7 mg). ^1H NMR (400 MHz) δ : 7.96 (d, $J=7.0$ Hz, 2H), 7.65~7.55 (m, 5H), 7.46~7.50 (m, 2H), 5.43 (dd, $J=8.1$, 4.0 Hz, 1H), 3.79 (s, 1H), 3.41~3.31 (m, 2H); ^{13}C NMR (100 MHz) δ : 199.8, 146.9, 136.3, 133.9, 130.3, 130.0, 129.6, 129.3, 128.8, 128.1, 126.0, 125.53, 125.50, 125.46, 125.42, 122.7, 69.4, 47.2.

3-Hydroxy-3-(4-methoxyphenyl)-1-phenylpropan-1-one (**3g**):^[30a] Colorless oil, yield 83% (42.5 mg). ^1H NMR (400 MHz) δ : 7.97~7.94 (m, 2H), 7.61~7.57 (m, 1H), 7.49~7.45 (m, 2H), 7.38~7.35 (m, 2H), 6.92~6.90 (m, 2H), 5.31 (dd, $J=7.6$, 4.6 Hz, 1H), 3.81 (s, 3H), 3.38~3.35 (m, 2H); ^{13}C NMR (100 MHz) δ : 200.3, 159.1, 136.6, 135.1, 133.6, 128.7, 128.1, 127.0, 113.9, 69.7, 55.3, 47.3.

3-(3-Bromophenyl)-3-hydroxy-1-phenylpropan-1-one (**3h**):^[34] Colorless oil, yield 81% (49.4 mg). ^1H NMR (400 MHz) δ : 8.0 (d, $J=6.9$ Hz, 2H), 7.66~7.62 (m, 2H), 7.53~7.46 (m, 3H), 7.38~7.40 (m, 1H), 7.28~7.29 (m, 1H), 5.37 (dd, $J=8.1$, 3.9 Hz, 1H), 3.71 (s, 1H), 3.40~3.37 (m, 2H); ^{13}C NMR (100 MHz) δ : 199.9, 145.2, 136.3, 133.8, 130.7, 130.1, 128.9, 128.7, 128.1, 124.3, 122.7, 69.4, 47.2.

3-Hydroxy-3-phenyl-1-(*p*-tolyl)propan-1-one (**3i**):^[34] Colorless oil, yield 90% (43.2 mg). ^1H NMR (400 MHz) δ : 7.84 (d, $J=8.3$ Hz, 2H), 7.41~7.42 (m, 2H), 7.34~7.37 (m, 2H), 7.23~7.30 (m, 1H), 7.26~7.23 (m, 2H), 5.32 (dd, $J=7.0$, 5.0 Hz, 1H), 3.71 (s, 1H), 3.36~3.27 (m, 2H), 2.39 (s, 3H); ^{13}C NMR (100 MHz) δ : 199.8, 144.6, 142.9, 134.0, 129.3, 128.5, 128.2, 127.6, 125.7, 70.0, 47.2, 21.7.

1-(4-Fluorophenyl)-3-hydroxy-3-phenylpropan-1-one (**3j**):^[30a] Colorless oil, yield 84% (41.0 mg). ^1H NMR (400 MHz) δ : 8.00 (dd, $J=8.9$ Hz, 5.4 Hz, 2H), 7.40~7.44 (m, 2H), 7.36~7.40 (m, 2H), 7.29~7.32 (m, 1H), 7.11~7.15 (m, 2H), 5.36 (dd, $J=8.6$, 3.6 Hz, 1H), 3.55 (s, 1H), 3.40~

3.28 (m, 2H); ^{13}C NMR (100 MHz) δ : 198.4, 167.3, 164.7, 142.8, 132.99, 132.96, 130.9, 130.8, 128.6, 127.7, 125.7, 115.9, 115.7, 70.0, 47.3.

3-Hydroxy-1-(4-methoxyphenyl)-3-phenylpropan-1-one (**3k**):^[30a] Colorless oil, yield 86% (44.0 mg). ^1H NMR (400 MHz) δ : 7.95 (m, 2H), 7.43~7.45 (m, 2H), 7.36~7.40 (m, 2H), 7.28~7.32 (m, 1H), 6.94 (d, $J=8.9$ Hz, 2H), 5.34 (dd, $J=8.3$, 3.8 Hz, 1H), 3.87 (s, 3H), 3.79 (s, 1H), 3.36~3.26 (m, 2H); ^{13}C NMR (100 MHz) δ : 198.8, 163.9, 143.0, 130.5, 129.6, 128.5, 127.6, 125.7, 113.8, 70.1, 55.5, 46.9.

3-Hydroxy-3-phenyl-1-(*m*-tolyl)propan-1-one (**3l**):^[34] Colorless oil, yield 96% (46.1 mg). ^1H NMR (400 MHz) δ : 7.77~7.74 (m, 2H), 7.46~7.44 (m, 2H), 7.41~7.35 (m, 4H), 7.33~7.29 (m, 1H), 5.36 (dd, $J=6.9$, 5.2 Hz, 1H), 3.64 (s, 1H), 3.37~3.36 (m, 2H), 2.41 (s, 3H); ^{13}C NMR (100 MHz) δ : 200.4, 142.9, 138.5, 136.6, 134.4, 128.7, 128.6, 128.5, 127.6, 125.7, 125.4, 70.0, 47.4, 21.3.

3-(4-Chlorophenyl)-1-(4-fluorophenyl)-3-hydroxypropan-1-one (**3m**):^[34] Colorless oil, yield 81% (45.2 mg). ^1H NMR (400 MHz) δ : 7.99~7.96 (m, 2H), 7.38~7.33 (m, 4H), 7.16~7.12 (m, 2H), 5.34~5.30 (m, 1H), 3.61 (br, 1H), 3.32~3.30 (m, 2H); ^{13}C NMR (100 MHz) δ : 198.2, 167.4, 164.8, 141.3, 133.4, 132.85, 132.82, 130.9, 130.8, 128.7, 127.1, 116.0, 115.8, 69.4, 47.2.

3-(4-Bromophenyl)-1-(4-fluorophenyl)-3-hydroxypropan-1-one (**3n**):^[34] Colorless oil, yield 68% (43.9 mg). ^1H NMR (400 MHz) δ : 7.99 (dd, $J=8.8$ Hz, 5.4 Hz, 2H), 7.49~7.51 (m, 2H), 7.30~7.32 (m, 2H), 7.12~7.16 (m, 2H), 5.32~5.28 (m, 1H), 3.59 (s, 1H), 3.29 (s, 2H); ^{13}C NMR (100 MHz) δ : 198.2, 167.4, 164.8, 141.8, 132.83, 132.81, 131.7, 130.9, 130.8, 127.4, 121.5, 116.0, 115.8, 69.4, 47.1.

1-(4-Fluorophenyl)-3-hydroxy-3-(4-methoxyphenyl)propan-1-one (**3o**):^[34] Colorless oil, yield 86% (47.1 mg). ^1H NMR (400 MHz) δ : 8.00~7.97 (m, 2H), 7.35~7.37 (m, 2H), 7.11~7.16 (m, 2H), 6.90~6.92 (m, 2H), 5.31~5.27 (m, 1H), 3.81 (s, 3H), 3.45 (br, 1H), 3.35~3.31 (m, 2H); ^{13}C NMR (100 MHz) δ : 198.5, 167.3, 164.7, 159.1, 135.0, 133.1, 133.0, 130.9, 130.8, 127.0, 115.9, 115.7, 113.9, 69.7, 55.3, 47.3.

3-(4-Bromophenyl)-3-hydroxy-1-(4-methoxyphenyl)propan-1-one (**3p**):^[32d] Colorless oil, yield 56% (37.5 mg). ^1H NMR (400 MHz) δ : 7.90~7.92 (m, 2H), 7.48~7.50 (m, 2H), 7.32~7.30 (m, 2H), 6.94 (d, $J=8.9$ Hz, 2H), 5.29~5.26 (m, 1H), 3.874 (br, 1H), 3.867 (s, 3H), 3.32~3.25 (m, 2H); ^{13}C NMR (100 MHz) δ : 198.5, 164.0, 142.0, 131.5, 130.5, 129.4, 127.5, 121.3, 113.9, 69.5, 55.5, 46.7.

3-Hydroxy-1,3-bis(4-methoxyphenyl)propan-1-one (**3q**):^[34] white solid, quant. (57.1 mg). m.p. 100~103 °C (lit.^[43b] 101~103 °C); ^1H NMR (400 MHz) δ : 7.95 (d, $J=8.9$ Hz, 2H), 7.35~7.37 (m, 2H), 6.92 (t, $J=7.9$ Hz, 4H), 5.29~5.26 (m, 1H), 3.87 (s, 3H), 3.81 (s, 3H), 3.72 (s, 1H), 3.34~3.25 (m, 2H); ^{13}C NMR (100 MHz) δ : 198.9, 163.9, 159.0, 135.2, 130.5, 129.6, 127.0, 113.9, 113.8, 69.8, 55.5, 55.3, 46.8.

3-(4-Fluorophenyl)-3-hydroxy-1-(*p*-tolyl)propan-1-one (**3r**):^[31e] Colorless oil, yield 85% (43.9 mg). ^1H NMR (400

MHz) δ : 7.86 (d, $J=8.3$ Hz, 2H), 7.42~7.39 (m, 2H), 7.26~7.27 (m, 2H), 7.03~7.08 (m, 2H), 5.33~5.29 (m, 1H), 3.77 (s, 1H), 3.32~3.25 (m, 2H), 2.42 (s, 3H); ^{13}C NMR (100 MHz) δ : 199.7, 163.4, 160.9, 144.7, 138.74, 138.71, 134.0, 129.4, 128.2, 127.44, 127.36, 115.4, 115.2, 69.5, 47.1, 21.7.

3-(2-Chlorophenyl)-3-hydroxy-1-(4-methoxyphenyl)propan-1-one (**3s**):^[34] Colorless oil, yield 94% (54.7 mg). ^1H NMR (400 MHz) δ : 7.92~7.95 (m, 2H), 7.70~7.72 (m, 1H), 7.35~7.31 (m, 2H), 7.25~7.20 (m, 1H), 6.93 (d, $J=9.0$ Hz, 2H), 5.67~5.61 (m, 1H), 4.07 (br, 1H), 3.86 (s, 3H), 3.54~3.49 (m, 1H), 3.11~3.04 (m, 1H); ^{13}C NMR (100 MHz) δ : 198.8, 163.9, 140.4, 131.1, 130.5, 129.4, 129.2, 128.5, 127.23, 127.19, 113.8, 66.9, 55.5, 44.8.

3-hydroxy-3-(naphthalen-1-yl)-1-phenylpropan-1-one (**3t**):^[34] Colorless oil, yield 82% (45.3 mg). ^1H NMR (400 MHz) δ : 8.07~8.05 (m, 1H), 8.00~7.90 (m, 3H), 7.83~7.81 (m, 2H), 7.59~7.43 (m, 6H), 6.18 (dd, $J=9.0, 2.6$ Hz, 1H), 3.83 (br, 1H), 3.58~3.49 (m, 2H); ^{13}C NMR (100 MHz) δ : 200.2, 138.4, 136.4, 133.7, 133.6, 129.8, 129.0, 128.6, 128.1, 128.0, 126.2, 125.6, 125.5, 123.1, 122.7, 66.7, 46.7.

3-Hydroxy-1-phenyl-3-(thiophen-2-yl)propan-1-one (**3u**):^[34] Colorless oil, yield 80% (37.1 mg). ^1H NMR (400 MHz) δ : 7.95~7.97 (m, 2H), 7.61~7.57 (m, 1H), 7.49~7.45 (m, 2H), 7.26~7.25 (m, 1H), 7.03~6.97 (m, 2H), 5.61~5.57 (m, 1H), 3.83 (s, 1H), 3.51~3.48 (m, 2H); ^{13}C NMR (100 MHz) δ : 199.5, 146.6, 136.3, 133.7, 128.7, 128.1, 126.6, 124.6, 123.5, 66.4, 47.1.

1-(4-Fluorophenyl)-3-hydroxy-3-(thiophen-2-yl)propan-1-one (**3v**):^[34] Colorless oil, yield 69% (34.5 mg). ^1H NMR (400 MHz) δ : 8.01~7.98 (m, 2H), 7.28~7.26 (m, 1H), 7.12~7.17 (m, 2H), 7.04~6.98 (m, 2H), 5.61~5.58 (m, 1H), 3.75 (s, 1H), 3.54~3.41 (m, 2H); ^{13}C NMR (100 MHz) δ : 197.8, 167.3, 164.8, 146.6, 132.90, 132.87, 130.9, 130.8, 126.7, 124.7, 123.5, 115.9, 115.7, 66.3, 47.1.

4-Hydroxy-4-phenylbutan-2-one (**3w**):^[30a] Colorless oil, yield 82% (26.9 mg). ^1H NMR (400 MHz) δ : 7.36 (d, $J=4.5$ Hz, 4H), 7.30~7.27 (m, 1H), 5.17~5.13 (m, 1H), 3.39 (s, 1H), 2.93~2.79 (m, 2H), 2.79 (s, 3H); ^{13}C NMR (100 MHz) δ : 209.1, 142.7, 128.5, 127.6, 125.6, 69.8, 51.9, 30.7.

4-(4-Chlorophenyl)-4-hydroxybutan-2-one (**3x**):^[34] Colorless oil, yield 73% (29.1 mg). ^1H NMR (400 MHz) δ : 7.31~7.27 (m, 4H), 5.13~5.09 (m, 1H), 3.46 (s, 1H), 2.82~2.79 (m, 2H), 2.18 (s, 3H); ^{13}C NMR (100 MHz) δ : 208.9, 141.2, 133.2, 128.6, 127.0, 69.1, 51.7, 30.7.

4-Hydroxy-4-(4-methoxyphenyl)butan-2-one (**3y**):^[34] Colorless oil, yield 61% (23.7 mg). ^1H NMR (400 MHz) δ : 7.29~7.26 (m, 2H), 6.89 (d, $J=8.7$ Hz, 2H), 5.12~5.08 (m, 1H), 3.80 (s, 3H), 3.23 (s, 1H), 2.89~2.76 (m, 2H), 2.19 (s, 3H); ^{13}C NMR (100 MHz) δ : 209.2, 159.1, 134.8, 126.9, 113.9, 69.5, 55.3, 51.9, 30.8.

1-Hydroxy-4,4-dimethyl-1-phenylpentan-3-one (**3z**):^[43c] Colorless oil, yield 71% (29.3 mg). ^1H NMR (400 MHz) δ : 7.38~7.28 (m, 5H), 5.15~5.11 (m, 1H), 3.64 (s, 1H), 2.89~2.87 (m, 2H), 1.13 (s, 9H); ^{13}C NMR (100 MHz) δ : 216.8, 143.0, 128.4, 127.5, 125.6, 70.0, 45.4, 44.3, 26.1.

4-Hydroxy-6-phenylhexan-2-one (**3aa**):^[30a] Colorless oil, yield 51% (19.4 mg). ^1H NMR (400 MHz) δ : 7.41~7.27 (m, 5H), 6.82 (d, $J=16.0$ Hz, 1H), 6.26 (dd, $J=16.0, 6.1$ Hz, 1H), 4.77 (s, 1H), 3.14 (br, 1H), 2.80~2.78 (m, 2H), 2.24 (s, 3H); ^{13}C NMR (100 MHz) δ : 209.0, 136.4, 130.4, 130.0, 128.6, 127.7, 126.5, 68.4, 49.9, 30.9.

3-Hydroxy-1,5-diphenylpent-4-en-1-one (**3ab**):^[34] white solid, yield 50% (25.2 mg), m.p. 57~60 °C (lit.^[43d] 53~54 °C); ^1H NMR (400 MHz) δ : 7.91~7.88 (m, 2H), 7.54~7.50 (m, 1H), 7.42~7.38 (m, 2H), 7.33~7.31 (m, 2H), 7.26~7.22 (m, 2H), 7.18~7.15 (m, 1H), 6.65~6.61 (m, 1H), 6.21~6.27 (m, 6.0 Hz, 1H), 4.89~4.86 (m, 1H), 3.38 (s, 1H), 3.26~3.16 (m, 2H); ^{13}C NMR (100 MHz) δ : 200.3, 136.54, 136.51, 133.6, 130.4, 130.2, 128.7, 128.5, 128.1, 127.7, 126.5, 68.6, 45.2.

3-Hydroxy-3-phenylpropanenitrile (**3ac**):^[30a] Colorless oil, yield 65% (19.1 mg). ^1H NMR (400 MHz) δ : 7.41~7.35 (m, 5H), 5.06~5.03 (m, 1H), 2.78~2.76 (m, 2H), 2.56 (s, 1H); ^{13}C NMR (100 MHz) δ : 141.0, 128.9, 128.8, 125.5, 117.2, 70.1, 27.9.

3-hydroxy-1-phenylbutan-1-one (**3ad**):^[30b] Colorless oil, yield 88% (28.9 mg). ^1H NMR (400 MHz) δ : 7.97~7.94 (m, 2H), 7.60~7.56 (m, 1H), 7.49~7.44 (m, 2H), 4.44~4.37 (m, 1H), 3.41 (s, 1H), 3.20~3.00 (m, 2H), 1.30 (d, $J=6.4$ Hz, 3H); ^{13}C NMR (100 MHz) δ : 200.9, 136.6, 133.6, 128.7, 128.1, 64.0, 46.4, 22.4.

4-Hydroxy-6-methylhept-5-en-2-one (**3ae**): Colorless oil, yield 85% (24.2 mg). ^1H NMR (400 MHz) δ : 5.18~5.13 (m, 1H), 4.80~4.75 (m, 1H), 2.86 (br, 1H), 2.68~2.54 (m, 2H), 2.16 (s, 3H), 1.70 (d, $J=1.4$ Hz, 3H), 1.67 (d, $J=1.4$ Hz, 3H); ^{13}C NMR (100 MHz) δ : 209.6, 135.8, 125.7, 64.7, 50.2, 30.8, 25.7, 18.2; IR (KBr) ν : 3401, 2975, 2914, 1703, 1433, 1355, 1302, 1267, 1163, 1119, 1058, 971, 936, 849, 544 cm^{-1} ; HRMS calcd for $\text{C}_8\text{H}_{15}\text{O}_2$ $[\text{M}+\text{H}]^+$ 143.1067, found 143.1069.

4.4 General procedure for gram-scale synthesis of **3m** and **3f**

In a 100 mL round bottom flask, THF (25 mL) and H_2O (25 mL) were successively added to a mixture of Zeolite-Cu (125 mg, 2.5 mol%) and B_2pin_2 (**1**) (1.52 g, 6.0 mmol) under air. The reaction mixture was stirred for 1 h at room temperature, followed by successive addition of substrate (**2m** or **2f**) (6.0 mmol). After stirring for 12 h at room temperature, the reaction mixture was filtered and the filtrate was extracted with EtOAc (100 mL $\times$ 3). The combined organic phase was concentrated under reduced pressure and the residue was dissolved in THF (30 mL) and H_2O (20 mL). Excess amount of $\text{NaBO}_3 \cdot 4\text{H}_2\text{O}$ (5.60 g) was then added and the mixture was stirred at room temperature for 6 h. The aqueous layer was extracted with EtOAc (50 mL $\times$ 3), and the combined organic layers were dried over anhydrous Na_2SO_4 . After concentrated under reduced pressure, the crude mixture was purified by flash column chromatograph (petroleum ether/EtOAc, $V:V=4:1$) to afford the desired product **3m** and **3f** in 85% (1.18 g) and 81% yield (1.12 g), respectively.

Supporting Information XRD and TEM images of Zeolite-Cu, and ^1H MMR and ^{13}C NMR spectra of compounds **3a**~**3ae**. The Supporting Information is available free of charge via the Internet at <http://sioc-journal.cn>.

References

- [1] (a) Burkhardt, E. R.; Matos, K. *Chem. Rev.* **2006**, *106*, 2617.
(b) Crudden, C. M.; Glasspoole, B. W.; Lata, C. J. *Chem. Commun.* **2009**, *45*, 6704.
(c) Yang, J.; Deng, M.; Yu, T. *Chin. J. Org. Chem.* **2013**, *33*, 693 (in Chinese)
(杨军, 邓敏智, 于涛, 有机化学, **2013**, *33*, 693.)
(d) Huang, H.; Lin, H.; Wang, M.; Liao, J. *Acta Chim. Sinica* **2020**, *78*, 1229 (in Chinese).
(黄浩, 林华鑫, 王敏, 廖建, 化学学报, **2020**, *78*, 1229.)
(e) Wang, G.; Gan, Y.; Liu, Y. *Chin. J. Chem.* **2018**, *36*, 916.
- [2] Lennox, A. J. J.; Lloyd-Jones, G. C. *Chem. Soc. Rev.* **2014**, *43*, 412.
- [3] Muncipinto, G.; Moquist, P. N.; Schreiber, S. L.; Schaus, S. E. *Angew. Chem., Int. Ed.* **2011**, *50*, 8172.
- [4] Ripin, D. H. B.; Cai, W.; Brenek, S. J. *Tetrahedron Lett.* **2000**, *41*, 5817.
- [5] Miura, T.; Nishida, Y.; Morimoto, M.; Murakami, M. *J. Am. Chem. Soc.* **2013**, *135*, 11497.
- [6] Matteson, D. S. *J. Org. Chem.* **2013**, *78*, 10009.
- [7] Shimizu, M. *Angew. Chem., Int. Ed.* **2011**, *50*, 5998.
- [8] Cho, C. S.; Ohe, T.; Uemura, S. *J. Organomet. Chem.* **1995**, *49*, 221.
- [9] Coeffard, V.; Moreau, X.; Thomassigny, C.; Greck, C. *Angew. Chem., Int. Ed.* **2013**, *52*, 5684.
- [10] Smoum, R.; Rubinstein, A.; Dembitsky, V. M.; Srebnik, M. *Chem. Rev.* **2012**, *112*, 4156.
- [11] (a) Kuang, Z.; Chen, H.; Yan, J.; Yang, K.; Lan, Y.; Song, Q. *Org. Lett.* **2018**, *20*, 5153.
(b) Kuang, Z.; Li, B.; Song, Q. *Chem. Commun.* **2018**, *54*, 34.
(c) Gao, G.; Kuang, Z.; Song, Q. *Org. Chem. Front.* **2018**, *5*, 2249.
- [12] Johnson, K. M. S. *Curr. Opin. Invest. Drugs* **2010**, *11*, 455.
- [13] Beenen, M. A.; An, C.; Ellman, J. A. *J. Am. Chem. Soc.* **2008**, *130*, 6910.
- [14] Cvek, B. *Drug Future* **2012**, *37*, 561.
- [15] (a) Stavber, G.; Časar, Z. *ChemCatChem* **2014**, *6*, 2162.
(b) Liu, Q.; Tian, B.; Tian, P.; Tong, X.; Lin G.-Q. *Chin. J. Org. Chem.* **2015**, *35*, 1 (in Chinese)
(刘强, 田兵, 田平, 童晓峰, 林国强, 有机化学, **2015**, *35*, 1.)
(c) Liu, Y.; Zhang, W. *Chin. J. Org. Chem.* **2016**, *36*, 2249 (in Chinese)
(刘媛媛, 张万斌, 有机化学, **2016**, *36*, 2249.)
- [16] Bonet, A.; Gulyás, H.; Koshevoy, I. O.; Estevan, F.; Sanaú, M.; Úbeda, A.; Fernández, E. *Chem.-Eur. J.* **2010**, *16*, 6382.
- [17] Bell, N. J.; Cox, A. J.; Cameron, N. R.; Evans, J. S. O.; Marder, T. B.; Duin, M. A.; Cornelis J.; Elsevier, C. J.; Baucherel, X.; Tulloch, A. A. D.; Tooze, R. P. *Chem. Commun.* **2004**, *16*, 1854.
- [18] Hirano, K.; Yorimitsu, H.; Oshima, K. *Org. Lett.* **2007**, *9*, 5031.
- [19] Shiomi, T.; Adachi, T.; Toribatake, K.; Zhou, L.; Nishiyama, H. *Chem. Commun.* **2009**, *40*, 5987.
- [20] Kajiwar, T.; Terabayashi, T.; Yamashita, M.; Nozaki, K. *Angew. Chem., Int. Ed.* **2008**, *47*, 6606.
- [21] Huang, X.; Hu, J.; Wu, M.; Wang, J.; Peng, Y.; Song, G. *Green Chem.* **2018**, *20*, 255.
- [22] Ito, H.; Yamanaka, H.; Tateiwa, J.-I.; Hosomi, A. *Tetrahedron Lett.* **2000**, *41*, 6821.
- [23] Takahashi, K.; Ishiyama, T.; Miyaura, N. *J. Organomet. Chem.* **2001**, *625*, 47.
- [24] (a) Mun, S.; Lee, J.-E.; Yun, J. *Org. Lett.* **2006**, *8*, 4887.
(b) Lee, J.-E.; Yun, J. *Angew. Chem., Int. Ed.* **2007**, *47*, 145.
- [25] O'Brien, J. M.; Lee, K.-S.; Hoveyda, A. H. *J. Am. Chem. Soc.* **2010**, *132*, 10630.
- [26] Solé, C.; Tatla, A.; Mata, J. A.; Whiting, A.; Gulyás, H.; Fernández, E. *Chem.-Eur. J.* **2011**, *17*, 14248.
- [27] (a) Gao, M.; Thorpe, S. B.; Santos, W. L. *Org. Lett.* **2009**, *11*, 3478.
(b) Chen, I.-H.; Yin, L.; Itano, M.; Kanai, M.; Shibasaki, M. *J. Am. Chem. Soc.* **2009**, *131*, 11664.
(c) Mlynarski, S. N.; Schuster, C. H.; Morken, J. P. *Nature* **2014**, *505*, 386.
(d) Dewhurst, R. D.; Marder, T. B. *Nat. Chem.* **2014**, *6*, 279.
- [28] Thorpe, S. B.; Calderone, J. A.; Santos, W. L. *Org. Lett.* **2012**, *14*, 1918.
- [29] Stavber, G.; Časar, Z. *ChemCatChem* **2014**, *6*, 2162.
- [30] (a) Kobayashi, S.; Xu, P.; Endo, T.; Ueno, M.; Kitanosono, T. *Angew. Chem., Int. Ed.* **2012**, *51*, 12763.
(b) Zhu, L.; Kitanosono, T.; Xu, P.; Kobayashi, S. *Chem. Commun.* **2015**, *51*, 11685.
(c) Zhu, L.; Kitanosono, T.; Xu, P.; Kobayashi, S. *Beilstein J. Org. Chem.* **2015**, *11*, 2007.
- [31] (a) Li, B.; Wang, L.; Qin, C.; Zhu, L. *Catal. Commun.* **2016**, *86*, 23.
(b) Zhu, L.; Wang, L.-S.; Li, B.; Fu Q.; Zhang, C.-P.; Li, W. *Chem. Commun.* **2016**, *52*, 6371.
(c) Zhu, L.; Li, B.; Wang, S.; Wang, W.; Wang, L.; Ding, L.; Qin, C. *Polymers* **2018**, *10*, 385.
(d) Wang, W.; Li, B.-J.; Xiao, Z.-F.; Yan, F.; Wei, P.-R.; Wang, L.-S.; Zhu, L. *J. Chin. Chem. Soc.* **2018**, *65*, 81.
(e) Wang, W.; Xiao, Z.; Huang, C.; Zheng, K.; Luo, Y.; Dong, Y.; Shen, Z.; Li, W.; Qin, C. *Polymers* **2019**, *11*, 1417.
- [32] Gawande, M. B.; Goswami, A.; Felpin, F.-X.; Asefa, T.; Huang, X.; Silva, R.; Zou, X.; Zboril, R.; Varma, R. S. *Chem. Rev.* **2016**, *116*, 3722.
- [33] Zhou, X.-F.; Sun, Y.-Y.; Wu, Y.-D.; Dai, J.-J.; Xu, J.; Huang, Y.; Xu, H.-J. *Tetrahedron* **2016**, *72*, 5691.
- [34] Wen, W.; Han, B.; Yan, F.; Ding, L.; Li, B.; Wang, L.; Zhu, L. *Nanomaterials* **2018**, *8*, 326.
- [35] Anastas, P.; Eghbali, N. *Chem. Soc. Rev.* **2010**, *39*, 301.
- [36] (a) Brezicki, G.; Kammert, J. D.; Gunnoe, T. B.; Paolucci, C.; Davis, R. J. *ACS Catal.* **2019**, *9*, 5308.
(b) Vanelderen, P.; Snyder, B. E. R.; Tsai, M.-L.; Hadt, R. G.; Vancauwenbergh, J.; Coussens, O.; Schoonheydt, R. A.; Sels, B. F.; Solomon, E. I. *J. Am. Chem. Soc.* **2015**, *137*, 6383.
(c) Wu, J.-F.; Gao, X.-D.; Wu, L.-M.; Wang, W. D.; Yu, S.-M.; Bai, S. *ACS Catal.* **2019**, *9*, 8677.
- [37] Blasco, T.; Boronat, M.; Concepción, P.; Corma, A.; Law, D.; Vidal-Moya, J. A. *Angew. Chem., Int. Ed.* **2007**, *46*, 3938.
- [38] Moglie, Y.; Buxaderas, E.; Mancini, A.; Alonso, F.; Radivoy, G. *ChemCatChem* **2019**, *11*, 1487.
- [39] Garnier, T.; Sakly, R.; Danel, M.; Chassaing, S.; Pale, P. *Synthesis* **2017**, *49*, 1223.
- [40] Kuhn, P.; Pale, P.; Sommer, J.; Louis, B. *J. Phys. Chem. C* **2009**, *113*, 2903.
- [41] Zhou, L.; Li, S.; Su, Y.; Li, B.; Deng, F. *Solid State Nucl. Magn. Reson.* **2015**, *66*~67, 29.
- [42] Isegawa, M.; Sameera, W. M. C.; Sharma, A. K.; Kitanosono, T.; Kato, M.; Kobayashi, S.; Morokuma, K. *ACS Catal.* **2017**, *7*, 5370.
- [43] (a) Singh, P.; Bhardwaj, A. *J. Med. Chem.* **2010**, *53*, 3707.
(b) Ravikumar, K. S.; Sinha, S.; Chandrasekaran, S. *J. Org. Chem.* **1999**, *64*, 5841.
(c) Bert, F.; Bincoletto, S.; Donati, I.; Fontanive, G.; Fregonesea, M.; Benedetti, F. *Org. Biomol. Chem.* **2011**, *9*, 1987.
(d) Barbero, M.; Bazzi, S.; Cadamuro, S.; Dughera, S.; Magistris, C.; Smarra, A.; Venturello, P. *Org. Biomol. Chem.* **2011**, *9*, 2192.

(Zhao, C.)